THE UNIVERSITY *of* EDINBURGH

Edinburgh Research Explorer

High pressure synthesis of late rare earth RFeAs(O,F) superconductors; R = Tb and Dy

Citation for published version:

Bos, J-WG, Penny, GBS, Rodgers, JA, Sokolov, DA, Huxley, AD & Attfield, JP 2008, 'High pressure synthesis of late rare earth RFeAs(O,F) superconductors; R = Tb and Dy', *Chemical Communications*, vol. 2008, no. 31, pp. 3634-3635. <https://doi.org/10.1039/b808474b>

Digital Object Identifier (DOI):

[10.1039/b808474b](https://doi.org/10.1039/b808474b)

Link:

[Link to publication record in Edinburgh Research Explorer](#)

Document Version:

Peer reviewed version

Published In:

Chemical Communications

Publisher Rights Statement:

Copyright © 2008 by the Royal Society of Chemistry. All rights reserved.

General rights

Copyright for the publications made accessible via the Edinburgh Research Explorer is retained by the author(s) and / or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

The University of Edinburgh has made every reasonable effort to ensure that Edinburgh Research Explorer content complies with UK legislation. If you believe that the public display of this file breaches copyright please contact openaccess@ed.ac.uk providing details, and we will remove access to the work immediately and investigate your claim.

Post-print of a peer-reviewed article published by the Royal Society of Chemistry.

Published article available at: <http://dx.doi.org/10.1039/B808474B>

Cite as:

Bos, J-W. G., Penny, G. B. S., Rodgers, J. A., Sokolov, D. A., Huxley, A. D., & Attfield, J. P. (2008). High pressure synthesis of late rare earth RFeAs(O,F) superconductors; R = Tb and Dy. *Chemical Communications*, 2008(31), 3634-3635.

Manuscript received: 19/05/2008; Accepted: 06/06/2008; Article published: 30/06/2008

High pressure synthesis of late rare earth RFeAs(O,F) superconductors; R = Tb and Dy †

Jan-Willem G. Bos,^{1,2} George B. S. Penny,^{1,2} Jennifer A. Rodgers,^{1,2} Dmitry A. Sokolov,^{1,3}

Andrew D. Huxley^{1,3} and J. Paul Attfield^{1,2,*}

^[1]Centre for Science at Extreme Conditions, University of Edinburgh, King's Buildings, Mayfield Road, Edinburgh, EH9 3JZ, UK.

^[2]EaStCHEM, School of Chemistry, Joseph Black Building, University of Edinburgh, West Mains Road, Edinburgh, EH9 3JJ, UK.

^[3]SUPA, School of Physics, University of Edinburgh, King's Buildings, Mayfield Road, Edinburgh, EH9 3JZ, UK.

^[*]Corresponding author; e-mail: j.p.attfield@ed.ac.uk

Supporting information:

^[†]Electronic supplementary information (ESI) available: Plots of the fitted X-ray diffraction profile and resistivity for DyFeAsO_{0.9}F_{0.1}. See <http://dx.doi.org/10.1039/B808474B>

Abstract

New TbFeAs(O,F) and DyFeAs(O,F) superconductors with critical temperatures $T_c = 46$ and 45 K and very high critical fields, ≥ 100 T, have been prepared at 1100–1150 °C and 10–12 GPa, demonstrating that high pressure may be used to synthesise late rare earth derivatives of the recently reported RFeAs(O,F) (R = La–Nd, Sm, Gd) high temperature superconductors.

Main text

A breakthrough in high temperature superconductivity has recently occurred with the discovery that rare earth oxypnictides RFeAsO (first reported for R = La, Ce, Pr, Nd, Sm and Gd)^[1] can show critical temperatures surpassed only by the high- T_c cuprates. These materials have a tetragonal, layered crystal structure as depicted in the inset to Fig. 1. Superconductivity has been induced by the partial substitution of fluoride into the RO layers, which leads to electron doping (reduction of iron) in the electronically active FeAs slabs. The first report of superconductivity was in LaFeAsO_{1-x}F_x samples with T_c values up to 26 K,^[2] increasing to 43 K at 4 GPa pressure.^[3] Superconductivity has subsequently been induced in the other members of the RFeAsO series using fluoride doping, with ambient pressure T_c values of 41 K for R = Ce,^[4] 52 K for Pr^[5] and Nd,^[6] 43–55 K for Sm samples,^[7] and 36 K for Gd.^[8]

Figure 1. Rietveld fit to the X-ray diffraction profile of TbFeAsO_{0.9}F_{0.1}, with Bragg reflection markers shown below those for the minority phase TbAs. An additional impurity peak is observed at 38° 2θ. Refinement residuals are $R_{wp} = 2.63\%$, $R_p = 2.00\%$ and $\chi^2 = 1.64$ for 24 variables. Atom positions (x, y, z) and isotropic- U values; Tb ($\frac{1}{4}, \frac{1}{4}, 0.1447(4)$), 0.003(1) Å²; As ($\frac{1}{4}, \frac{1}{4}, 0.6654(6)$), 0.009(2) Å²; Fe ($\frac{3}{4}, \frac{1}{4}, \frac{1}{2}$), 0.003(1) Å²; O,F ($\frac{3}{4}, \frac{1}{4}, 0$), 0.07(1) Å². The inset shows the structure.

High pressure and temperature synthesis is known to stabilise many late rare earth analogues of early rare earth solid compounds. This approach has been used to explore the stabilisation of TbFeAs(O,F) and DyFeAs(O,F) phases. Polycrystalline samples of nominal compositions $R\text{FeAsO}_{1-x}\text{F}_x$ ($R = \text{Tb, Dy}$; $x = 0, 0.1, 0.2$) were synthesised from stoichiometric amounts of RAs, Fe_2O_3 , FeF_2 and Fe. TbAs and DyAs were prepared from a stoichiometric mixture of the elements heated to 500 °C for 5 h and then 900 °C for 10 h in an evacuated quartz tube. All chemicals were obtained from Sigma Aldrich with at least 99.9% purity. The reactants were mixed and ground in a glove box, sealed in a BN capsule, and subjected to pressures of 10 GPa ($R = \text{Tb}$) or 12 GPa ($R = \text{Dy}$) using a Walker two-stage multianvil within a 1000 tonne press. Once at pressure, the samples were heated to 1100–1150 °C in 10 min, held at this temperature for 20 min, and then quenched to room temperature, followed by release of the pressure. The products were dense, black, sintered polycrystalline pellets and were characterised by powder X-ray diffraction, (Fig. 1) magnetisation (Fig. 2) and resistivity (Fig. 3) measurements.†

Figure 2. → Ac magnetic volume susceptibility vs. temperature plot for $R\text{FeAs}(\text{O},\text{F})$ ($R = \text{Tb, Dy}$) samples; $\chi' = -1$ corresponds to full diamagnetism.

← **Figure 3.** Temperature dependence of the resistivity of $\text{TbFeAsO}_{0.8}\text{F}_{0.2}$. The lower inset shows the superconducting transitions in zero and 9 T fields, and the upper inset shows the onset (0%) of the transition and the zero resistance point (100%) indicative of the upper critical field (B_{c2}). The coherence length is obtained from the fit to the latter values.

The R = Tb samples all contained the tetragonal RFeAsO type phase with traces of TbAs (Fig. 1). The synthesis of DyFeAsO was unsuccessful but DyFeAsO_{1-x}F_x phases were obtained for $x = 0.1$, and 0.2 with DyAs also present.^[1] All four fluoride-doped samples show both magnetic and resistive superconducting transitions, with critical temperatures of 40–46 K. Fig. 2 shows that the samples are bulk superconductors, with some reduction from the theoretical full diamagnetism due to the presence of impurities and field penetration into small grains. The refined lattice parameters and T_c values are shown in Table 1. We also synthesised a new TbFeAsO_{0.9} analogue of the reported oxygen-deficient RFeAsO_{0.85} superconductors at 10 GPa.^[9] This sample is superconducting with $T_c = 50$ K; further details will be reported elsewhere.

RFeAs(O,F)	$a/\text{\AA}$	$c/\text{\AA}$	Volume/$\text{\AA}^3$	$T_c(\chi_{\text{ons}})/\text{K}$	$T_c(\rho_{\text{mid}})/\text{K}$
TbFeAsO	3.8632(8)	8.322(3)	124.20(8)	—	—
TbFeAsO _{0.9} F _{0.1}	3.8634(3)	8.333(1)	124.38(3)	45.5	43.8
TbFeAsO _{0.8} F _{0.2}	3.860(2)	8.332(6)	124.2(2)	45.2	45.9
DyFeAsO _{0.9} F _{0.1}	3.8425(3)	8.2837(8)	122.30(3)	45.3	45.4
DyFeAsO _{0.8} F _{0.2}	3.8530(3)	8.299(1)	123.21(2)	43.0	43.0

Table 1. Cell parameters and volume and T_c values from the onset of diamagnetism and the resistive transition mid-point for RFeAs(O,F)

The resistivities show clear transitions to zero resistance (Fig. 3) with a smooth negative curvature of the resistivity in the normal state. This differs from data for other superconducting oxypnictides that appear to show higher temperature transitions.^[10] Changes in this behaviour are theoretically predicted to be very sensitive to competing energy scales controlling the physics of these materials.^[11] The resistive transition width increases with magnetic field for all samples as observed in other oxypnictides,^[12] consistent with a large anisotropy of the critical field, reflecting the structural and electronic anisotropy. The upper critical field B_{c2} increases to 9 T in <2 K below T_c for TbFeAsO_{0.8}F_{0.2} (Fig. 3 upper inset) and, in BCS (Bardeen–Cooper–Schrieffer) theory neglecting paramagnetic limitation, this corresponds to B_{c2} exceeding 100 T at low temperatures. Taking the onset of the transition to give the upper critical field for superconductivity in the most favourable direction (parallel to the FeAs planes) an upper estimate for the superconducting coherence length perpendicular to this direction is 13(1) Å. This corresponds to the geometric mean of the in-plane and out-of-plane coherence lengths. Given that the anisotropy is large, the out-of-plane value is therefore likely to be significantly smaller than the FeAs layer spacing, demonstrating that superconductivity is strongly 2-dimensional. The zero resistance transition field has a noticeably more marked upward curvature at low field than observed for the transition onset. This might reflect a transition to a vortex liquid state, which is well known in the high- T_c copper oxide superconductors, or be an indication of multiple band superconductivity as established in MgB₂.^[13]

The T_c values of the $\text{RFeAsO}_{1-x}\text{F}_x$ ($\text{R} = \text{Tb, Dy}, x = 0.1, 0.2$) samples do not differ greatly and there is no clear trend in the lattice parameters with x , showing that the actual range of doping may be more limited than in the nominal compositions. Further work will be needed to determine the precise range of x and optimise phase purity. It is notable that the T_c values of TbFeAs(O,F) and DyFeAs(O,F) are comparable to those of the early $\text{R} = \text{Ce, Pr, Nd, Sm}$ materials. The lower value of 36 K reported for GdFeAs(O,F) ^[8] suggested that superconductivity might be suppressed as the rare earth size decreases, but the present results show that the superconducting properties change little between Ce and Dy. It will be important to explore further RFeAs(O,F) superconductors of the heavy rare earths to discover how superconductivity develops across the entire series.

‡ Powder X-ray diffraction data were collected on a Bruker AXS D8 diffractometer using $\text{Cu K}\alpha_1$ radiation. Data were recorded at $10 \leq 2\theta \leq 100^\circ$ with a step size of 0.007° for Rietveld analysis. The ac magnetic susceptibility was measured from 3 to 50 K with a field of 0.5 Oe oscillating at 117 Hz using a Quantum Design superconducting quantum interference device magnetometer. The electrical resistivity was measured by the conventional four-probe method between 1.7 and 300 K using a Quantum Design physical property measurement system.

References

- [1] P. Quebe, L. J. Terbuchte and W. Jeitschko, *J. Alloys Compd.*, 2000, **302**, 70.
- [2] Y. Kamihara, T. Watanabe, M. Hirano and H. Hosono, *J. Am. Chem. Soc.*, 2008, **130**, 3296.
- [3] H. Takahashi, K. Igawa, K. Arii, Y. Kamihara, M. Hirano and H. Hosono, *Nature*, 2008, **453**, 376.
- [4] G. F. Chen, Z. Li, D. Wu, G. Li, W. Z. Hu, J. Dong, P. Zheng, J. L. Luo and N. L. Wang, *Phys. Rev. Lett.*, 2008, **100**, 247002.
- [5] Z.-A. Ren, J. Yang, W. Lu, W. Yi, G.-C. Che, X.-L. Dong, L.-L. Sun and Z.-X. Zhao, unpublished results, arXiv:0803.4283.
- [6] Z.-A. Ren, J. Yang, W. Lu, W. Yi, X.-L. Shen, Z.-C. Li, G.-C. Che, X.-L. Dong, L.-L. Sun, F. Zhou and Z.-X. Zhao, *Europhys. Lett.*, 2008, **82**, 57002.
- [7] X. H. Chen, T. Wu, G. Wu, R. H. Liu, H. Chen and D. F. Fang, *Nature*, 2008, **453**, 761; Z.-A. Ren, W. Lu, J. Yang, W. Yi, X.-L. Shen, Z.-C. Li, G.-C. Che, X.-L. Dong, L.-L. Sun, F. Zhou and X.-X. Zhao, *Chin. Phys. Lett.*, 2008, **25**, 2215; R. H. Liu, G. Wu, T. Wu, D. F. Fang, H. Chen, S. Y. Li, K. Liu, Y. L. Xie, X. F. Wang, R. L. Wang, L. Ding, C. He, D. L. Feng and X. H. Chen, unpublished results, arXiv:0804.2105.
- [8] P. Cheng, L. Fang, H. Yang, X. Zhu, G. Mu, H. Luo, Z. Wang and H.-H. Wen, *Sci. China, Ser. G*, 2008, **51**, 719.
- [9] Z.-A. Ren, G.-C. Che, X.-L. Dong, J. Yang, W. Lu, W. Yi, X.-L. Shen, Z.-C. Li, L.-L. Sun, F. Zhou and Z.-X. Zhao, *Europhys. Lett.*, 2008, **83**, 17002.
- [10] G. F. Chen, Z. Li, D. Wu, J. Dong, G. Li, W. Z. Hu, P. Zheng, J. L. Luo and N. L. Wang, *Chin. Phys. Lett.*, 2008, **25**, 2235.
- [11] K. Haule and G. Kotliar, unpublished results, arXiv:0805.0722.
- [12] F. Hunte, J. Jaroszynski, A. Gurevich, D. C. Larbalestier, R. Jin, A. S. Sefat, M. A. McGuire, B. C. Sales, D. K. Christen and D. Mandrus, *Nature*, 2008, **453**, 903.
- [13] V. H. Dao and M. E. Zhitomirsky, *Eur. Phys. J. B*, 2005, **44**, 183.