THE UNIVERSITY *of* EDINBURGH

Edinburgh Research Explorer

In Situ Versus Isolated Zinc Catalysts in the Selective Synthesis of Homo and Multi-block Polyesters

Citation for published version:

Gruszka, W, Walker, LC, Shaver, MP & Garden, JA 2020, 'In Situ Versus Isolated Zinc Catalysts in the Selective Synthesis of Homo and Multi-block Polyesters', *Macromolecules*.
<https://doi.org/10.1021/acs.macromol.0c00277>

Digital Object Identifier (DOI):

[10.1021/acs.macromol.0c00277](https://doi.org/10.1021/acs.macromol.0c00277)

Link:

[Link to publication record in Edinburgh Research Explorer](#)

Document Version:

Peer reviewed version

Published In:

Macromolecules

General rights

Copyright for the publications made accessible via the Edinburgh Research Explorer is retained by the author(s) and / or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

The University of Edinburgh has made every reasonable effort to ensure that Edinburgh Research Explorer content complies with UK legislation. If you believe that the public display of this file breaches copyright please contact openaccess@ed.ac.uk providing details, and we will remove access to the work immediately and investigate your claim.

In Situ versus Isolated Zinc Catalysts in the Selective Synthesis of Homo and Multi-block Polyesters

Weronika Gruszka,^a Leah C. Walker,^a Michael P. Shaver,^{b, c} Jennifer A. Garden^{*a}

^a EaStCHEM School of Chemistry, University of Edinburgh, EH9 3FJ, UK

^b School of Natural Sciences, Department of Materials, The University of Manchester,
Manchester, M13 9PL, UK

^c Henry Royce Institute, The University of Manchester, Oxford Road, Manchester, M13 9PL,
UK

Dedicated to Prof. Robert E. Mulvey on the occasion of his 60th birthday.

Table of Contents

For Table of Contents use only.

Abstract

The *in situ* generation of metal-alkoxide complexes is a common initiation method in cyclic ester ring-opening polymerisation. Yet this method is often a “black box”, where the species so generated are assumed to be the same as the isolated complex. We now demonstrate that an isolated Zn-benzoxide catalyst gives a remarkable reactivity enhancement in lactide ROP, with k_{obs} values 10 times higher than the *in situ* generated analogue. The dinuclear zinc catalyst, built using the Trost ProPhenol ligand, offers these excellent activities and good control over homopolymerisation of multiple cyclic esters (*rac*-lactide, ϵ -caprolactone and *rac*- β -butyrolactone). The stability of this isolated catalyst also controls chain exchange and back-biting, allowing for one-pot synthesis of multi-block polyesters without loss of activity, selectivity and control. To the best of our knowledge, this is the first catalyst reported for the selective preparation of block terpolymers of ϵ -CL, *rac*-LA and *rac*- β -BL.

Introduction

The ring-opening polymerisation (ROP) of cyclic esters is an efficient route to polyesters such as poly(lactic acid) (PLA), poly(ϵ -caprolactone) (PCL) and poly(3-hydroxybutyrate) (PHB). These and other aliphatic polyesters offer improved degradation rates compared to many conventional polymers and a wide range of applications including biomedical devices,¹ electronics and packaging.² Careful control over the polymer microstructure is key to tuning the material properties and requires the use of an appropriate catalyst; some of the most effective are homogeneous organometallic complexes. Many monometallic complexes, including (salen)Al,^{3,4} [amino(trisphenolato)]Zr⁵ and (phosphasalen)Y,⁶ have accessed high catalyst activities, broad monomer scope and excellent control over the polymer stereochemistry.

Bimetallic catalysts have shown exciting promise in cyclic ester ROP, and bis-Zn complexes have been particularly successful (Fig. 1).^{7–9} Zinc is an attractive metal for lactide (LA) ROP, as it is inexpensive, colourless, non-redox active and non-toxic; the lack of toxicity is strongly desirable for the use of PLA in biomedical applications.¹⁰ To date, the most active bis-Zn catalyst reported for LA ROP is based on a macrocyclic bis(imino)diphenylamido ligand (Fig. 1, top right), where the activity is enhanced by close metal-metal proximity.¹¹ This mirrors studies in CO₂/epoxide ring-opening copolymerisation (ROCOP), which shares several mechanistic features with cyclic ester ROP (monomer coordination and nucleophilic attack), and where short intermetallic distances (3–8 Å) often give enhanced catalyst activities.^{12–14} Notably, [(bis(imino)diphenylamido)ZnN(SiMe₃)₂] remains highly effective at low catalyst loadings.¹¹ This opens up access to high M_n PLA and indicates that dinucleating ligands offer a method of maintaining metal-metal cooperativity at low catalyst loadings.^{9,15} Studies have suggested that the catalyst solution-state structure (aggregation state and ligand conformation) can influence the

catalytic activity in ROP.^{11,15–18} However, many organometallic precursors are still converted to the active metal-alkoxide catalyst *in situ* without investigation of the impact upon the structure and reactivity.

Figure 1. Highly active bis-Zn catalysts for LA ROP.

Metal-based catalysts can selectively form block copolymers that self-assemble into materials with superior properties and applications including thermoplastic elastomers, adhesives and lithography.¹⁹ Block copolymers of ϵ -CL/LA have applications as drug delivery agents and nerve guides,^{20,21} combining the drug permeability, elasticity and thermal properties of PCL with the mechanical properties and degradation rate of PLA ($t_{1/2}$ *in vivo* = a few weeks; PCL, $t_{1/2}$ *in vivo* = 1 year).^{22–25} Copolymerisation of LA and β -BL can give materials with improved mechanical properties, higher degradation rates and lower melting points than naturally-occurring PHB, yet examples of selective catalysts for PLA-PHB block copolymers remain rare.^{26–31} However, sequential addition of D-LA, *rac*- β -BL and L-LA was previously used by Mehrkhodavandi *et al.* to generate triblock poly(lactic acid-*block-rac*- β -butyrolactone-*block*-lactic acid) copolymers using dinuclear indium catalysts.³² Catalysts based on Al, La, Sm, Sn, Ti and Zr have been reported

for selective ϵ -CL/LA copolymerisation, albeit with relatively long reaction times.^{33–38} Zinc catalysts remain underexplored despite the excellent activities and selectivities demonstrated for cyclic ester homopolymerisation. The efficient, controlled one-pot synthesis of di- and tri-block copolymers *via* ROP opens up a broad range of degradable materials with tuneable properties, yet remains a synthetic challenge, which is partly due to transesterification reactions that can randomise the polymer structure. Here, we explore a bimetallic zinc-benzoxide complex, based on a commercially available dinucleating ligand scaffold, for the selective preparation of homopolymers and block copolymers.

Results and Discussion

Complex **LZn₂Et** (Scheme 1) is an interesting catalyst precursor for cyclic ester ROP as the close metal-metal proximity facilitated efficient CO₂/epoxide ROCOP.³⁹ While **LZn₂Et** has catalysed enantioselective organic transformations,^{40,41} it is typically generated and used *in situ* without full characterisation. To probe the solution state structure, we prepared **LZn₂Et** through **LH₃** deprotonation with Et₂Zn (2 equiv.) and characterised the product by NMR spectroscopy, mass spectrometry and elemental analysis (refer to ESI). ¹H NMR spectroscopic analysis highlights the asymmetry of **LZn₂Et**, suggesting two inequivalent zinc sites where one zinc bears a highly nucleophilic/Brønsted basic ethyl group and the other forms a Zn-THF Lewis acid/base adduct (Fig S1).^{39,42–44} These two features are key in ROP based on the coordination-insertion mechanism.^{4,45}

Whilst **LZn₂Et** was inactive towards *rac*-lactide (*rac*-LA) ROP under the conditions tested (Table 1), addition of benzyl alcohol initiator (BnOH, 1 equiv.) gave excellent conversions of 87% after 10 minutes (60 °C in toluene solvent). Reaction between **LZn₂Et** and 1 eq. BnOH in toluene-

d_8 was monitored by ^1H NMR spectroscopy, which indicated the rapid loss of ethyl resonances at 1.94 and 1.13 ppm and the formation of ethane gas (0.81 ppm, Fig. S3 and S10). The polymerisation was relatively well-controlled, displaying first-order kinetics in monomer and a linear relationship between M_n and monomer conversion, as well as narrow to moderate dispersities ($D = 1.07 - 1.22$). However, there was some discrepancy between the observed and calculated M_n values. In addition to the expected α -benzoxy, ω -hydroxy end-capped polymer chains, MALDI-ToF analysis showed a second series featuring ligand end-groups in the late stages of the polymerisation.

Scheme 1. Synthesis and reactivity of LZn_2Et and LZn_2OBn towards *rac*-LA ROP.

The polymerisation was significantly faster in toluene solvent compared to THF. While 21% conversion was obtained after 1 hour in THF, 79% conversion took just 7 minutes in toluene (Table 1). DOSY analysis suggested that this enhanced activity was not caused by differences in the catalyst aggregation state, as LZn_2Et was monomeric in both d_8 -THF and d_8 -toluene (Fig S6-S7). However, DOSY analysis suggests that in neat THF the solvent was in coordinative equilibrium with LZn_2Et , whereas THF was non-coordinated in d_8 -toluene. These observations suggest that excess THF may block LA coordination and reduce the rate of ring-opening.⁴⁶ Supporting this hypothesis, addition of 2 and 100 equivalents of THF per dinuclear catalyst significantly decreased the conversion after 10 min, from 87% (neat toluene), to 80% (2 equiv. THF), down to 58% (100

equiv. THF). Toluene solvent presents a challenge for LA solubility, which was addressed by “pre-stirring” LA in toluene at 60 °C prior to the addition of **LZn₂Et** and BnOH (refer to ESI for details). Unfortunately, **LZn₂OBn** did not exhibit stereocontrol for *rac*-LA ROP, resulting in atactic PLA ($P_s = 0.48$ -0.50, Table 1). Polymerisation of L-LA led to isotactic PLA, albeit at approximately half the rate observed for *rac*-LA and with a significant induction period of approximately 7.5 min, which was not detected for *rac*-LA (Figure S12). This difference in initiation implies that the chiral ligand of **LZn₂OBn** (*S,S*) is structurally arranged with a preference for D-LA coordination and insertion to initiate the polymerisation.^{8,47,48} While the difference in propagation rates could imply that **LZn₂OBn** prefers polymerisation of D-LA, the production of an atactic polymer combined with a lack of transesterification (determined by MALDI-ToF analysis) suggests that other factors are also important such as solubility differences between *rac*-LA and L-LA. The induction period observed for L-LA may arise from structural rearrangement of the ligand to facilitate coordination, which may influence the catalyst geometry and thus activity.

Table 1. ROP of *rac*-LA catalysed by *in situ* generated **LZn₂OBn**:

Ent-ry	Time (min)	Conv ^a (%)	$M_{n,obs}^b$ (Da)	$M_{n,calc}^c$ (Da)	$\bar{D}^b$	P_s^d
1 ^e	60	21	-	-	-	-
2 ^e	90	50	-	-	-	-
3 ^f	10	0	-	-	-	-
4	2.5	35	2000	5100	1.18	0.48
5	5	56	4500	8100	1.22	0.48
6	7	79	7100	11400	1.08	-

7	10	87	8100	12500	1.07	0.50
8	11	89	8400	12800	1.09	-
9 ^g	10	58	3400	8400	1.11	0.52
10 ^h	10	80	5200	11500	1.07	-

[LA] = 1 M in toluene. *rac*-LA and complex **LZn₂Et** pre-stirred separately for 3 min in toluene at 60 °C before mixing and initiation with BnOH. ^a Conversion calculated using ¹H NMR spectroscopy. ^b $M_{n,obs}$ and $\bar{D}$ determined by gel permeation chromatography using polystyrene standards in THF. Values corrected by Mark Houwink factor (0.58).⁴⁹ ^c $M_{n,calc}$ of polymers calculated from the monomer conversion $M_{n,calc} = M_0 \times ([M]/[I]) \times \text{conversion}$ assuming 1 chain per catalyst centre. ^d Determined by homodecoupled ¹H NMR spectroscopy. ^e [*rac*-LA] = 1 M in THF. *Rac*-LA and **LZn₂Et** weighed out into the same vial and not pre-stirred separately for 3 min before initiation with BnOH. ^f No BnOH used. ^g 100 eq. of THF added with respect to **LZn₂Et**. ^h 2 eq. of THF added with respect to **LZn₂Et**.

To address the low M_n values obtained using *in situ* generated **LZn₂OBn**, this complex was isolated, characterised and tested in *rac*-LA ROP. Unlike the **LZn₂Et** precursor, ¹H NMR spectroscopic analysis suggests **LZn₂OBn** is symmetrical, attributed to OBn bridging two metal centres (Figure S3).^{50–56} Intriguingly, the isolated complex was an order of magnitude more active than the *in situ* analogue (isolated **LZn₂OBn**, $k_{obs} = 3.5 \times 10^{-2} \text{ s}^{-1}$; *in situ* **LZn₂OBn**, $k_{obs} = 3.6 \times 10^{-3} \text{ s}^{-1}$) under identical reaction conditions (toluene solvent, 60 °C). Isolated **LZn₂OBn** also displayed good catalytic activities at lower catalyst loadings of 0.2 mol% and 0.1 mol%, producing PLA with M_n values above 50, 000 g mol⁻¹ (Entry 10, Table 2). The isolated catalyst is amongst the most active zinc complexes reported for LA ROP (refer to Table S3 for details),^{8,9,11} and displays good control over the M_n and dispersity (Table 2). The observed activity differences may originate from slower initiation with *in situ* generated **LZn₂OBn**, possibly from incomplete reaction between **LZn₂Et** and BnOH in the presence of LA. Notably, unreacted BnOH could act as a chain-transfer agent, resulting in narrower $\bar{D}$ values than observed with isolated **LZn₂OBn**. However, careful inspection of the M_n data suggests that this is not the full explanation. With isolated **LZn₂OBn**, the observed M_n values are slightly higher than the calculated values, at both room temperature and 60 °C, suggesting that not all of the catalyst is active (Tables S2 and 2). In

contrast, the M_n values from the *in situ* catalyst are lower than expected. Perhaps the aggregation state of the catalyst is also important? To answer this question, **LZn₂OBn** was investigated using DOSY analysis. While **LZn₂Et** is monomeric in *d*₈-toluene, **LZn₂OBn** is a dimer (refer to ESI for details). These results suggest *in situ* generation of metal-alkoxy catalysts can influence the aggregation state and therefore the catalyst activity. It is plausible that Lewis basic *rac*-LA could reduce the aggregation state of the isolated **LZn₂OBn** dimer to a monomer. As the rapid reaction between **LZn₂OBn** and *rac*-LA prevented DOSY investigations into monomer coordination and aggregation state, γ -valerolactone (γ -VL) was used as this cyclic ester is challenging to polymerise.⁵⁷ Instead of decreasing the aggregation state of **LZn₂OBn**, γ -VL increased the aggregation state, suggesting that cyclic esters can bridge between metal centres and modify the aggregation state (refer to ESI for details). Whilst *in situ* alcoholysis of an organometallic precursor is a popular method of initiating ROP, there are surprisingly few accounts of the difference between *in situ* generation vs. isolation of the catalyst. Ejfler *et al.* reported that isolated dimers, **[L'ZnOR]₂** (L' = aminonaphtholate), were less active and controlled than the *in situ* generated analogues.¹⁸ This was attributed to the formation of different catalyst structures when alcoholysis of **[L'ZnEt]₂** was performed in the presence of LA, with complex dynamic equilibria influenced by the order of addition and the nature of the alcohol (methanol/BnOH/1-phenylethanol) and ligand. These studies highlight the importance of understanding of the catalyst solution-state chemistry to access improved activities and polymerisation control.

The MALDI data reveals an α -benzoxo, ω -hydroxy end-capped series at low LA conversion, however, some ligand end groups are also observed at high conversions. Ligand end groups were also reported by Chakraborty *et al.* with a Trost ligand zirconium complex, **(LH)₂Zr**, in the absence of an alcohol initiator.⁵⁸ These observations suggest that with **LZn₂OBn**, the ligand

becomes non-innocent in the late stages of the reaction, where transesterification becomes competitive with propagation. It seems likely that transesterification occurs *via* cleavage of the Zn-O(ligand) bond, which undergoes nucleophilic attack upon an ester carbonyl of the growing polymer chain (Scheme S1). As the polymer chain grows, the steric strain of forming cyclic products decreases, which may favour transesterification. The analogous ethyl complex, **LZn₂Et**, is inactive towards LA ROP in the absence of BnOH, suggesting that Zn-O(ligand) groups cannot initiate ROP. DOSY analysis of the quenched PLA oligomer revealed that the ligand and PLA chains have identical diffusion coefficients (Fig. S20). This suggests that transesterification reactions promoted by Zn-O(ligand) groups can occur even with oligomeric chains at high conversions. However, it cannot be unequivocally ruled out that the identical diffusion coefficients arise from similarity between the catalyst (870 g mol⁻¹) and oligomeric PLA (monomer = 144 g mol⁻¹). Nozaki *et al.* reported that dimeric Zn-Et complex [Et₂Zn₂((*S*)-diphenyl(pyrrolidin-2-yl)methanol)] can initiate CO₂/epoxide ROCOP through CO₂ insertion into the Zn-O(ligand) bond.⁵⁹ In contrast, the addition of ethanol generated a Zn-OEt complex that efficiently initiated CO₂/epoxide ROCOP, leading to enhanced control and narrow dispersities. The improved initiation efficiency was attributed to a lack of chelate stabilisation for the Zn-OEt initiating group. A similar effect may occur with **LZn₂Et/LZn₂OBn**, where increased stabilisation due to chelation prevents the Zn-O(ligand) groups from initiating ROP, in spite of the apparent similarity in p*K*_a between the benzoxide initiator and the substituted benzoxide groups of the Trost ligand.

Table 2. ROP of *rac*-LA with isolated **LZn₂OBn**:

Ent- ry	Time (min)	Conv ^a (%)	<i>M</i> _{n,obs} ^b (Da)	<i>M</i> _{n,calc} ^c (Da)	<i>Đ</i> ^b	% active cat.
1 ^{d,e}	0.08	38	8600	5500	1.23	64
2 ^{d,f}	0.33	66	12000	9500	1.42	80
3	0.67	74	13100	10700	1.42	82
4 ^{d,g}	1.25	92	16400	13300	1.36	81
5	2	99	19900	14300	1.35	72
6 ^h	4	91	29300	26200	1.20	45
7 ⁱ	20	71	49100	51200	1.09	21
8 ^{i,j}	5	82	46700	59100	1.08	25
9 ^k	20	24	26000	34600	1.06	13
10 ^{j,k}	10	43	52300	62000	1.12	12

100:1 [LA]:[**LZn₂OBn**], [LA] = 1 M in toluene, 60 °C. LA and **LZn₂OBn** pre-stirred separately for 3 min in toluene at 60 °C before mixing. ^a Conversion calculated using ¹H NMR spectroscopy. ^b *M*_{n,obs} and *Đ* determined by gel permeation chromatography using polystyrene standards in THF. Values corrected by Mark-Houwink factor (0.58).⁴⁹ ^c *M*_{n,calc} of polymers calculated from the monomer conversion $M_{n,calc} = M_0 \times ([M]/[I]) \times \text{conversion}$ assuming 1 chain per catalyst centre. ^d Determined by homodecoupled ¹H NMR spectroscopy. ^e *P*_s = 0.48 ^f *P*_s = 0.52 ^g *P*_s = 0.50 ^h 200:1 [LA]:[**LZn₂OBn**]. ⁱ 500:1 [LA]:[**LZn₂OBn**]. ^j 120 °C. ^k 1000:1 [LA]:[**LZn₂OBn**].

Based on the activities and control observed with LA, **LZn₂OBn** was also tested for ε-CL ROP. Isolated **LZn₂OBn** displayed excellent catalytic activity (*k*_{obs} = 5.3 × 10⁻³ s⁻¹, Fig. 2, left), and is one of the few bis-Zn catalysts reported for ε-CL ROP. Other bis-Zn systems include an anilido-aldimine zinc-alkyl complex reported by Mu *et al.*, which converts 98 % of ε-CL in 1 min at 70°C ([ε-CL]:[cat]:[I] = 100:1:2; [ε-CL] = 3 M in toluene),⁶⁰ and a dinuclear amido zinc-alkyl complex employed by Chakraborty and Chen to form 62 % yield of PCL after 2 h at room temperature ([ε-CL]:[cat]:[I] = 200:1:0; [ε-CL] = 1 M in toluene).⁶¹ With both *in situ* generated and isolated

LZn₂OBn, the initiation of ϵ -CL ROP was faster than that observed for *rac*-LA, which was attributed to the improved solubility of ϵ -CL in toluene and the high ring strain of ϵ -CL. Rapid alcoholysis, initiation and early propagation followed by a slower first-order propagation has been reported for other ROP systems.^{48,62} The similar activities of the *in situ* generated and isolated catalysts could arise from the improved solubility and stronger Lewis basicity of ϵ -CL compared to LA, as suggested by the FT-IR carbonyl shifts [$\nu(\text{C=O}) = 1770 \text{ cm}^{-1}$ for LA; $\nu(\text{C=O}) = 1732 \text{ cm}^{-1}$ for ϵ -CL].⁶³ Therefore, ϵ -CL may reduce the aggregation state of isolated **LZn₂OBn** catalyst to a monomer, i.e. the same species as when **LZn₂OBn** is formed *in situ*. The slower propagation rate for ϵ -CL may also give the catalyst more time to rearrange in solution upon monomer addition. Complex **LZn₂OBn** also demonstrated good polymerisation control, with narrow to moderate dispersities and good agreement between the observed and calculated M_n (Fig. 2, right).

MALDI-ToF analysis shows only α -benzoxy, ω -hydroxy end-capped PCL. The absence of ligand end groups supports the hypothesis that the Zn-O(ligand) bonds do not initiate ROP; instead, the ligand becomes involved in transesterification in the late stages of the reaction. With ϵ -CL as the monomer, there is a greater separation between the Zn-O(ligand) unit and the first carbonyl group on the growing polymer chain, disfavoring nucleophilic attack (Scheme S1).

Figure 2. LHS: Plots of $\ln([\epsilon\text{-CL}]_0/[\epsilon\text{-CL}]_t)$ vs. time (min) for the ROP of ϵ -CL with *in situ* generated and isolated **LZn₂OBn** (100 eq. of ϵ -CL in toluene, $[\epsilon\text{-CL}] = 1 \text{ M}$, 60°C). RHS:

Comparison between experimental and calculated M_n values and dispersity values at increasing conversions of ϵ -CL in presence of isolated **LZn₂OBn**.

Catalyst **LZn₂OBn** also displayed good activities for *rac*- β -BL ROP. Optimising the reaction conditions showed that the highest catalytic activities were observed under neat conditions, which also gave improved stereocontrol and molecular weight control compared to reactions performed in toluene (Figure 3, Table S4). It is difficult to draw comparisons between the theoretical and experimental (SEC) M_n values for PHB, as no reliable correction factor has been reported and SEC analysis of higher molecular weight PHB is known to be problematic.⁶⁴ Similarly to ϵ -CL ROP, the initiation was faster than propagation, particularly in toluene, which was attributed to the rapid dissolution of *rac*- β -BL. A maximum conversion of 60% was reached, which is attributed to the polymerisation/depolymerisation equilibrium under the conditions tested. Within *rac*- β -BL ROP, there are a limited number of catalysts that combine speed with M_n and tacticity control.⁶⁵ In nature, PHB produced by bacteria is isotactic with all stereocentres in the *R* configuration, resulting in high crystallinity and low thermostability and making this polymer industrially irrelevant.^{66,67} Generation of syndiotactic-enriched PHB therefore opens up an exciting possibility of preparing materials with novel properties. Syndiotactic control has been achieved using complexes of La (P_s = 0.86), Sc (P_s = 0.60),⁶⁴ Sn (P_s = 0.70),^{68,69} and Y (P_s = 0.94, 0.87).^{64,70} To the best of our knowledge, **LZn₂OBn** is the first zinc-based catalyst to generate PHB with syndiotactic control, with P_s values in the range 0.65-0.70.⁷¹⁻⁷⁵

Similar to PLA, MALDI-ToF analysis of PHB revealed α -benzoxo, ω -hydroxy end-capped chains, with a second series possibly featuring ligand end groups at high conversions. This might suggest that transesterification with the ligand occurs in the late stages of *rac*- β -BL ROP, as

propagation slows down. Importantly, the Zn-O(ligand) unit is closer to the adjacent PHB carbonyl group compared to PCL (refer to ESI for details), which presumably facilitates ligand reactivity. Elimination reactions to form crotonate or carboxy PHB end groups can be catalysed by $[(\text{BDI})\text{Zn}(\text{O}^i\text{Pr})]$,⁷² $\text{Al}(\text{O}^i\text{Pr})_3$ ⁷⁶ and tin-based catalysts.^{77–79} While MALDI-ToF analysis showed no evidence of crotonate or carboxy end groups, trace resonances of the crotonate groups were observed by ^1H NMR spectroscopy (5.81 and 7.00 ppm), suggesting that **LZn₂OBn** may promote elimination reactions (refer to ESI for further details). These findings agree with the M_n values determined by ^1H NMR spectroscopy (Table S4), which were approximately half the calculated M_n values.

Figure 3. LHS: Plots of $\ln([\beta\text{-BL}]_0/[\beta\text{-BL}]_t)$ vs. time (min) for *rac*-β-BL ROP with isolated **LZn₂OBn** (when in toluene: 100 eq. of *rac*-β-BL in toluene, $[\beta\text{-BL}] = 2.45 \text{ M}$). RHS: Plot of experimental M_n (SEC) and dispersity values vs. *rac*-β-BL conversion (%) (isolated **LZn₂OBn**, neat conditions, 60 °C).

As **LZn₂OBn** successfully initiated *rac*-LA, ε-CL and *rac*-β-BL ROP, the preparation of diblock copolymers was investigated. Firstly, **LZn₂OBn** was used in the rapid, selective and well-controlled synthesis of poly(ε-caprolactone-*block*-lactic acid) through a one-pot method with sequential monomer introduction. The order of addition was essential to selectively synthesise a

block copolymer; the PCL block had to be prepared first, followed by the addition of LA. This observation correlates with the reactivity ratios of LA and ϵ -CL, as well as previous studies with other catalysts.^{33–38} Similar sequential monomer addition strategies have also been employed to prepare di- to octa-stereoblocks of D-LA and L-LA.^{80,81} The block copolymer was characterised using GPC analysis, with an increase in M_n from 8100 g mol⁻¹ to 32900 g mol⁻¹ upon *rac*-LA addition (using uncorrected M_n values due to two different monomers, Fig. S41). DSC analysis gave single T_m (54.7 °C) and T_g (-61.3 °C) values, which match literature reports for PCL suggesting that no randomisation occurs (Fig. S42).^{82,83} The absence of T_m and T_g values for the PLA block was attributed to the amorphous nature and the overlap of the T_m and T_g values of PCL and PLA, respectively. DOSY analysis revealed a single diffusion coefficient for both the PCL and PLA blocks, suggesting that the two blocks are connected (Fig. S38). Providing further support for the formation of a block copolymer, ¹H NMR resonances were present for PCL and PLA blocks, with only trace resonances observed for the CL-LA linking units at 2.3 and 4.1 ppm (Fig. S39). The ¹³C NMR spectrum showed only resonances corresponding to the PCL and PLA blocks (Fig. S40).⁸⁴ In contrast, initial preparation of the PLA block followed by addition of ϵ -CL generated a random/gradient copolymer (Figure S43). The random/gradient copolymer structure was assigned from the ¹H NMR spectra based on the ratio between the block PLA/PCL resonances and the linkages between these blocks. The relative integrals of the CL-LA vs. CL-CL linkages were 1.00 vs. 0.63 irrespective of whether *rac*-LA was added first or simultaneously with ϵ -CL, suggesting a relatively weak gradient copolymer structure (refer to ESI for further details). This randomisation is attributed to the rate of transesterification becoming competitive with the rate of propagation; the rate of *rac*-LA ROP ($k_{\text{obs}} = 3.5 \times 10^{-2}$ g mol⁻¹) was approximately seven times faster than ϵ -CL ROP ($k_{\text{obs}} = 5.3 \times 10^{-3}$ s⁻¹) under identical reaction conditions (*vide supra*). When

starting with ϵ -CL followed by *rac*-LA, the faster propagation of *rac*-LA prevents transesterification, effectively suppressing this side reaction to enable the selective synthesis of block copolymers. There are some reports that living PLA* chains do not initiate ϵ -CL polymerisation, however this challenge has previously been overcome using aminodiol supported Ti-alkoxides, dimethyl(salicylaldiminato)Al complexes and an *in situ* generated (diphenolate)Al-alkoxide complex to selectively generate di- and triblock copolymers.^{37,85,86} To the best of our knowledge, **LZn₂OBn** is the fastest and most controlled catalyst reported for the selective production of poly(ϵ -caprolactone-*block*-lactic acid).^{33–38} The polymerisation reached completion in just 7 minutes (PCL block, 50 equivalents ϵ -CL, 93% conversion in 5 minutes; PLA block, 50 equivalents *rac*-LA, 95% conversion in 2 minutes) with narrow *D* (1.1). In contrast, other catalysts often require prolonged reaction times (1–96 h, albeit under a range of different reaction conditions) and typically generate poly(ϵ -caprolactone-*block*-lactic acid) with broader dispersities (1.2–1.8).^{33–38}

To selectively prepare poly(β -butyrolactone-*block*-lactic acid) in one-pot, a similar strategy was exploited, beginning with *rac*- β -BL ROP followed by *rac*-LA ROP. The resultant polymer was identified as poly(*rac*- β -butyrolactone-*block*-lactic acid) on the basis of DOSY studies, GPC analysis and ¹H NMR spectroscopic analysis (Fig. S50 – S52). Reversing the order of monomer addition also generated poly(*rac*- β -butyrolactone-*block*-lactic acid) with good control, demonstrating that *rac*- β -BL ROP can be initiated by a living PLA* chain. Unfortunately, the selective one-pot synthesis of block poly(ϵ -caprolactone-*block*-*rac*- β -butyrolactone) was unsuccessful, independent of whether the PCL or PHB block was prepared first. Both GPC analysis and DOSY studies suggested that PCL and PHB homopolymers were produced (Fig. S44

– S47), which was attributed to the slower propagation of ϵ -CL and *rac*- β -BL enabling side reactions such as transesterification and polymerisation/depolymerisation equilibria.

Figure 4. Copolymerisation of *rac*-LA, ϵ -CL and *rac*- β -BL to produce di- and ter-block copolymers using isolated **LZn₂OBn** (toluene, 60 °C).

As **LZn₂OBn** selectively prepared diblock poly(ϵ -caprolactone-*block*-lactic acid) and poly(*rac*- β -butyrolactone-*block*-lactic acid), the preparation of poly(ϵ -caprolactone-*block*-lactic acid-*block*-*rac*- β -butyrolactone) terpolymers was investigated (Table 3). The order of addition was again key to achieving good selectivity and suppressing transesterification. In line with observations from the diblock copolymer synthesis, sequential addition of ϵ -CL, *rac*-LA then *rac*- β -BL gave the optimum selectivity. The block structure of the terpolymer was identified through GPC and DSC analysis, DOSY studies and ¹H NMR spectroscopic analysis (Fig. S53 – S56). Notably, switching the order to ϵ -CL followed by *rac*- β -BL then *rac*-LA gave a bimodal distribution in the GPC analysis, suggesting that a mixture of homo- and co-polymers was formed. A difference from the diblock studies was that addition of *rac*- β -BL as the final monomer gave improved control over

the selectivity. Under the optimised conditions, the maximum conversion of *rac*- β -BL obtained was around 60%, whereas high monomer conversions of 96% were observed for both ϵ -CL and *rac*-LA. These findings suggest that unreacted *rac*- β -BL interfered with the polymerisation of ϵ -CL and *rac*-LA, presumably through competition with the other monomer(s) for coordination to **LZn₂OBn**, ring-opening and insertion into the growing polymer chain. To the best of our knowledge, **LZn₂OBn** is the first catalyst that can selectively prepare block terpolymers based on ϵ -CL, *rac*-LA and *rac*- β -BL, demonstrating high catalyst activities as well as excellent control over the block structure.

Table 3: Copolymerisation of ϵ -CL, *rac*-LA and *rac*- β -BL via sequential monomer addition with isolated **LZn₂OBn**:

Entry	1 st M	2 nd M	3 rd M	M:M:M ratio	% conv. 1 st M ^a	% conv. 2 nd M ^a	% conv. 3 rd M ^a	<i>M</i> _{n,obs} ^b (Da)	<i>Đ</i> ^b
1	ϵ -CL	-		33:0:0	96	-	-	9300	1.20
2 ^c	ϵ -CL	<i>rac</i> -LA		33:33:0	91	96	-	19100	1.12
3 ^d	ϵ -CL	<i>rac</i> -LA	β -BL	33:33:33	88	99	28	25900	1.13

M = monomer. *rac*-LA, ϵ -CL and **LZn₂OBn** were pre-stirred separately for 3 min in toluene at 60 °C before mixing and initiation of polymerization. ^a Conversion calculated using ¹H NMR spectroscopy. ^b *M*_{n,obs} and *Đ* determined by gel permeation chromatography using polystyrene standards in THF. ^c [ϵ -CL] = 0.52 M, [*rac*-LA] = 0.33 M in toluene. ^d [ϵ -CL] = 0.52 M, [*rac*-LA] = 0.33 M, [β -BL] = 0.33 M in toluene. β -BL was injected *via* a micropipette.

Conclusions

The *in situ* conversion of a metal-alkyl precursor to a metal-alkoxide species is a widely used method of initiating ROP, yet it can lead to different solution-state chemistries and influence the catalytic activity. Notably, isolated **LZn₂OBn** outperforms the *in situ* generated analogue by an

order of magnitude in *rac*-LA ROP. **LZn₂OBn** also displays excellent catalyst activities for a range of cyclic esters, including *rac*-LA, ϵ -CL and *rac*- β -BL; this exceptional activity and versatility has been exploited to achieve the selective one-pot synthesis of poly(ϵ -caprolactone-*block*-lactic acid) and poly(*rac*- β -butyrolactone-*block*-lactic acid). To the best of our knowledge, **LZn₂OBn** is the fastest catalyst reported for poly(ϵ -caprolactone-*block*-lactic acid), and the first catalyst to selectively prepare poly(ϵ -caprolactone-*block*-lactic acid-*block*- β -butyrolactone) in a one-pot synthesis, leading to a range of block polyesters. Dinuclear zinc complexes are amongst the front runners in cyclic ester ROP, and some of the best performing systems are dimeric with two sites that may operate independently. In contrast, **LZn₂OBn** contains just one initiating group. The high activities observed herein may therefore arise from cooperativity between the two metals, where one Lewis acidic Zn centre coordinates a cyclic ester, and the second Zn bears the alkoxide group (OBn or the polymer chain) to perform nucleophilic attack upon the coordinated monomer. The development of bi-metallic, mono-initiator catalysts offers a promising route to exploit metal-metal cooperativity and achieve both high activities and careful control over the polymer structure.

Supporting Information

The Supporting Information is available free of charge on the ACS Publications website at DOI: xxxxxxxx.

Experimental details, NMR, EA, MS characterisation data, polymer MALDI-TOF, GPC and DSC characterisation, kinetic and DOSY NMR studies, supplementary experiments.

Author Information

Corresponding Author

*E-mail Email: j.garden@ed.ac.uk (J. A. G.).

ORCID

Michael P. Shaver: 0000-0002-7152-6750

Jennifer A. Garden: 0000-0002-9027-4931

Notes

The authors declare no competing financial interest.

Acknowledgements

We would like to thank the CRITICAT Centre for Doctoral Training and Engineering and Physical Sciences Research Council (Ph.D. studentship to W. G.; Grant EP/L016419/1, funding to M. P. S.; Grants EP/S025200/1 and EP/P026095/2), Royal Society (J. A. G., Grant RSG/R1/180101), British Ramsay Memorial Trust (J. A. G.) and L'Oréal-UNESCO For Women in Science (J. A. G.) for funding. Dr Yuechao Xu is thanked for running DSC polymer analysis.

References

1. Ha, C., Gardella, J. A. Surface chemistry of biodegradable polymers for drug delivery systems. *Chem. Rev.* **2005**, *105*, 4205-4232.
2. Auras, R., Harte, B., Selke, S. An overview of polylactides as packaging materials. *Macromol. Biosci.* **2004**, *4*, 835–864.
3. Le Borgne, A., Vincens, V., Jouglard, M., Spassky, N. Ring-opening oligomerization reactions using aluminium complexes of schiff's bases as initiators. *Makromol. Chemie. Macromol. Symp.* **1993**, *73*, 37–46.
4. Stanford, M. J., Dove, A. P. Stereocontrolled ring-opening polymerisation of lactide. *Chem. Soc. Rev.* **2010**, *39*, 486-494.
5. Chmura, A. J., Davidson, M. G., Frankis, C. J., Jones, M. D., Lunn, M. D. Highly active and stereoselective zirconium and hafnium alkoxide initiators for solvent-free ring-opening polymerization of *rac*-lactide. *Chem. Commun.* **2008**, 1293–1295.
6. Bakewell, C., Cao, T., Long, N., Le Geoff, X. F., Auffrant, A., Williams, C. K. Yttrium Phosphasalen Initiators for *rac*-Lactide Polymerization: Excellent Rates and High Iso-Selectivities. *J. Am. Chem. Soc.* **2012**, *134*, 20577-20580.
7. Kremer, A. B., Mehrkhodavandi, P. Dinuclear catalysts for the ring opening polymerization of lactide. *Coord. Chem. Rev.* **2019**, *380*, 35–57.
8. Chamberlain, B. M., Cheng, M., Moore, D. R., Ovitt, T. M., Lobkovsky, E. B., Coates, G. W. Polymerization of lactide with zinc and magnesium β -diiminate complexes: stereocontrol and mechanism. *J. Am. Chem. Soc.* **2001**, *123*, 3229–3238.

9. Williams, C. K., Breyfogle, L. E., Choi, S. K., Nam, W., Young, V. G., Hillmyer, M. A., Tolman, W. B. A Highly Active Zinc Catalyst for the Controlled Polymerization of Lactide. *J. Am. Chem. Soc.* **2003**, *125*, 11350-11359.
10. Inkinen, S., Hakkarainen, M., Albertsson, A.-C., Södergård, A. From Lactic Acid to Poly(lactic acid) (PLA): Characterization and Analysis of PLA and Its Precursors. *Biomacromolecules* **2011**, *12*, 523–532.
11. Thevenon, A., Romain, C., Bennington, M. S., White, A. J. P., Davidson, H. J., Brooker, S., Williams, C. K. Dizinc lactide polymerization catalysts: Hyperactivity by control of ligand conformation and metallic cooperativity. *Angew. Chem. Int. Ed.* **2016**, *55*, 8680–8685.
12. Kissling, S., Altenbuchner, P. T., Lehenmeier, M. W., Herdtweck, E., Deglmann, P., Seemann, U. B., Rieger, B. Mechanistic Aspects of a Highly Active Dinuclear Zinc Catalyst for the Co-polymerization of Epoxides and CO₂. *Chem. Eur. J.* **2015**, *21*, 8148–8157.
13. Reiter, M., Vagin, S., Kronast, A., Jandl, C., Rieger, B. A Lewis acid β -diiminato-zinc-complex as all-rounder for co- and terpolymerisation of various epoxides with carbon dioxide. *Chem. Sci.* **2017**, *8*, 1876-1882.
14. Piesik, D. F.-J., Range, S., Harder, S. Bimetallic Calcium and Zinc Complexes with Bridged β -Diketiminato Ligands: Investigations on Epoxide/CO₂ Copolymerization. *Organometallics* **2008**, *27*, 6178–6187.
15. Ouhadi, T., Hamitou, A., Jerome, R., Teyssie, P. Soluble Bimetallic μ -Oxo-alkoxides. 8. Structure and Kinetic Behaviour of the Catalytic Species in Unsubstituted Lactone Ring-Opening Polymerization. *Macromolecules* **1976**, *9*, 927-931.

16. Osten, K. M., Mehrkhodavandi, P. Indium catalysts for ring opening polymerization: exploring the importance of catalyst aggregation. *Acc. Chem. Res.* **2017**, *50*, 2861–2869.
17. Ma, H., Okuda, J. Kinetics and Mechanism of L-Lactide Polymerization by Rare Earth Metal Silylamido Complexes: Effect of Alcohol Addition. *Macromolecules* **2005**, *38*, 2665-2673.
18. Jędrzkiewicz, D., Adamus, G., Kwiecień, M., John, Ł., Ejfler, J. Lactide as the Playmaker of the ROP Game: Theoretical and Experimental Investigation of Ring-Opening Polymerization of Lactide Initiated by Aminonaphtholate Zinc Complexes. *Inorg. Chem.* **2017**, *56*, 1349–1365.
19. Yoshida, H., Takenaka, M. Physics of block copolymers from bulk to thin films. in *Directed Self-assembly of Block Co-polymers for Nano-manufacturing*, 3–26 (Elsevier, 2015).
20. Wada, R., Hyon, S. H., Nakamura, T., Ikada, Y. *In Vitro* Evaluation of Sustained Drug Release from Biodegradable Elastomer. *Pharm. Res.* **1991**, *8*, 1292–1296.
21. Meek, M. F., Jansen, K., Steendam, R., van Oeveren, W., van Wachem, P. B., van Luyn, M. J. A. *In vitro* degradation and biocompatibility of poly(DL-lactide- ϵ -caprolactone) nerve guides. *J. Biomed. Mater. Res.* **2004**, *68*, 43–51.
22. Chiellini, E., Solaro, R. Biodegradable polymeric materials. *Adv. Mater.* **1996**, *8*, 305–313.
23. Albertsson, A.-C., Varma, I. K. Recent developments in ring opening polymerization of lactones for biomedical applications. *Biomacromolecules* **2003**, *4*, 1466–1486.
24. Labet, M., Thielemans, W. Synthesis of polycaprolactone: a review. *Chem. Soc. Rev.* **2009**, *38*, 3484-3504.

25. Rasal, R. M., Janorkar, A. V., Hirt, D. E. Poly(lactic acid) modifications. *Progress in Polymer Science (Oxford)* **2010**, *35*, 338–356.
26. Abe, H., Doi, O., Hori, Y., Hagiwara, T. Physical properties and enzymatic degradability of copolymers of (*R*)-3-hydroxybutyric acid and (*S*, *S*)-lactide. *Polymer* **1998**, *39*, 59–67.
27. Macdonald, J. P., Parker, M. P., Greenland, B. W., Hermida-Merino, D., Hamley, I. W., Shaver, M. P. Tuning thermal properties and microphase separation in aliphatic polyester ABA copolymers. *Polym. Chem.* **2015**, *6*, 1445–1453.
28. Cross, E. D., Allan, L. E. N., Decken, A., Shaver, M. P. Aluminium salen and salan complexes in the ring-opening polymerization of cyclic esters: Controlled immortal and copolymerization of *rac*- β -butyrolactone and *rac*-lactide. *J. Polym. Sci. Part A Polym. Chem.* **2013**, *51*, 1137–1146.
29. Basko, M., Duda, A., Kazmierski, S., Kubisa, P. Cationic copolymerization of racemic- β -butyrolactone with L,L-lactide: One-pot synthesis of block copolymers. *J. Polym. Sci. Part A Polym. Chem.* **2013**, *51*, 4873–4884.
30. Yu, I., Ebrahimi, T., Hatzikiriakos, S. G., Mehrkhodavandi, P. Star-shaped PHB-PLA block copolymers: immortal polymerization with dinuclear indium catalysts. *Dalton Trans.* **2015**, *44*, 14248–14254.
31. Fagerland, J., Finne-Wistrand, A., Pappalardo, D. Modulating the thermal properties of poly(hydroxybutyrate) by the copolymerization of *rac*- β -butyrolactone with lactide. *New J. Chem.* **2016**, *40*, 7671–7679.
32. Aluthge, D. C., Xu, C., Othman, N., Noroozi, N., Hatzikiriakos, S. G., Mehrkhodavandi, P. PLA-PHB-PLA triblock copolymers: Synthesis by sequential addition and investigation of mechanical and rheological properties. *Macromolecules* **2013**, *46*, 3965–3974.

33. Dubois, P., Jérôme, R., Teyssié, P. Aluminium alkoxides: A family of versatile initiators for the ring-opening polymerization of lactones and lactides. *Makromol. Chemie. Macromol. Symp.* **1991**, 42–43, 103–116.
34. Fan, L., Xiong, Y. B., Xu, H., Shen, Z. Q. L-Lactide homopolymerization and L-lactide- ϵ -caprolactone block copolymerization by lanthanide tris(2,4,6-trimethylphenolate)s. *Eur. Polym. J.* **2005**, 41, 1647–1653.
35. Cui, D. Tang, T., Bi, W., Cheng, J., Chen, W., Huang, B. Ring-opening polymerization and block copolymerization of L-lactide with divalent samarocene complex. *J. Polym. Sci. Part A Polym. Chem.* **2003**, 41, 2667–2675.
36. Stassin, F., Jérôme, R. Polymerization of (L, L)-lactide and copolymerization with ϵ -caprolactone initiated by dibutyltin dimethoxide in supercritical carbon dioxide. *J. Polym. Sci. Part A Polym. Chem.* **2005**, 43, 2777–2789.
37. Dakshinamoorthy, D., Peruch, F. Block and random copolymerization of ϵ -caprolactone, L-, and *rac*-lactide using titanium complex derived from aminodiol ligand. *J. Polym. Sci. Part A Polym. Chem.* **2012**, 50, 2161–2171.
38. Chmura, A. J., Davidson, M. G., Jones, M. D., Lunn, M. D., Mahon, M. F., Johnson, A. F., Khankamchoo, P., Roberts, S. L., Wong, S. S. F. Group 4 complexes with aminebisphenolate ligands and their application for the ring opening polymerization of cyclic esters. *Macromolecules* **2006**, 39, 7250–7257.
39. Xiao, Y., Wang, Z., Ding, K. Copolymerization of Cyclohexene Oxide with CO₂ by Using Intramolecular Dinuclear Zinc Catalysts. *Chem. - A Eur. J.* **2005**, 11, 3668–3678.
40. Trost, B. M., Hung, C.-I. J., Mata, G. Dinuclear Metal-ProPhenol Catalysts: Development and Synthetic Applications. *Angew. Chem. Int. Ed.* **2019**, 58, 2-24.

41. Trost, B. M., Silcoff, E. R., Ito, H. Direct Asymmetric Aldol Reactions of Acetone Using Bimetallic Zinc Catalysts. *Org. Lett.* **2001**, *3*, 2497–2500.
42. Trost, B. M., Silcoff, E. R. & Ito, H. Direct asymmetric aldol reactions of acetone using bimetallic zinc catalysts. *Org. Lett.* **2001**, *3*, 2497–2500.
43. Trost, B. M., Fettes, A., Shireman, B. T. Direct catalytic asymmetric aldol additions of methyl ynones. Spontaneous reversal in the sense of enantioinduction. *J. Am. Chem. Soc.* **2004**, *126*, 2660–2661.
44. Trost, B. M., Terrell, L. R. A direct catalytic asymmetric Mannich-type reaction to *syn*-amino alcohols. *J. Am. Chem. Soc.* **2003**, *125*, 338–339.
45. Dechy-Cabaret, O., Martin-Vaca, B., Bourissou, D. Controlled ring-opening polymerization of lactide and glycolide. *Chem. Rev.* **2004**, *104*, 6147–6176.
46. Darensbourg, D. J., Choi, W., Karroonnirun, O., Bhuvanesh, N. Ring-Opening Polymerization of Cyclic Monomers by Complexes Derived from Biocompatible Metals. Production of Poly(lactide), Poly(trimethylene carbonate), and Their Copolymers. *Macromolecules* **2008**, *41*, 3493–3502.
47. Sanchez-Sanchez, A., Rivilla, I., Agirre, M., Basterretxea, A., Etxeberria, A., Veloso, A., Sardon, H., Mecerreyes, D., Cossio, F. P. Enantioselective Ring-Opening Polymerization of *rac*-Lactide Dictated by Densely Substituted Amino Acids. *J. Am. Chem. Soc.* **2017**, *139*, 4805–4814.
48. Zhong, Z., Dijkstra, P. J., Birg, C., Westerhausen, M., Feijen, J. A Novel and Versatile Calcium-Based Initiator System for the Ring-Opening Polymerization of Cyclic Esters. *Macromolecules* **2001**, *34*, 3863–3868.
49. Kowalski, A., Duda, A., Penczek, S. Polymerization of L,L-Lactide Initiated by Aluminum

- Trimer or Tetramer. *Macromolecules* **1998**, *31*, 2114–2122.
50. Fliedel, C., Vila-Viçosa, D., Calhorda, M. J., Dagorne, S., Avilés, T. Dinuclear Zinc-N-Heterocyclic Carbene Complexes for Either the Controlled Ring-Opening Polymerization of Lactide or Controlled Degradation of Polylactide Under Mild Conditions. *ChemCatChem* **2014**, *6*, 1357-1367.
51. Chen, H. L., Chuang, H. J., Huang, B. H., Lin, C. C. Ring-opening polymerization of ϵ -caprolactone, β -butyrolactone and lactides by β -ketiminate pyrazolonate zinc complexes: Preparation and characterization. *Inorg. Chem. Commun.* **2013**, *35*, 247–251.
52. Ebrahimi, T., Mamleeva, E., Yu, I., Hatzikiriakos, S. G., Mehrkhodavandi, P. The role of nitrogen donors in zinc catalysts for lactide ring-opening polymerization. *Inorg. Chem.* **2016**, *55*, 9445–9453.
53. Ebrahimi, T., Aluthge, D. C., Hatzikiriakos, S. G., Mehrkhodavandi, P. Highly active chiral zinc catalysts for immortal polymerization of β -butyrolactone from melt processable syndio-rich poly(hydroxybutyrate). *Macromolecules* **2016**, *49*, 8812–8824.
54. Wu, J.-C., Huang, B.-H., Hsueh, M.-L., Lai, S.-L., Lin, C.-C. Ring-opening polymerization of lactide initiated by magnesium and zinc alkoxides. *Polymer* **2005**, *46*, 9784–9792.
55. Hung, W.-C., Huang, Y., Lin, C.-C. Efficient initiators for the ring-opening polymerization of L-lactide: Synthesis and characterization of NNO-tridentate Schiff-base zinc complexes. *J. Polym. Sci. Part A Polym. Chem.* **2008**, *46*, 6466–6476.
56. Kong, W. L., Wang, Z. X. Dinuclear magnesium, zinc and aluminum complexes supported by bis(iminopyrrolide) ligands: synthesis, structures, and catalysis toward the ring-opening polymerization of ϵ -caprolactone and *rac*-lactide. *Dalton Trans.* **2014**, *43*, 9126–9135.

57. Solaro, R., Cantoni, G., Chiellini, E. Polymerisability of different lactones and methyl methacrylate in the presence of various organoaluminium catalysts. *Eur. Polym. J.* **1997**, *33*, 205–211.
58. Rajashekhar, B., Roymuhury, S. K., Chakraborty, D., Ramkumar, V. Group 4 metal complexes of Trost's semi-crown ligand: synthesis, structural characterization and studies on the ring-opening polymerization of lactides and ϵ -caprolactone. *Dalt. Trans.* **2015**, *44*, 16280–16293.
59. Nakano, K., Nozaki, K., Hiyama, T. Asymmetric Alternating Copolymerization of Cyclohexene Oxide and CO₂ with Dimeric Zinc Complexes. *J. Am. Chem. Soc.* **2003**, *125*, 5501–5510.
60. Yao, W., Mu, Y., Gao, A., Gao, W., Ye, L. Bimetallic anilido-alimine Al or Zn complexes for efficient ring-opening polymerization of ϵ -caprolactone. *Dalt. Trans.* **2008**, *24*, 3199–3206.
61. Chakraborty, D., Chen, E. Y.-X. Chiral amido aluminum and zinc alkyls: a synthetic, structural, and polymerization study. *Organometallics* **2003**, *22*, 769–774.
62. Zhong, Z., Ankoné, M. J., Dijkstra, P. J., Birg, C., Westerhausen, M., Feijen, M. Calcium methoxide initiated ring-opening polymerization of ϵ -caprolactone and L-lactide. *Polym. Bull.* **2001**, *46*, 51–57.
63. Dubois, P., Jacobs, C., Jerome, R., Teyssie, P. Macromolecular engineering of polylactones and polylactides. 4. Mechanism and kinetics of lactide homopolymerization by aluminum isopropoxide. *Macromolecules* **1991**, *24*, 2266–2270.
64. Grunova, E., Kirillov, E., Roisnel, T., Carpentier, J. F. Group 3 metal complexes supported by tridentate pyridine-and thiophene-linked bis(naphtholate) ligands: synthesis, structure,

- and use in stereoselective ring-opening polymerization of racemic lactide and β -butyrolactone. *Dalton Trans.* **2010**, 39, 6739-6752.
65. Thomas, C. M. Stereocontrolled ring-opening polymerization of cyclic esters: synthesis of new polyester microstructures. *Chem. Soc. Rev.* **2010**, 39, 165-173.
66. Müller, H. -M, Seebach, D. Poly(hydroxyalkanoates): a fifth class of physiologically important organic biopolymers? *Angew. Chem. Int. Ed.* **1993**, 32, 477–502.
67. Sudesh, K., Abe, H., Doi, Y. Synthesis, structure and properties of polyhydroxyalkanoates: biological polyesters. *Prog. Polym. Sci.* **2000**, 25, 1503–1555.
68. Kemnitzer, J. E., McCarthy, S. P., Gross, R. A. Syndiospecific ring-opening polymerization of β -butyrolactone to form predominantly syndiotactic poly(β -hydroxybutyrate) using tin(IV) catalysts. *Macromolecules* **1993**, 26, 6143-6150.
69. Kemnitzer, J. E., McCarthy, S. P., Gross, R. A. Preparation of predominantly syndiotactic poly(β -hydroxybutyrate) by the tributyltin methoxide catalyzed ring-opening polymerization of racemic β -butyrolactone. *Macromolecules* **1993**, 26, 1221-1229.
70. Amgoune, A., Thomas, C. M., Ilinca, S., Roisnel, T., Carpentier, J.-F. Highly Active, Productive, and Syndiospecific Yttrium Initiators for the Polymerization of Racemic β -Butyrolactone. *Angew. Chem. Int. Ed.* **2006**, 45, 2782-2784.
71. Shaik, M., Peterson, J., Du, G. Cyclic and linear polyhydroxybutyrates from ring-opening polymerization of β -butyrolactone with amido-oxazolate zinc catalysts. *Macromolecules* **2019**, 52, 157-166.
72. Rieth, L. R., Moore, D. R., Lobkovsky, E. B., Coates, G. W. Single-site β -diiminate zinc catalysts for the ring-opening polymerization of β -butyrolactone and β -valerolactone to poly(3-hydroxyalkanoates). *J. Am. Chem. Soc.* **2002**, 124, 15239–15248.

73. Wang, B., Wei, Y., Li, Z.-J., Pan, L., Li, Y.-S. From $\text{Zn}(\text{C}_6\text{F}_5)_2$ to ZnEt_2 -based Lewis Pairs: Significantly Improved Catalytic Activity and Monomer Adaptability for the Ring-opening Polymerization of Lactones. *ChemCatChem* **2018**, *10*, 5287–5296.
74. Ebrahimi, T., Hatzikiriakos, S. G., Mehrkhodavandi, P. Synthesis and Rheological Characterization of Star-Shaped and Linear Poly(hydroxybutyrate). *Macromolecules* **2015**, *48*, 6672–6681.
75. Tai, Y.-E., Li, C.-Y., Lin, C.-H., Liu, Y.-C., Ko, B.-T., Sun, Y.-S. Efficient catalysts for ring-opening polymerization of ϵ -caprolactone and β -butyrolactone: Synthesis and characterization of zinc complexes based on benzotriazole phenoxide ligands. *J. Polym. Sci. Part A Polym. Chem.* **2011**, *49*, 4027–4036.
76. Kurcok, P., Dubois, P., Jérôme, R. Polymerization of β -butyrolactone initiated with $\text{Al}(\text{O}^i\text{Pr})_3$. *Polym. Int.* **1996**, *41*, 479–485.
77. Kricheldorf, H. R., Scharnagl, N., Jedlinski, Z. Poly lactones 33. The role of deprotonation in the anionic polymerization of β -propiolactone. *Polymer* **1996**, *37*, 1405–1411.
78. Melchiors, M., Keul, H., Höcker, H. Synthesis of highly isotactic poly[(*R*)-3-hydroxybutyrate] by ring-opening polymerization of (*R,R,R*)-4,8,12-trimethyl-1,5,9-trioxacyclododeca-2,6,10-trione. *Macromol. Rapid Commun.* **1994**, *15*, 497–506.
79. Melchiors, M., Keul, H., Höcker, H. Depolymerization of Poly[(*R*)-3-hydroxybutyrate] to Cyclic Oligomers and Polymerization of the Cyclic Trimer: An Example of Thermodynamic Recycling. *Macromolecules* **1996**, *29*, 6442–6451.
80. Rosen, T., Goldberg, I., Navarra, W., Venditto, V., Kol, M. Divergent $\{\text{ONNN}\}\text{Mg-Cl}$ complexes in highly active and living lactide polymerization. *Chem. Sci.* **2017**, *8*, 5476–5481.

81. Rosen, T., Goldberg, I., Venditto, V., Kol, M. Tailor-Made Stereoblock Copolymers of Poly(lactic acid) by a Truly Living Polymerization Catalyst. *J. Am. Chem. Soc.* **2016**, *138*, 12041–12044.
82. Vanhoorne, P., Dubois, P., Jerome, R., Teyssie, P. Macromolecular Engineering of Polylactones and Polylactides. 7. Structural Analysis of Copolyesters of ϵ -Caprolactone and L- or D, L-Lactide Initiated by $\text{Al}(\text{O}^i\text{Pr})_3$. *Macromolecules* **1992**, *25*, 37-44.
83. Raycraft, B. M., Macdonald, J. P., McIntosh, J. T., Shaver, M. P., Gillies, E. R. Post-polymerization functionalization of poly(ethylene oxide)-poly(β -6-heptenolactone) diblock copolymers to tune properties and self-assembly. *Polym. Chem.* **2017**, *8*, 557-567.
84. Kasperczyk, J., Bero, M. Coordination polymerization of lactides, 2. Microstructure determination of poly[(L,L-lactide)-*co*-(ϵ -caprolactone)] with ^{13}C nuclear magnetic resonance spectroscopy. *Die Makromol. Chemie* **1991**, *192*, 1777–1787.
85. Pappalardo, D., Annunziata, L., Pellecchia, C. Living Ring-Opening Homo- and Copolymerization of ϵ -Caprolactone and L- and D,L-Lactides by Dimethyl(salicylaldiminato)aluminum Compounds. *Macromolecules* **2009**, *42*, 6056–6062.
86. Florczak, M., Libiszowski, J., Mosnacek, J., Duda, A., Penczek, S. L,L-Lactide and ϵ -Caprolactone Block Copolymers by a 'Poly(L,L-lactide) Block First' Route. *Macromol. Rapid Commun.* **2007**, *28*, 1385–1391.