THE UNIVERSITY *of* EDINBURGH

Edinburgh Research Explorer

Valorization of Humins from Food Waste Biorefinery for Synthesis of Biochar-supported Lewis Acid Catalysts

Citation for published version:

Xiong, X, Yu, IKM, Dutta, S, Masek, O & Tsang, DCW 2021, 'Valorization of Humins from Food Waste Biorefinery for Synthesis of Biochar-supported Lewis Acid Catalysts', *Science of the Total Environment*, vol. 775, 145851. <https://doi.org/10.1016/j.scitotenv.2021.145851>

Digital Object Identifier (DOI):

[10.1016/j.scitotenv.2021.145851](https://doi.org/10.1016/j.scitotenv.2021.145851)

Link:

[Link to publication record in Edinburgh Research Explorer](#)

Document Version:

Peer reviewed version

Published In:

Science of the Total Environment

General rights

Copyright for the publications made accessible via the Edinburgh Research Explorer is retained by the author(s) and / or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

The University of Edinburgh has made every reasonable effort to ensure that Edinburgh Research Explorer content complies with UK legislation. If you believe that the public display of this file breaches copyright please contact openaccess@ed.ac.uk providing details, and we will remove access to the work immediately and investigate your claim.

Valorization of Humins from Food Waste Biorefinery for Synthesis of Biochar-supported Lewis Acid Catalysts

Xinni Xiong ^a, Iris K.M. Yu ^{a,b,#}, Shanta Dutta^a, Ondřej Mašek^c, Daniel C.W. Tsang ^{a,*}

^a Department of Civil and Environmental Engineering, Hong Kong Polytechnic University, Hung Hom, Kowloon, Hong Kong, China

^b Department of Chemistry and Catalysis Research Center, Technische Universität München, Lichtenbergstrasse 4, 85747 Garching, Germany

^c UK Biochar Research Centre, School of GeoSciences, University of Edinburgh, Edinburgh, Alexander Crum Brown Road, EH9 3FF, UK

**Corresponding author: dan.tsang@polyu.edu.hk*

#Co-corresponding author: iris.yu@tum.de

Abstract

To close the carbon loop of biomass waste valorization, it is imperative to utilize the unavoidable by-products such as humins, a carbonaceous residue with complex and heterogeneous composition. In this study, starch-rich rice waste was effectively converted into value-added chemicals (e.g., 5-hydroxymethylfurfural) under microwave heating at 160 °C using AlCl_3 as the catalyst. The solid by-products, i.e., humins, were then valorized as a raw material for fabricating biochar-supported Lewis acid catalysts. The humins were collected and pretreated by AlCl_3 as the impregnation agent, followed by carbonization. Detailed characterization revealed several Al-O species on the biochar surface plausibly in the amorphous state. The oxygen-containing functional groups of humins might serve as anchoring sites for the Al species during impregnation. The humins-derived biochars exhibited good catalytic activity toward glucose-to-fructose isomerization, a common biorefinery reaction catalyzed by Lewis acids. A fructose yield of up to 14 Cmol% could be achieved under microwave heating at 160 °C for 20 min in water as the greenest solvent. Such catalytic performance was comparable with the previously reported Al-based catalysts derived from wood waste and graphene/graphitic oxide. This study herein highlights humins as a low-cost alternative source of carbon for the preparation of renewable solid catalysts, proposing a novel practice for recycling by-products from food waste valorization to foster circular economy and sustainable development.

Keywords: biomass valorization; food waste recycling; engineered biochar; sustainable biorefinery; glucose isomerization; waste management.

1. Introduction

The global shortage of energy and resources has driven the urgent demand for innovative technologies to seek renewable alternatives to fossil fuels. Waste biomass generated in significant amounts has been promisingly serving as a sustainable and green resource for the production of value-added products in recent years, which will play an important role in our transition to circular economy (Mak et al., 2020). Food waste is one of the major waste biomass streams receiving considerable public attention and research interest. Various valorization options using physical, chemical, and biological processing technologies have been reported (Xiong et al., 2019). The composition of food waste makes it suitable as a starting material for the production of biofuels and chemicals. For instance, cellulose and starch, the major components in food waste, are a source of versatile glucose molecules that can be converted to fructose. The latter is a promising substrate for the synthesis of value-added chemicals, such as 5-hydroxymethylfurfural (HMF), which is a critical and valuable building block for the manufacture of pharmaceuticals, resins, solvents, and polymers (Mukherjee et al., 2015; Yu and Tsang, 2017).

The chemical process of cellulose/starch conversion involves multiple reactions that are often accelerated over different catalysts. For example, the hydrolysis of polysaccharides to glucose is commonly catalyzed by Brønsted acid sites, whereas glucose isomerization to fructose can be promoted over Lewis acids or Brønsted bases (Yu and Tsang, 2017). Most of the reported catalytic conversions are accompanied by side reactions under hydrothermal conditions, which generate heterogeneous solid residues, denoted as humins, via irreversible aldol condensation among intermediates and products (Cheng et al., 2018; Filiciotto et al., 2018;

Pfab et al., 2019). Humins is insoluble and macromolecular substances composed of co-products such as furanics, levulinates, and sugar-derived molecules (Filiciotto et al., 2019). The cross-linked structure renders humins as a potential carbon matrix for catalyst support. To achieve high carbon efficiency in the circular bioeconomy, it is desirable to explore value-added application of the unavoidable humins. Previous studies investigated steam reforming of humins to hydrogen (Hoang et al., 2013) and liquefaction/depolymerization of humins into pyrolysis oil (Agarwal et al., 2017). These technologies focused on mineralization via selective bond dissociation, yet high temperature and catalyst consumption may restrict its large-scale valorization (Hoang et al., 2015). An alternative approach that might be more energy-efficient is to exploit and modify the polycyclic aromatic structure of humins. Previous studies examined humins as a prospective precursor of eco-friendly carbon materials, such as hydrophobic humins/flax fibres composites and humins-based resins (Sangregorio et al., 2019; Sangregorio et al., 2020).

There are, however, limited research studies on the synthesis of humins-derived biochar for the application in green biorefinery processes. Biochar is an environmentally friendly, low-cost, and renewable material produced from waste biomass by means of pyrolysis or hydrothermal carbonization (Tang et al., 2013). They have been extensively tested in a range of applications, including uses as potential catalysts or catalyst supports, because the porous structure, surface area, and functional groups can be tuned to facilitate the impregnation of active sites and adsorption of reactants (Xiong et al., 2017; Kumar et al., 2020). While raw lignocellulosic biomass (forestry waste, agricultural residue, etc.) are typical feedstock in the biochar production, humins could be an alternative carbon source, especially for applications

that would benefit from hydrophilic surface (van Zandvoort et al., 2013), such as catalyst supports. Sulfonated humins-derived catalysts were studied for the esterification of levulinic acid (LA) and n-butanol, hydroxyalkylation/alkylation of 2-methylfuran and furfural (Yang et al., 2020), and cellulose conversion to LA (Wang et al, 2018). We conjecture that impregnation of transition metals can introduce Lewis acid sites on humins-derived biochar surface, which would enable its application in more diverse reactions. Our previous studies of Al-based catalysts supported on wood waste biochar (Yu et al., 2019a) and graphene/graphite oxide (Yu et al., 2019b; Xiong et al., 2020) revealed their good performance in glucose-fructose isomerization.

In this study, we aim to recycle and valorize humins for the synthesis of renewable, sustainable solid Lewis acids that can catalyze biorefinery processes. Cooked rice waste daily generated in the Hong Kong International Airport (HKIA) was collected and used as the food waste substrate in this work. A high-performance waste recycling system for valorization of starch-rich waste from local enterprises is expected to bring environmental and economic benefits to the society. Rice waste conversion was performed for HMF production and the simultaneously produced humins were collected and modified by metal impregnation in AlCl_3 aqueous solutions. The prepared catalysts were characterized and evaluated for glucose isomerization as a model reaction mediated by Lewis acids in biorefineries.

2. Materials and methods

2.1 Chemicals and raw materials

Cooked rice waste was collected from restaurants in the HKIA, and was subjected to drying at 105 °C, grinding, and sieving (0.2 mm mesh), before storage in an airtight container at 4 °C. The $\text{AlCl}_3 \cdot 6\text{H}_2\text{O}$ (ACS grade) purchased from Anaqua was used for impregnation in this study. Standard compounds were used for catalytic glucose conversion and equipment calibration, including glucose ($\geq 99.5\%$), HMF ($\geq 99\%$), and furfural (99%) from Sigma Aldrich; cellobiose ($\geq 98\%$), LA (98%), and formic acid (FA) (98%) from Alfa Aesar; levoglucosan from Fluorochem; and fructose ($\geq 99\%$) and maltose monohydrate ($\geq 98\%$) from Wako. All the chemicals were used as received.

2.2 Rice waste and glucose catalytic conversion

The catalytic conversion of rice waste or glucose was performed following the procedures reported in our previous studies (Yu et al., 2019a; Yu et al., 2019b). The mixture was placed in a sealed Teflon vessel, followed by heating to 160 °C in the Ethos Up Microwave Reactor (Milestone, maximum power 1900 W). Various rice waste loading (0.1, 0.15, and 0.2 g mL⁻¹) and AlCl_3 catalyst dosage (Al concentration = 10 or 20 wt%) were tested at 160 °C with a ramp time of 5 min and holding time ranging from 0 to 40 min. Vigorous magnetic stirring was maintained throughout the whole process. After the reaction, the vessel was cooled to room temperature under continuous mechanical ventilation for 40 min in the reactor. The soluble samples were prepared for product analysis, while the solid residues were collected for the synthesis of humins-derived biochar catalysts. The catalysts were evaluated for glucose isomerization, which was performed following the abovementioned procedure. The biochar

catalyst (0.25 g) and glucose (0.5 g) were added to 10 mL deionized water or water/acetone (1:1 v/v) solvent, followed by microwave heating at 140 °C and 160 °C for 5, 20, and 40 min, respectively. All trials were carried out in duplicate.

2.3 Synthesis of humins-derived biochar catalysts

Based on the results of rice waste conversion achieving the maximal HMF yield, the conditions for batch production of humins were determined at 0.15 g mL⁻¹ rice waste in 10 wt% AlCl₃ aqueous solution at a temperature of 160 °C. The holding time was 0 and 15 min, producing residues denoted as Humins0 and Humins15, respectively. The residues were recovered by centrifugation and decantation, followed by multiple washing with deionized water. For Al impregnation, 10 g residues were suspended in a 200 mL solution of 10 wt% AlCl₃ with stirring for 4 h. After oven-drying the mixture at 105 °C, the AlCl₃-treated humins were placed in a ceramic boat for carbonization in a Carbolite muffle furnace at 500 °C for 2 h (10 °C min⁻¹ ramping), which produced humins-derived biochars labelled as HB15-Al and HB0-Al. It was reported that pyrolysis temperatures ranging from 500 to 700 °C are favourable for biochar production in view of stable polycyclic aromatic carbon and overall yield for common feedstock (Xiong et al., 2017). For an energy-efficient utilization and fair comparison with our previous reports on biochar-based catalysts (Yu et al., 2019a; Xiong et al., 2020), we selected 500 °C as the carbonization temperature in this study (**Fig. 1**). As for control experiments, humins without AlCl₃ treatment were subjected to the same pyrolysis treatment, and the resultant biochars were denoted as HB15 and HB0. All prepared catalysts were stored in a sealed container in a desiccator before characterization and catalytic activity evaluation.

2.4 Biochar catalyst characterization

The morphology, topography, and elemental distribution of the humins-based biochar catalysts were revealed by scanning electron microscopy (SEM) with energy dispersive X-ray analysis (EDX) [TESCAN VEGA3]. Brunauer-Emmett-Teller (BET) surface area and pore volume were measured by nitrogen adsorption–desorption isotherm measurement at -196 °C using a gas sorption analyser (Micromeritics Accelerated Surface Area and Porosimetry system, ASAP 2020). The crystalline and amorphous phases were revealed by X-ray diffraction analysis (XRD; Rigaku SmartLab) in a scanning range of 10–80° 2 θ at a rate of 5° min⁻¹ at 45 kV and 200 mA. The surface functionalities were studied using micro-Raman spectroscopy (Renishaw) with a laser source at a wavelength of 532 nm and an objective of 50 $\times$. X-ray photoelectron spectroscopy (XPS; ESCALAB 250Xi spectrometer, USA) with monochromated Al K α radiation was performed with a pass energy of 187.85 eV at 1.6 eV per step for survey scans (0 to 1200 eV). Curve fitting was performed for the obtained spectra of Al 2p using XPSPEAK41.

2.5 Catalysis product analysis

Liquid samples collected after microwave-assisted conversion were diluted with deionized water (1:3 v/v) and filtered through a mixed cellulose ester filter (0.22 μ m) before analysis. High-performance liquid chromatography (HPLC) was performed using a Chromaster instrument equipped with a refractive index detector (Hitachi, Japan) and an Aminex HPX-87H column (Bio-Rad) at an analytical temperature of 50 °C. The mobile phase was 0.01 M

H₂SO₄ at a flow rate of 0.5 mL min⁻¹. The yield and selectivity of the products were calculated in terms of the carbon content.

$$\text{Product yield (Cmol\%)} = \frac{P_f(\text{mg/ml}) \times n_p / MW_P}{Glu_i(\text{mg/ml}) \times n_{Glu} / MW_{Glu}} \times 100, \quad (1)$$

$$\text{Product selectivity (Cmol\%)} = \frac{P_f(\text{mg/ml}) \times n_p / MW_P}{(Glu_i - Glu_f)(\text{mg/ml}) \times n_{Glu} / MW_{Glu}} \times 100 \quad (2)$$

where P_f represents the concentration of the products, n_p and n_{Glu} are number of carbons in the corresponding product and glucose, MW_P and MW_{Glu} are molecular mass of the corresponding product and glucose, and Glu_i and Glu_f represent the initial and final concentration of glucose, respectively. One gram of starch (90.1 wt% in rice waste) is equivalent to 1.11 g glucose.

3. Results and discussion

3.1 HMF production from rice waste

The distribution of products from catalytic conversion of rice waste at various substrate and catalyst loadings are shown in **Fig. 2** (160 °C, 15 min). The total yields of detectable products were 32.6-58.6 Cmol%, in which the major species were glucose, fructose, and HMF, along with LA, FA, and levoglucosan in small quantities. The aqueous AlCl₃ provided Brønsted acids as the cation underwent partial hydrolysis in water, releasing protons promoting the cleavage of C-O-C linkages in rice starch. The produced glucose was then isomerized over the Lewis acid site of Al³⁺ ions to form fructose, which could undergo dehydration to yield HMF in the presence of Brønsted acids. Increasing the rice waste loading from 0.1 to 0.15 g mL⁻¹ did not affect the HMF yield (16.6 to 15.4 Cmol%; **Fig. 2**). However, a further increase to 0.2 g mL⁻¹ rice waste resulted in a drop of HMF production (8.6 Cmol%) and a decrease in the fructose-to-glucose molar ratio from ~1.1 to ~0.73. Lewis acid site density might be insufficient to

maintain the isomerization rate at a high feedstock loading, and the reduced concentration of fructose might slow down the subsequent dehydration step. The following experiments adopted the rice waste loading of 0.15 g mL⁻¹ for a high-throughput HMF generation.

The time-dependent product yields from rice waste conversion are shown in **Fig. 3a&b** (rice waste 0.15 g mL⁻¹, 160 °C). At 10 wt% catalyst loading, rapid starch hydrolysis was promoted and the glucose yield peaked at 33.2 Cmol% within 5 min of microwave-assisted conversion. During this period, the fructose yield of 24.6 Cmol% was obtained, and the fructose-to-glucose ratio of 0.74:1 was close to the thermodynamic equilibrium of 1:1, suggesting efficient isomerization. As the reaction time increased, the yield of HMF increased to 15.4 Cmol% and reached a plateau after 15 min. Increasing the catalyst loading to 20 wt% shortened the reaction time from 15 min to 5 min for reaching the peak of HMF yield (**Fig. 3b**). Nevertheless, the product profiles at both catalyst loadings remained similar, when considering glucose, fructose, and HMF as the major products.

The hydrothermal catalytic conditions also facilitated side reactions such as rehydration of HMF to LA (~5-13 Cmol%; **Fig. 3**). A carbon loss of 32-75 Cmol% was estimated (**Fig. 3**) while 7.1-8.4 wt% insoluble, dark solid residues were observed after the conversion, which could be attributed to the polymerization among intermediates and HMF through aldol addition and condensation. Such residues, broadly named as humins, are carbonaceous, heterogeneous materials with a furan-rich polymer network containing different oxygen functional groups (van Zandvoort et al., 2013). Our screening experiments showed that the condition at 0.15 g mL⁻¹ rice waste, 10 wt% catalyst loading, and heating at 160 °C for 15 min could generate 15.4 Cmol% HMF and 25.9 Cmol% sugars with considerable humins production when using water

as the greenest solvent. While HMF and the sugars are attractive platform chemicals, the low-value humins residues were collected for the synthesis of biochar-supported catalysts to achieve carbon-efficient biorefinery, which is discussed in the following sections.

3.2 Biochar catalyst characterization

As shown in **Fig. 4**, the SEM image of the solid residues generated after 15-min conversion of rice waste (Humins15) shows a rougher surface compared to that collected at 0 min (Humins0) (methods in **Section 2.3**). HB0 resulting from the pyrolysis of Humins0 presented macropores (5-40 μm), which might collapse when Al impregnation was performed prior to pyrolysis (i.e., HB0-Al). This observation is substantiated by the evidence that the BET surface area significantly decreased from 125 $\text{m}^2 \text{g}^{-1}$ for HB0 to 23 $\text{m}^2 \text{g}^{-1}$ for HB0-Al (**Table 1**). Such difference was smaller in the case of HB15 vs. HB15-Al (201 vs. 150 $\text{m}^2 \text{g}^{-1}$). This suggests that precursor Humins15 had a more stable structure compared to Humins0, probably due to the higher degree of condensation associated with a longer reaction time. It is noted that the measured surface area might be higher if the probing gas is changed from N_2 to CO_2 due to higher kinetic energy and smaller kinetic diameter of the latter one (Weber and Quicker, 2018).

Successful incorporation of Al species on the biochars was evidenced by the EDX mapping (**Fig. 5**). It is noted that Humins0 carried more oxygen-containing functional groups (34.7% O) than Humins15 (28.6% O), which might facilitate the impregnation of Al species (Yu et al., 2019a). This was corroborated by the observation that HB0-Al had a higher Al content (3.47%) compared to HB15-Al (2.99%) (**Table 2**). Such elemental comparison based on the EDX results was consistent with the XPS analysis, although the latter revealed a higher proportion

of Al (8.7-9.2%; **Table 2**). Given that XPS has a smaller depth of analysis (3-5 nm) than EDX (μm) (Hantsche, 1989; Kerber et al., 1998), the difference in Al% measurement suggests that the Al species were mainly located on the surface of the humins-derived biochar catalyst. Curve fitting of the XPS spectra of Al 2p indicated the possible Al species as $\text{Al}(\text{OH})_3$, $\text{AlO}(\text{OH})$, and $\text{Al}-\text{O}-\text{C}$ in HB0-Al and HB15-Al (**Fig. 6**). This is in agreement with the profiles of Al-impregnated wood waste-derived biochar and graphene/graphite oxide in our previous studies (Yu et al., 2019a; Yu et al., 2019b; Xiong et al., 2020). The XRD patterns of HB0-Al and HB15-Al display no distinct peaks assigned to any Al-based minerals, suggesting that the Al species were primarily in amorphous structures and/or short-range crystalline order (Lawrinenko et al., 2017; Yu et al., 2019a) (**Fig. 7a**).

Pyrolysis of humins tends to generate aromatic structures such as furans, arenes, and phenolics (Shen et al., 2020). The broad XRD peak at $20-30^\circ$, which was characteristic of amorphous carbon (Rajan et al., 2014; Shang et al., 2015), had a higher intensity in HB0 compared to HB15 (**Fig. 7a**). The graphitization of humins-derived biochar catalyst was further examined by calculating the ratios of D peak to G peak (I_D/I_G) in Raman spectra (**Fig. 7b**). Biochar derived from Humins15 (with and without Al impregnation) presented lower I_D/I_G values (0.62-0.74) than those from Humins0 (0.96-0.98), indicating a lower proportion of disorder fraction in the former sample. The prolonged conversion process of rice waste valorization consumed the amorphous polysaccharide and promoted the condensation reactions among the intermediates and HMF. This could have reduced the amount of defects on the humins surface, which was reflected by the decrease in the O content from 34.7% in Humins0 to 28.6% in Humins15 (**Table 2**).

3.3 Glucose isomerization over humins-derived biochar catalysts

The catalytic activity of the humins-derived biochar catalysts was evaluated for the isomerization of glucose to fructose under microwave heating at 160 °C for 20 min in water (**Fig. 8**). The HB0-Al and HB15-Al successfully achieved 14.1 and 10.4 Cmol % fructose yields, respectively. This performance was comparable with the Al-impregnated wood waste-derived biochar (14% fructose, 160 °C, 20 min; Yu et al., 2019a) and Al-impregnated graphite oxide (15% fructose, 140 °C, 20 min; Yu et al., 2019b), which were synthesized following a similar protocol. The use of humins herein, a biorefinery by-product, presents a more economical option for fabricating the carbon-supported heterogeneous catalysts. The use of humins and humins-derived biochar without Al modification (Humins0, Humins15, HB0, HB15) resulted in negligible fructose yields (< 3 Cmol%), confirming that the catalytic activity was associated with the available Al sites impregnated in the biochar catalysts as revealed in the characterization (**Section 3.2**).

The catalytic performance of HB0-Al and HB15-Al was further studied under various conditions. As shown in **Fig. 9**, increasing the reaction temperature from 140 to 160 °C increased the fructose yield over both catalysts from 4 to 10-14 Cmol%, after 20-min microwave-assisted reaction in water as the medium. At 160 °C, a longer reaction time of 40 min marginally increased the fructose yield to 13.8-15.6 Cmol%. The reduced rate of fructose formation may imply the deactivation of catalysts, plausibly due to metal leaching and agglomeration and/or carbon intermediate/byproduct deposit on the biochar catalyst surface during the conversion process. Changing the reaction medium from water only to a mixture of

water and acetone (1:1 v/v) achieved similar fructose yields (~14 Cmol%) yet enhanced the selectivity by 10-15% after microwave heating at 160 °C for 20 min. It has been suggested that solvation of intermediates/products in organic solvents may suppress the side reactions and improve the selectivity (Yu and Tsang, 2017). Overall, these results suggest that the humins-derived biochar can serve as a useful support for Al species to catalyze glucose isomerization in green solvent systems (water and acetone/water). The low-value humins generated during the waste-to-chemical process could be further valorized into sustainable solid catalysts for sustainable biorefinery applications, making a step forward to achieve circular bioeconomy with a closed carbon loop.

4. Conclusions

This study proposed the valorization of humins, a biorefinery by-product, for the synthesis of biochar-supported Lewis acid catalysts. Effective catalytic conversion of rice waste into useful platform chemicals (HMF and sugars) was achieved by microwave heating, using AlCl_3 as the catalyst in aqueous medium. The co-produced humins were subjected to Al impregnation and carbonization, which produced biochar catalysts carrying Al-O species on the surface and plausibly in amorphous state. The oxygen-containing functional groups on humins could serve as the anchoring sites for the impregnation agent. The humins-derived biochar catalysts were active toward the isomerization of glucose to fructose under microwave heating at 160 °C in both water and water/acetone medium. Their catalytic performance was comparable with previously reported carbon-based materials, suggesting that humins is a potentially competitive, low-cost precursor of carbon supports. Our findings reveal an innovative practice of integrated

297 biorefinery, by recycling the unavoidable solid residues into renewable catalysts useful for a
298 typical biorefinery chemical process. Such an emerging application of humins can facilitate
299 value-added waste recycling and promote a closed carbon loop to achieve circular economy
300 and sustainable development.

301

302 **Acknowledgement**

303 The authors appreciate the financial support from the Hong Kong International Airport
304 Environmental Fund (Phase 2) and PolyU Project of Strategic Importance. We also
305 acknowledge the support of the University Research Facility on Chemical and Environmental
306 Analysis (URFCE) of PolyU.

307

Reference

1. Agarwal, S., van Es, D., Heeres, H. J. (2017). Catalytic pyrolysis of recalcitrant, insoluble humin byproducts from C6 sugar biorefineries. *J. Anal. Appl. Pyrolysis*, 123, 134-143.
2. Cheng, Z., Everhart, J. L., Tsilomelekis, G., Nikolakis, V., Saha, B., Vlachos, D. G. (2018). Structural analysis of humins formed in the Brønsted acid catalyzed dehydration of fructose. *Green Chem.*, 20, 997-1006.
3. Kerber, S.J., Barr, T.L., Mann, G.P., Brantley, W.A., Papazoglou, E. and Mitchell, J.C. (1998). The complementary nature of x-ray photoelectron spectroscopy and angle-resolved x-ray diffraction part II: Analysis of oxides on dental alloys. *J. Mater. Eng. Perform.*, 7, 334-342.
4. Kumar, M., Xiong, X., Sun, Y., Yu, I.K.M., Tsang, D.C.W., Hou, D., Gupta, J., Bhaskar, T., Pandey, A. (2020) Critical review on biochar-supported catalysts for pollutant degradation and sustainable biorefinery. *Adv. Sustain. Sys.*, 4, 1900149.
5. Lawrinenko, M., Jing, D., Banik, C., Laird, D. A. (2017). Aluminum and iron biomass pretreatment impacts on biochar anion exchange capacity. *Carbon*, 118, 422-430.
6. Mak, T. M. W., Xiong, X., Tsang, D. C. W., Yu, I. K. M., Poon, C. S. (2020). Sustainable food waste management towards circular bioeconomy: Policy review, limitations and opportunities. *Bioresour. Technol.*, 297, 122497.
7. Mukherjee, A., Dumont, M.J., Raghavan, V., 2015. Review: sustainable production of hydroxymethylfurfural and levulinic acid: challenges and opportunities. *Biomass Bioenergy*, 72, 143–183.
8. Filiciotto, L., Balu, A. M., Romero, A. A., Angelici, C., van der Waal, J. C., & Luque, R. (2019). Reconstruction of humins formation mechanism from decomposition products: A GC-MS study based on catalytic continuous flow depolymerizations. *Mol. Catal.*, 479, 110564.
9. Filiciotto, L., Balu, A. M., Van der Waal, J. C., Luque, R. (2018). Catalytic insights into the production of biomass-derived side products methyl levulinate, furfural and humins. *Catal. Today*, 302, 2-15.
10. Hantsche, H.. 1989. Comparison of basic principles of the surface-specific analytical methods: AES/SAM, ESCA (XPS), SIMS, and ISS with X-ray microanalysis, and some applications in research and industry. *Scanning*, 11, 257-280.
11. Hoang, T. M. C., Lefferts, L., Seshan, K. (2013). Valorization of Humin - Based Byproducts from Biomass Processing—A Route to Sustainable Hydrogen. *ChemSusChem*, 6, 1651-1658.

12. Hoang, T.M.C., Geerdink, B., Sturm, J.M., Lefferts, L. and Seshan, K., 2015. Steam reforming of acetic acid—A major component in the volatiles formed during gasification of humin. *Appl. Catal., B*, 163, pp.74-82.
13. Pfab, E., Filiciotto, L., Luque, R. (2019). The Dark Side of Biomass Valorization: A Laboratory Experiment To Understand Humin Formation, Catalysis, and Green Chemistry. *J. Chem. Educ.*, 96, 3030-3037.
14. Rajan, A.S., Sampath, S. and Shukla, A.K., 2014. An in situ carbon-grafted alkaline iron electrode for iron-based accumulators. *Energy Environ. Sci.*, 7, 1110-1116.
15. Sangregorio, A., Muralidhara, A., Guigo, N., Thygesen, L.G., Marlair, G., Angelici, C., de Jong, E. and Sbirrazzuoli, N. (2020). Humin based resin for wood modification and property improvement. *Green Chem.*, 22, 2786-2798.
16. Sangregorio, A., Guigo, N., van der Waal, J.C. and Sbirrazzuoli, N. (2019). All 'green' composites comprising flax fibres and humins' resins. *Compos. Sci. Technol.*, 171, 70-77.
17. Shang, H., Lu, Y., Zhao, F., Chao, C., Zhang, B. and Zhang, H. (2015). Preparing high surface area porous carbon from biomass by carbonization in a molten salt medium. *RSC Adv.*, 5, 75728-75734.
18. Shen, H., Shan, H., Liu, L. (2020). Evolution process and controlled synthesis of humins with 5 - hydroxymethylfurfural (HMF) as model molecule. *ChemSusChem*, 13, 513-519.
19. Tang, J., Zhu, W., Kookana, R., Katayama, A., 2013. Characteristics of biochar and its application in remediation of contaminated soil. *J. Biosci. Bioeng.* 116, 653-659.
20. van Zandvoort, I., Wang, Y., Rasrendra, C. B., van Eck, E. R., Bruijninx, P. C., Heeres, H. J., Weckhuysen, B. M. (2013). Formation, molecular structure, and morphology of humins in biomass conversion: influence of feedstock and processing conditions. *ChemSusChem*, 6, 1745-1758.
21. Wang, K., Jiang, J., Liang, X., Wu, H., Xu, J. (2018). Direct conversion of cellulose to levulinic acid over multifunctional sulfonated humins in sulfolane–water solution. *ACS Sustain. Chem. Eng.*, 6, 15092-15099.
22. Weber, K. and Quicker, P., 2018. Properties of biochar. *Fuel*, 217, 240-261.
23. Xiong, X., Yu, I. K. M., Cao, L., Tsang, D.C.W., Zhang, S.; Ok, Y.S. A review of biochar-based catalysts for chemical synthesis, biofuel production, and pollution control. *Bioresour. Technol.*, 2017, 246, 254-270.

24. Xiong, X., Yu, I. K. M., Tsang, D.C.W., Chen, L., Su, Z., Hu, C., Luo, G., Zhang, S., Ok, Y.S., Clark, J.H., Study of glucose isomerisation to fructose over three heterogeneous carbon-based aluminium-impregnated catalysts. *J. Clean. Prod.*, 2020, 268, 122378.
25. Xiong, X., Yu, I. K. M., Tsang, D.C.W., Bolan, N.S., Ok, Y.S., Igalavithana, A.D., Kirkham, M.B., Kim, K.H., Vikrant, K. (2019). Value-added chemicals from food supply chain wastes: State-of-the-art review and future prospects. *Chem. Eng. J.*, 375, 121983.
26. Yang, J., Niu, X., Wu, H., Zhang, H., Ao, Z., Zhang, S. (2020). Valorization of humin as a glucose derivative to fabricate a porous carbon catalyst for esterification and hydroxyalkylation/alkylation. *Waste Manage.*, 103, 407-415.
27. Yu, I.K.M., Tsang, D.C.W. (2017). Conversion of biomass to hydroxymethylfurfural: A review of catalytic systems and underlying mechanisms. *Bioresour. Technol.*, 238, 716-732.
28. Yu, I. K. M., Xiong, X., Tsang, D. C. W., Wang, L., Hunt, A.J., Song, H., Shang, J., Ok, Y.S., and Poon, C.S., (2019a). Aluminium-biochar composites as sustainable heterogeneous catalysts for glucose isomerisation in a biorefinery. *Green Chem.*, 21, 1267-1281.
29. Yu, I. K. M., Xiong, X., Tsang, D. C. W., Ng, Y.H., Clark, J.H., Fan, J., Zhang, S., Hu, C. and Ok, Y.S., (2019b). Graphite oxide-and graphene oxide-supported catalysts for microwave-assisted glucose isomerisation in water. *Green Chem.*, 21, 4341-4353.