THE UNIVERSITY *of* EDINBURGH

Edinburgh Research Explorer

Tetrazine-Mediated Postpolymerization Modification

Citation for published version:

Jain, S, Neumann, K, Zhang, Y, Geng, J & Bradley, M 2016, 'Tetrazine-Mediated Postpolymerization Modification', *Macromolecules*, vol. 49, no. 15, pp. 5438-5443.
<https://doi.org/10.1021/acs.macromol.6b00867>

Digital Object Identifier (DOI):

[10.1021/acs.macromol.6b00867](https://doi.org/10.1021/acs.macromol.6b00867)

Link:

[Link to publication record in Edinburgh Research Explorer](#)

Document Version:

Peer reviewed version

Published In:

Macromolecules

General rights

Copyright for the publications made accessible via the Edinburgh Research Explorer is retained by the author(s) and / or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

The University of Edinburgh has made every reasonable effort to ensure that Edinburgh Research Explorer content complies with UK legislation. If you believe that the public display of this file breaches copyright please contact openaccess@ed.ac.uk providing details, and we will remove access to the work immediately and investigate your claim.

This document is confidential and is proprietary to the American Chemical Society and its authors. Do not copy or disclose without written permission. If you have received this item in error, notify the sender and delete all copies.

Tetrazine Mediated Post-polymerization

Journal:	Macromolecules
Manuscript ID	ma-2016-00867k.R1
Manuscript Type:	Article
Date Submitted by the Author:	05-Jul-2016
Complete List of Authors:	Jain, Sarthak; University of Edinburgh, School of Chemistry Neumann, Kevin; University of Edinburgh, School of Chemistry Zhang, Yichuan; University of Edinburgh, School of Chemistry Geng, Jin; University of Edinburgh, School of Chemistry Bradley, Mark; University of Edinburgh, School of Chemistry

SCHOLARONE™
Manuscripts

Tetrazine Mediated Post-polymerization Modification

Sarthak Jain[‡], Kevin Neumann[‡], Yichuan Zhang, Jin Geng^{} and Mark Bradley^{*}*

School of Chemistry, The University of Edinburgh, Joseph Black Building, David Brewster
Road, Edinburgh, EH9 3FJ.

ABSTRACT. A new and highly efficient polymer, post-polymerization, modification platform based on an inverse electron demand Diels-Alder reaction is reported. Well-defined defined polymers were synthesized from allyl glycidyl ether and glycidol by anionic ring-opening polymerization with post-polymerization modifications conducted with a number of tetrazine derivatives which carried functional groups spanning from carboxylates and esters to primary amines. Analysis of polymerization kinetics by real-time ¹H NMR and GPC revealed a rapid and high degree of side-chain conversion (>99%), with the generation of well-defined functional polymers, in both organic and aqueous solvents, without the need for additives or catalysts.

Introduction

Poly (ethylene glycol)s (PEGs) are one of the most widely used polymers, with applications ranging from drug-delivery¹ and protein bioconjugation,² to the synthesis of hydrogels,³ as well as being applied in emerging technologies such as solar cells.⁴ Poly (allyl glycidyl ethers) (PAGE's) have been suggested as functional alternatives to PEG, as they offer an identical

polyether backbone, while offering post-polymerization modification capability through the functional allyl handles positioned along the polymer chain.⁵⁻⁹

Post-polymerization modifications are typically based on the reaction of functional groups incorporated within a polymer that are inert under polymerization conditions, but which can be converted in a subsequent reaction step into a broad range of other functional groups, or act as the site of a second polymerization reaction. These modifications need to be highly efficient to guarantee near quantitative conversion, ideally under mild reaction conditions that avoid degradation of either the polymer or the functionality that is being introduced. Although a number of successful reactions have been introduced for post-polymerization modifications,^{10,11} the development of efficient synthetic protocols to decorate polymers with functional units remains a key need in macromolecular chemistry.

The advent of so-called “click chemistry”¹² techniques have led to widely accessible, and well-defined macromolecular architectures and functional polymers. Among these, the copper-catalyzed azide-alkyne Huisgen 1,3-dipolar cycloaddition (CuAAC) reaction has become almost synonymous with the term “click reaction” and has led to a great number of post-polymerization modifications over the past decade.¹⁰ Although the requirement for a metal catalyst and its subsequent removal can be a limitation (particularly for biomedical applications) there are always concerns over the explosive nature of low-molecular weight azido species. Some metal-free “click chemistries” have been reported for polymer modification, such as the ‘thiol-ene’^{13,14} reaction, however, thiol-containing compounds undergo various of oxidation-based chemistries, such as disulfide formation, limiting scope. An other possible drawback of thiol-ene addition chemistry is that the radical formed following thiol addition may attack adjacent vinyl groups, leading to intramolecular cyclizations.¹⁵

The additive free, inverse electron demand Diels-Alder ($_{inv}DA$) reaction, between electron deficient tetrazines and electron rich dienophiles has attracted considerable attention. Thus tetrazine-norbornene chemistry has been extensively employed in bioconjugation,¹⁶⁻¹⁸ in cellular imaging,¹⁹ and DNA ligation roles.²⁰ Notably, the $_{inv}DA$ has been applied to modify and conjugate polymer chains, however, to date, only tetrazine strained-norbornene chemistry has been reported.²¹⁻²⁶ An alternative to strained norbornenes are unstrained dienophiles which can also react with tetrazines,²⁷⁻²⁹ and which are synthetically readily available, stable, and comparatively small in size compared to norbornene, an important feature as smaller functional side chain typically result in increased degrees of functionalization,³⁰ due to diminished steric effects. In particular, the study of the explosive properties of tetrazine-based high nitrogen molecules indicated that 1,2,4,5-tetrazine derivatives display good thermal stability.^{31,32}

The significant promise of PAGE-based materials, thus promoted an investigation into post-polymerization modification through $_{iva}DA$ reaction's with tetrazines with the aim of establishing a robust platform amenable to the elaboration of polymers with a wide variety of functionalities^{24,33} in an efficient fashion.

Results and Discussion

A series of tetrazine derivatives containing pyridyl, phenyl and/or pyrimidyl moieties attached to carboxylic acids, esters and primary amine moieties were employed to study how these substituents influenced the bimolecular reaction of the $_{iva}DA$ reaction, with allyl glycidyl ether used as the reaction partner in these initial scoping reactions with reaction monitoring conducted via NMR analysis. The reaction with TZ1 was found to proceed to completion within 2 hours at 25 °C (Table 1). Under the same conditions the reactions with the TZ2-TZ7 were significantly

1
2
3 slower with conversions of 17% to 50% within 14 hours, however increasing the temperature to
4
5 60 °C gave conversions of over 90% in 10 hours in all cases. At 100 °C, the reaction with TZ7
6
7 reached completion within 3 hours, however under these conditions TZ2 gradually degraded.
8
9

10 TZ2, TZ6 and TZ7 were chosen as examples of different tetrazine reaction centers with rate
11
12 constants determined under pseudo first-order conditions following the decay in the absorption
13
14 of the tetrazine unit at 530 nm. Pseudo first-order rate constants were obtained by fitting the data
15
16 with a simple exponential equation. (Figure S5-7 in supporting information) with the second-
17
18 order rate constants were calculated from the linear dependence of the observed rate constants on
19
20 the concentration of the allyl glycidyl ether used (Table 2). It was expected that the reaction
21
22 between the tetrazines (TZ2-7) and allyl glycidyl ether would be a slower than the corresponding
23
24 strained dienophiles, such as norbornenes ($k \approx 1\text{-}5 \text{ M}^{-1}\text{s}^{-1}$) or *trans*-cyclooctenes ($k \approx 10^4 \text{ M}^{-1}\text{s}^{-1}$).
25
26 but there is considerable discrepancy in the literature.^{16,34-37} The strong electron-withdrawing
27
28 effect of the esters in TZ1, clearly enhances the reactivity of the tetrazine, displaying rates
29
30 comparable to those of the strained dienophiles with dipyridyltetrazine.³⁴ Herein, our results
31
32 showed that the reactivity of TZs followed the order of $\text{TZ1} \gg \text{TZ2} \approx \text{TZ6} > \text{TZ7}$, as a result of
33
34 the decreasing electron-density of the tetrazines.³⁸ However, TZ1 was highly reactive, being
35
36 fully/rapidly degraded in the presence of trace amounts of water and was not used in studies
37
38 going forward.
39
40
41
42
43
44

45 Based upon this understanding, post-polymerization modifications of the poly (allyl glycidyl
46
47 ether)s were carried out. The homopolymers (PAGE1, PAGE2 and PAGE3) and the random
48
49 copolymers poly (allyl glycidyl ether-*co*-glycidol) (PAGE-*co*-PG) were prepared via anion ring-
50
51 opening polymerization using potassium alkoxide/naphthalenide as initiators.^{6,7,39,40} All polymers
52
53
54
55
56
57
58
59
60

obtained exhibited mono-modal molecular weight distributions and low PDIs, with absolute molecular weights determined by ^1H NMR analysis (Table 3).

Similar rates were found when react TZ6, TZ2 and TZ7 with the monomer, AGE at 60 °C (see Figure 1a). The reaction of PAGE2 with TZ2, TZ6 and TZ7 showed relative rates analogous to those found above with under the same reaction conditions (Figure 1b), with TZ2 and TZ6 displaying similar reactivities some 2 fold greater than TZ7. The different rates were likely to be the result of the electronic effects and steric effects of the becoming neighboring tetrazine groups on the polymer chain. It has been reported that steric effects are important when functional groups are close to the polymer backbone.⁴¹ TZ6 is smaller than TZ2 and TZ7, and the pyridine groups of TZ6 can be readily protonated which probably enhances its reactivity, thus resulting in a faster rate of reaction. TZ2 has a bulky end group (tert-butyloxycarbonyl) compared to TZ7 which has a free carboxylic acid group. We assume that the slower rate of conversion with TZ7 was due to the electronic effects of TZ7 with unfavorable carboxylic acid concentrations along the polymer backbone distanced.

Virtually complete conversion of all allyl-ether pendants could be achieved by tuning the reaction temperature (see Figure 2), with NMR revealing complete consumption of all pendant allyl groups within 18 hours at 60 °C and 8 hours at 100°C, with the slowest reacting tetrazine TZ7. Interestingly, the rate of the post-polymerization reaction was also found to be molecular weight dependent, as shown in Figure 3, with PAGE1-3 (M_n = 511 Da, 9 kDa and 40.5 kDa) showing 50% conversion after 1, 4 and 16 hours respectively, despite there being a 4 fold excess of tetrazine (over alkene) in each case. GPC showed the expected increase in molecular weight with no observable crosslinking (Figure 4), It is also important to emphasize that gel permeation

1
2
3 chromatography (GPC) analysis of the resulting polymers showed low PDI = 1.03-1.07,
4
5 indicating well-controlled reactions (Table 3).
6
7

8 During post-polymerization modification of PAGE2 with TZ2, the reaction lead to polymers
9
10 bearing both hydroxyridazine and 1,2-pyridazine pendant units (as evidenced by ^1H NMR
11
12 analysis (Figure 5)), over time the aromatization of the intermediate product, hydroxyridazine
13
14 pendant units, proceeded to completion via air oxidation (O_2).
15
16

17 To further explore the potential scope of the post-polymerization in aqueous environments, a
18
19 copolymer was prepared using ethoxyethyl glycidyl ether (EEGE) and allyl glycidyl ether. Poly
20
21 (allyl glycidyl ether-*co*-glycidol) was obtained through the removal of the protecting group with
22
23 modification using the water soluble tetrazine, TZ3, conducted in D_2O and followed by ^1H NMR
24
25 with a single isomer depicted. The reactions proceeded at higher rates compared to similar
26
27 reactions in $[\text{D}_6]\text{DMSO}$ with the reaction in water reaching full conversion of the polymer within
28
29 2 hours at 37 °C (Figure 6). The inverse electron demand Diels-Alder performed an aqueous
30
31 acceleration behavior, in an agreement with the previous report.⁴²
32
33
34
35
36
37

38 Conclusion

39
40 A series of allyl glycidyl ether polymers were prepared by anionic ring-opening
41
42 polymerization giving control over the properties of the polymers. Post-polymerization
43
44 functionalization of the polymers though an inverse electron demand Diels-Alder reaction with a
45
46 range of tetrazines was demonstrated in both organic and aqueous environments, giving high
47
48 degrees of conversion (> 99%) with relative reaction rates determined by ^1H NMR. The
49
50 observation of different reaction rates between polymers with the tetrazines being a combination
51
52 of steric and electronic effects, with presumably the steric effects being more following
53
54
55
56
57
58
59
60

1
2
3 modification of the side-chains of the polymer. This approach enables the direct post-
4
5 functionalization of allyl glycidyl ether polymers in a highly efficient fashion without the need
6
7 for catalysts or additives. In particular, with high rates of reaction in water, we propose that the
8
9 reaction offers some advantages over existing methodologies for post-polymerization in aqueous
10
11 solution. We believe this concept can be used as a versatile post-polymerization modification
12
13 tool and adds value to the available repertoire of functionalization techniques. The general nature
14
15 of the synthesis is remarkable and points towards broad applicability of this method in the
16
17 fabrication of functional soft materials.
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

Scheme 1. (a) Preparation of poly(allyl glycidyl ether) and their reaction with tetrazine, and (b) Tetrazines used in this study.

Table 1. Reaction conditions used for the analysis of tetrazines with allyl glycidyl ether (AGE) in [D₆]DMSO^a, and conversion.

Tetrazine	Temperature / °C	Conversion ^b / %	Time / h
TZ1	25	100	1.5
TZ2	25	50	10
TZ2	60	91	10
TZ2	100	80	2.5
TZ3	25	38	14
TZ3	60	95	12
TZ4	25	17	10
TZ4	60	95	11
TZ6	25	14	14
TZ6	60	97	14
TZ7	25	32	14
TZ7	60	88	12
TZ7	100	100	3

[^a]the molar ratio of tetrazine to allyl glycidyl ether was 4:1; [^b]Measured by relative integration of the allyl vs aromatic protons of 1,2,4,5-tetramethylbenzene (used as an internal standard).

Table 2. Second-order rate constants for invDA reaction of tetrazines TZ2, TZ6 and TZ7 with allyl glycidyl ethers.

Tetrazine	$k \times 10^{-5} [\text{M}^{-1} \text{s}^{-1}]^{\text{a}}$	R^2
TZ2	8.93	0.97
TZ6	7.18	0.98
TZ7	1.99	0.98

[a]All reactions were performed in DMSO at 25 °C and repeated at least three times. The initial concentration of tetrazines was 0.5 mM and varying concentration of AGE between 5 mM to 50 mM, corresponding to 10-100 equivalents with respect to the tetrazines respectively. The loss of the absorption of the TZ was measured over time at 530 nm. The linear dependence of the observed rate constants k' on the concentration of AGE provided the second-order rate constants k ($n=3$) (for details see the supporting information).

Table 3. Polymer characterization

Polymer	M_n (g mol^{-1})	PDI^{b}
PAGE1	511 ^a	1.06
PAGE2	9004 ^a	1.11
PAGE3	40584 ^a	1.24
PAGE- <i>co</i> -PG	9966 ^a	1.30
PAGE2 + TZ2	10400 ^b	1.07
PAGE2 + TZ6	6430 ^b	1.05
PAGE- <i>co</i> -PG + TZ3	11023 ^b	1.31

[^a]Determined by ^1H NMR. [^b]Determined by GPC (eluting with DMF with 1% LiBr at 60 °C, calibrated with PMMA standards).

Figure 1. Reaction progress of tetrazines (● TZ2; □ TZ6; and △ TZ7 with a) AGE and b) PAGE2, in $[D_6]$ DMSO at 60 °C. Reaction condition: $[Alkene]/[TZ2] = 1/4$, $[alkene] = 14$ mM.

Figure 2. Reaction progress of TZ7 with PAGE2, $M_n = 9004$ g mol⁻¹) in $[D_6]$ DMSO at different temperatures: (●) 25 °C; (○) 60 °C; (□) 100 °C. Reaction condition: $[Alkene]/[TZ2] = 1/4$, $[alkene] = 14$ mM.

Figure 3. Reaction progress using polymers of differing molecular weigh: ($\square$) PAGE1; ($\circ$) PAGE2; and ($\triangle$) PAGE3 with TZ2 in $[D_6]$ DMSO at 60 °C. $[Alkene]/[TZ2] = 1/4$, $[alkene] = 14$ mM.

Figure 4. Gel permeation chromatographs of PAGE2 (black trace) and *inv*DA reaction products PAGE2+TZ2 (green trace) and PAGE2+TZ6 (red trace) (eluting with DMF with 1% LiBr at 60 °C, calibrated with PMMA standards).

Figure 5. ¹H NMR analysis of the reaction of PAGE2 with TZ2 at 60 °C in [D₆]DMSO. Protons of the alkenes are labeled (a, blue). The hydroxyl methyl protons of the hydroxyridazine, and pyridazine are depicted (b, pink) and (c, brown), respectively. Spectra were recorded at 30 min intervals.

Figure 6. Reaction progress of PAGE-co-PG with TZ3 in D₂O at 25 °C (●) and 37 °C (Δ).

Reaction condition: [Alkene]/[TZ2] = 1/4, [alkene] = 14 mM.

ASSOCIATED CONTENT

Supporting Information. Data analysis and details of synthesis of tetrazines, homopolymers and copolymer. This material is available free of charge via the Internet at <http://pubs.acs.org>.

AUTHOR INFORMATION

Corresponding Author

*E-mail: jin.geng@ed.ac.uk; mark.bradely@ed.ac.uk

Author Contributions

‡These authors contributed equally.

ACKNOWLEDGMENT

This work was supported by the European Research Council (Advanced Grant ADREEM ERC-2013-340469) and Biotechnology and Biological Sciences Research Council (BB/L00609X/1).

Table of Contents

REFERENCES

- (1) Knop, K.; Hoogenboom, R.; Fischer, D.; Schubert, U. S. Poly(ethylene glycol) in Drug Delivery: Pros and Cons as Well as Potential Alternatives. *Angew Chem Int Edit* **2010**, *49* (36), 6288–6308.
- (2) Caliceti, P.; Veronese, F. Pharmacokinetic and biodistribution properties of poly(ethylene glycol)-protein conjugates. *Adv Drug Deliver Rev* **2003**, *55* (10), 1261–1277.
- (3) Pritchard, C. D.; O'Shea, T. M.; Siegwart, D. J.; Calo, E.; Anderson, D. G.; Reynolds, F. M.; Thomas, J. A.; Slotkin, J. R.; Woodard, E. J.; Langer, R. An injectable thiol-acrylate

poly(ethylene glycol) hydrogel for sustained release of methylprednisolone sodium succinate. *Biomaterials* **2011**, 32 (2), 587–597.

(4) de Freitas, J. N.; Nogueira, A. F.; de Paoli, M. A. New insights into dye-sensitized solar cells with polymer electrolytes. *J Mater Chem* **2009**, 19 (30), 5279–5294.

(5) Sunder, A.; Türk, H.; Haag, R.; Frey, H. Copolymers of Glycidol and Glycidyl Ethers: Design of Branched Polyether Polyols by Combination of Latent Cyclic AB₂ and ABR Monomers. *Macromolecules* **2000**, 33 (21), 7682–7692.

(6) Michael E.; Helmut K.; Möller, M. Polyglycidols with Two Orthogonal Protective Groups: Preparation, Selective Deprotection, and Functionalization. *Macromolecules* **2007**, 40 (9), 3070–3079.

(7) Lee, B. F.; Kade, M. J.; Chute, J. A.; Gupta, N.; Campos, L. M.; Fredrickson, G. H.; Kramer, E. J.; Lynd, N. A.; Hawker, C. J. Poly(allyl glycidyl ether)-A versatile and functional polyether platform. *J Polym Sci Pol Chem* **2011**, 49 (20), 4498–4504.

(8) Persson, J.; Jannasch, P. Intrinsically proton-conducting comb-like copolymers with benzimidazole tethered to the side chains. *Solid State Ionics* **2006**, 177 (7-8), 653–658.

(9) Hu, Z.; Fan, X.; Zhang, G. Synthesis and characterization of glucose-grafted biodegradable amphiphilic glycopolymers P(AGE-glucose)-*b*-PLA. *Carbohydr Polym* **2010**, 79 (1), 119–124.

(10) Günay, K.; Theato, P.; Klok, H. Standing on the shoulders of Hermann Staudinger: Post-polymerization modification from past to present. *J Polym Sci Pol Chem* **2013**, 51 (1), 1–28.

- (11) Willcock, H.; O'Reilly, R. K. End group removal and modification of RAFT polymers. *Polym Chem* **2010**, *1* (2), 149–157.
- (12) Kolb, H. C.; Finn, M. G.; Sharpless, K. B. Click Chemistry: Diverse Chemical Function from a Few Good Reactions. *Angew Chem Int Edit* **2001**, *40* (11), 2004–2021.
- (13) Hoyle, C. E.; Bowman, C. N. Thiol–Ene Click Chemistry. *Angew Chem Int Edit* **2010**, *49* (9), 1540–1573.
- (14) Hoyle, C. E.; Lowe, A. B.; Bowman, C. N. Thiol -click chemistry: a multifaceted toolbox for small molecule and polymer. *Chem Soc Rev* **2010**, *39* (4), 1355–1387.
- (15) Justynska, J.; Hordyjewicz, Z.; Schlaad, H. Toward a toolbox of functional block copolymers via free-radical addition of mercaptans. *Polymer* **2005**, *46* (26), 12057–12064.
- (16) Šečkutė, J.; Devaraj, N. K. Expanding room for tetrazine ligations in the in vivo chemistry toolbox. *Curr Opin Chem Biol* **2013**, *17* (5), 761–767.
- (17) Kurra, Y.; Odoi, K. A.; Lee, Y. J.; Yang, Y.; Lu, T.; Wheeler, S. E.; Torres-Kolbus, J.; Deiters, A.; Liu, W. R. Two Rapid Catalyst-Free Click Reactions for In Vivo Protein Labeling of Genetically Encoded Strained Alkene/Alkyne Functionalities. *Bioconjugate Chem* **2014**, *25* (9), 1730–1738.
- (18) Devaraj, N. K.; Weissleder, R.; Hilderbrand, S. A. Tetrazine-Based Cycloadditions: Application to Pretargeted Live Cell Imaging. *Bioconjugate Chem* **2008**, *19* (12), 2297–2299.
- (19) Lang, K.; Davis, L.; Torres-Kolbus, J.; Chou, C.; Deiters, A.; Chin, J. W. Genetically encoded norbornene directs site-specific cellular protein labelling via a rapid. *Nat Chem* **2012**, *4* (4), 298–304.

(20) Schoch, J.; Wiessler, M.; Jäschke, A. Post-Synthetic Modification of DNA by Inverse-Electron-Demand Diels–Alder Reaction. *J Am Chem Soc* **2010**, *132* (26), 8846–8847.

(21) Hansell, C. F.; Lu, A.; Patterson, J. P.; O'Reilly, R. K. Exploiting the tetrazine–norbornene reaction for single polymer chain collapse. *Nanoscale* **2014**, *6* (8), 4102–4107.

(22) Hansell, C. F.; Espeel, P.; Stamenović, M. M.; Barker, I. A.; Dove, A. P.; Prez, Du, F. E.; O'Reilly, R. K. Additive-Free Clicking for Polymer Functionalization and Coupling by Tetrazine–Norbornene Chemistry. *J Am Chem Soc* **2011**, *133* (35), 13828–13831.

(23) Alge, D. L.; Azagarsamy, M. A.; Donohue, D. F.; Anseth, K. S. Synthetically Tractable Click Hydrogels for Three-Dimensional Cell Culture Formed Using Tetrazine–Norbornene Chemistry. *Biomacromolecules* **2013**, *14* (4), 949–953.

(24) Barker, I. A.; Hall, D. J.; Hansell, C. F.; Prez, Du, F. E.; O'Reilly, R. K.; Dove, A. P. Tetrazine–Norbornene Click Reactions to Functionalize Degradable Polymers Derived from Lactide. *Macromol Rapid Comm* **2011**, *32* (17), 1362–1366.

(25) Desai, R. M.; Koshy, S. T.; Hilderbrand, S. A.; Mooney, D. J.; Joshi, N. S. Versatile click alginate hydrogels crosslinked via tetrazine–norbornene chemistry. *Biomaterials* **2015**, *50*, 30–37.

(26) Han, H.S.; Devaraj, N. K.; Lee, J.; Hilderbrand, S. A.; Weissleder, R.; Bawendi, M. G. Development of a Bioorthogonal and Highly Efficient Conjugation Method for Quantum Dots Using Tetrazine–Norbornene Cycloaddition. *J Am Chem Soc* **2010**, *132* (23), 7838–7839.

(27) Lee, Y.J.; Kurra, Y.; Yang, Y.; Torres-Kolbus, J.; Deiters, A.; Liu, W. R. Genetically encoded unstrained olefins for live cell labeling with tetrazine dyes. *Chem Comm* **2014**, 50 (86), 13085–13088.

(28) Rieder, U.; Luedtke, N. W. Alkene-Tetrazine Ligation for Imaging Cellular DNA. *Angew Chem Int Edit* **2014**, 53 (35), 9168–9172.

(29) Chen, C.; Allen, C. A.; Cohen, S. M. Tandem Postsynthetic Modification of Metal–Organic Frameworks Using an Inverse-Electron-Demand Diels–Alder Reaction. *Inorg Chem* **2011**, 50 (21), 10534–10536.

(30) Hatada, K.; Kitayama, T.; Vogl, O. In *Macromolecular Design of Polymeric Materials*; Jaycox, G. D.; Vogl, O.; Hatada, K.; Eds.; CRC Press, 1997; p 1.

(31) Chavez, D. E.; Tappan, B. C.; Hiskey, M. A.; Son, S. F.; Harry, H.; Montoya, D.; Hagelberg, S. New High-Nitrogen Materials Based on Nitroguanyl-Tetrazines: Explosive Properties, Thermal Decomposition and Combustion Studies. *Propellants Explos. Pyrotech. PEP* **2005**, 30 (6), 412–417.

(32) Chavez, D. E.; Hanson, S. K.; Veauthier, J. M.; Parrish, D. A. Electroactive Explosives: Nitrate Ester-Functionalized 1,2,4,5-Tetrazines. *Angewandte Chemie* **2013**, 125 (27), 7014–7017.

(33) Chen, L.; Phillip, W. A.; Cussler, E. L.; Hillmyer, M. A. Robust Nanoporous Membranes Templated by a Doubly Reactive Block Copolymer. *J Am Chem Soc* **2007**, 129 (45), 13786–13787.

(34) Sauer, J.; Heldmann, D. K.; Hetzenegger, J.; Krauthan, J.; Sichert, H.; Schuster, 1,2,4,5-Tetrazine: Synthesis and Reactivity in [4+2] Cycloadditions. *J. Eur J Org Chem* **1998**, 1998 (12), 2885–2896.

(35) Wang, D.; Chen, W.; Zheng, Y.; Dai, C.; Wang, K.; Ke, B.; Wang, B. 3,6-Substituted-1,2,4,5-tetrazines: tuning reaction rates for staged labeling applications. *Org Biomol Chem* **2014**, 12 (23), 3950–3955.

(36) Vrabel, M.; Kölle, P.; Brunner, K. M.; Gattner, M. J.; López Carrillo, V.; de Vivie Riedle, R.; Carell, T. Norbornenes in Inverse Electron-Demand Diels–Alder Reactions. *Chem Eur J* **2013**, 19 (40), 13309–13312.

(37) Blackman, M. L.; Royzen, M.; Fox, J. M. Tetrazine Ligation: Fast Bioconjugation Based on Inverse-Electron-Demand Diels–Alder Reactivity. *J Am Chem Soc* **2008**, 130 (41), 13518–13519.

(38) Carboni, R. A.; Lindsey, R. V., Jr. Reactions of Tetrazines with Unsaturated Compounds. A New Synthesis of Pyridazines. *J Am Chem Soc* **1959**, 81 (16), 4342–4346.

(39) Barteau, K. P.; Wolffs, M.; Lynd, N. A.; Fredrickson, G. H.; Kramer, E. J.; Hawker, C. J. Allyl Glycidyl Ether-Based Polymer Electrolytes for Room Temperature Lithium Batteries. *Macromolecules* **2013**, 46 (22), 8988–8994.

(40) Hrubý, M.; Koňák, Č.; Ulbrich, K. Poly(allyl glycidyl ether)-block-poly(ethylene oxide): A novel promising polymeric intermediate for the preparation of micellar drug delivery systems. *J Appl Polym Sci* **2005**, 95 (2), 201–211.

(41) Ebdon, J. R. *New Methods Polymer Synthesis*; Ebdon, J. R., Ed.; Springer Science & Business Media: Boston, MA, 2012; p 138.

(42) Wijnen, J. W.; Zavarise, S.; Engberts, J. B. F. N.; Charton, M. Substituent Effects on an Inverse Electron Demand Hetero Diels–Alder Reaction in Aqueous Solution and Organic Solvents: Cycloaddition of Substituted Styrenes to Di(2-pyridyl)-1,2,4,5-tetrazine. *J Org Chem* **1996**, *61* (6), 2001–2005.