THE UNIVERSITY *of* EDINBURGH

Edinburgh Research Explorer

Nonlinear homogenisation of trabecular bone: effect of solid phase constitutive model

Citation for published version:

Levrero-Florencio, F, Manda, K, Margetts, L & Pankaj, P 2017, 'Nonlinear homogenisation of trabecular bone: effect of solid phase constitutive model', *Proceedings of the Institution of Mechanical Engineers, Part H: Journal of Engineering in Medicine*, vol. 231, no. 5, pp. 405-414.
<https://doi.org/10.1177/0954411916676220>

Digital Object Identifier (DOI):

[10.1177/0954411916676220](https://doi.org/10.1177/0954411916676220)

Link:

[Link to publication record in Edinburgh Research Explorer](#)

Document Version:

Peer reviewed version

Published In:

Proceedings of the Institution of Mechanical Engineers, Part H: Journal of Engineering in Medicine

General rights

Copyright for the publications made accessible via the Edinburgh Research Explorer is retained by the author(s) and / or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

The University of Edinburgh has made every reasonable effort to ensure that Edinburgh Research Explorer content complies with UK legislation. If you believe that the public display of this file breaches copyright please contact openaccess@ed.ac.uk providing details, and we will remove access to the work immediately and investigate your claim.

Nonlinear homogenisation of trabecular bone: effect of solid phase constitutive model

Francesc Levrero-Florencio¹, Krishnagoud Manda¹, Lee Margetts^{2,3}, Pankaj Pankaj¹

¹ Institute for Bioengineering, School of Engineering

The University of Edinburgh, United Kingdom

² School of Earth, Atmospheric and Environmental Sciences

University of Manchester, United Kingdom

³ Oxford e-Science Research Centre

University of Oxford, United Kingdom

Corresponding author:

Francesc Levrero Florencio, Institute for Bioengineering, School of Engineering, The University of Edinburgh, Faraday Building, King's Buildings, EH9 3JG Edinburgh, United Kingdom.

Email: f.levrero-florencio@ed.ac.uk

Abstract

Micro-finite element models have been extensively employed to evaluate the elastic properties of trabecular bone and, to a limited extent, its yield behaviour. The macroscopic stiffness tensor and yield surface are of special interest since they are essential in the prediction of bone strength and stability of implants at the whole bone level. While macroscopic elastic properties are now well understood, yield and post-yield properties are not. The aim of this study is to shed some light on what the effect of the solid phase yield criterion is on the macroscopic yield of trabecular bone for samples with different microstructure. Three samples with very different density were subjected to a large set of apparent load cases (which is important since physiological loading is complex and can have multiple components in stress or strain space) with two different solid phase yield criteria: Drucker-Prager and Eccentric-Ellipsoid. The study found that these two criteria led to small differences in the macroscopic yield strains for most load cases except for those that were compression-dominated; in these load cases the yield strains for the Drucker-Prager criterion were significantly higher. Higher density samples resulted in higher differences between the two criteria. This work provides a comprehensive assessment of the effect of two different solid phase yield criteria on the macroscopic yield strains of trabecular bone, for a wide range of load cases, and for samples with different morphology.

Keywords: Finite element, bone biomechanics, micro-architecture, constitutive models, multiscale modelling

Introduction

With the exponential growth of older population, problems associated with the load bearing capacity of trabecular bone need urgent attention. Thus, a deeper understanding of how the microstructure of bone, the material properties of the solid phase, and its macroscopic mechanical properties are related is needed in order to examine the response of musculoskeletal systems ¹.

Trabecular bone is a highly heterogeneous material that resembles open-cell foams and its properties depend on the considered working scale. While trabecular bone at the macroscale is highly anisotropic ²⁻⁴, trabecular bone at the microscale is usually modelled as an isotropic material ^{5, 6} although it is recognised that trabecular bone at this level is transverse isotropic or orthotropic ⁷⁻⁹. However, as Cowin ¹⁰ pointed out, since the axis of the trabecula is the same as the loading axis, a beam made of orthotropic material can be reduced to a beam made of isotropic material. Although trabecular bone elastic properties ^{11, 12} are well established, its nonlinear behaviour is not fully understood.

The cellular structure of trabecular bone endows it with complex failure mechanisms. These mechanisms are known to depend on trabecular bone microstructure, and while high density bone tends to fail due to tissue yielding, low density bone is inclined to fail due to a combination of tissue yielding and large deformation mechanisms, i.e. bending and buckling of trabeculae ¹³⁻¹⁵. Therefore, in numerical simulations using micro-finite element models (μ FE) both material and geometric nonlinearities need to be included in order to capture the correct behaviour of a trabecular bone specimen.

Porosity is a key feature of bone, which is reported to be present at every hierarchical scale ¹⁶. Tai, Ulm ¹⁷ showed that bone behaves like a cohesive-frictional material and that the increased yield properties in compression may be explained by the friction between the mineral components, and that cohesion is provided by the organic matrix. Several computational studies on the nanoindentation behaviour of bone tissue have successfully modelled the mechanical response found in nanoindentation experiments by

using a Mohr-Coulomb ¹⁷ or a Drucker-Prager ¹⁸ (DP) yield surfaces. Maghous, Dormieux ¹⁹ showed that an eccentric-ellipsoid (EE) is the yield surface of an isotropic porous material the matrix of which is modelled with a DP yield surface. Consequently, Schwiedrzik and Zysset ²⁰ reported that EE could effectively approximate the yield behaviour of bone tissue. Data on post-yield hardening behaviour of the solid phase of bone is not readily available and most of the simulations for nonlinear homogenisation use a 5% of the elastic slope as the linear hardening slope ^{5, 21-23}. Some experimental studies have measured the hardening behaviour of the extracellular matrix ^{24, 25}, but this cannot be directly employed for representing the solid phase of trabecular bone due to the difference in scale.

Homogenisation techniques to obtain the macroscopic response of bone from its microstructure have been successfully employed for determining bone apparent anisotropic elastic properties ^{11, 12, 26}. Links have also been established to relate elastic properties with bone volume over total volume fraction (BV/TV) and fabric tensors ^{3, 27, 28}. However, homogenisation procedures to find yield and post-yield properties of bone are much more computationally expensive since they require evaluation of multiple load cases to assess multiaxial behaviour. Additionally, in order to capture nonlinear phenomena, FE meshes need to be finer and each load step may require a number of iterations to obtain a converged solution if an implicit time integration scheme is used. Only few studies have attempted nonlinear homogenisation techniques on trabecular bone ^{5, 21-23, 29}. In these studies, only Panyasantisuk, Pahr ²¹ and Levrero-Florencio, Margetts ²⁹ used a DP criterion, while the others used a simple bilinear criterion to represent the solid phase of bone. Results of these studies indicate that the macroscopic yield surface of trabecular bone can be effectively approximated by an isotropic criterion in strain space.

To our knowledge there is only one previous study that has examined the effect of different solid phase yield criteria on the macroscopic yield response of bone ³⁰. However, this study only considered two simple load cases, unconfined uniaxial compression and pure shear, and concluded that the differences

between macroscopic yield with different solid phase criteria were small and any solid phase criterion with strength asymmetry will perform reasonably well. The aim of this study is to evaluate the effect of two different solid phase yield surfaces with the same uniaxial strength asymmetry, DP and EE, on the yield strains at the macroscopic level by using a nonlinear homogenisation approach, derived from multiscale theory³¹⁻³³, by applying a large range of load cases, including complex normal and shear scenarios.

Materials and methods

Sample extraction and imaging

Three cylindrical specimens of bovine trabecular bone (young cattle, <2.5 years old) were extracted from bovine trochanters. The extracted specimens had approximate dimensions of 10.7 mm diameter and 30 mm length. Diamond-tipped cores (Starlite Industries, Rosemont PA, USA) were used in the extraction of the specimens and the edges were cut with a slow speed saw (Isomet 1000, Buehler, Düsseldorf, Germany) by using a diamond wafering blade designed for bone; all these operations were performed under constant irrigation to avoid excessive abrasion and overheating. After coring, the specimens were submerged in phosphate buffered saline (PBS) and scanned using a μ CT device (Skyscan 1172, Bruker, Zaventem, Belgium) with a resolution of 17.22 μ m. The scanning parameters were 94 kV, 136 mA and 200 ms integration time; four scans in 720 equiangular radial positions. Binarisation of the grey scale images was performed with an automatic thresholding algorithm ³⁴.

Three virtual cubes of 5 mm length were extracted from each of the previously mentioned cylinders; this length has been previously considered appropriate to capture the features of trabecular bone ^{23, 26, 35}.

Figure 1 shows the geometry of these specimens and Table 1 shows their morphological indices. The Mean Intercept Length (MIL) fabric tensor ³⁶ was evaluated using BoneJ ³⁷ and then used to align the coordinate axes of the images with the fabric. This approach has been recently employed by Wolfram, Gross ²² and Levrero-Florencio, Margetts ²⁹. After the 5 mm cubes were cropped, the alignment was rechecked to ensure that no misalignment larger than 8° was found ^{22, 23, 29}. MIL is known to approximate the macroscopic elastic orthotropy of trabecular bone ⁴ and thus the samples can be considered to be aligned with these axes.

[insert Figure 1.]

Figure 1. The three used specimens ordered in increasing density from left to right.

Table 1. Morphological indices of the three used specimens.

	Porous sample	Medium sample	Dense sample
BV/TV (%)	14.8	23.1	30.3
Degree of Anisotropy	2.65	2.09	2.67
Structure model index	1.59	0.98	0.52
Trabecular thickness (μm)	221.8	183.6	175.3
Connectivity	209	813	1059

Constitutive models

The solid phase was assumed to be a homogeneous isotropic elastoplastic material, although it is recognised that bone at the tissue level is actually transverse isotropic or orthotropic⁷⁻⁹ and heterogeneous^{38, 39}. However, as Cowin¹⁰ pointed out, there is little to no error in assuming tissue isotropy. This is because trabecula are composed of laminated material about their axes, which implies anisotropy, as in lack of isotropy; but since the axis of a trabecula is the same as its loading axis, a beam made of orthotropic material can be reduced to a beam made of isotropic material. Further, it has been argued that the solid phase of bone is not homogeneous; Renders, Mulder³⁹ found a decrease of 21% in apparent stiffness when considering a heterogeneous solid phase. Since we wanted to be able to validate our results with previously published data, we kept our solid phase properties as homogeneous^{22, 23}. Moreover, since the aim of this study was to compare two different constitutive models, this assumption of solid phase homogeneity was not expected to change trends.

The notation used in this section follows the notation used by Schwiedrzik, Wolfram⁴⁰ and Levrero-Florencio, Margetts²⁹. The elastic regime of the solid phase was modelled by using a Hencky's

hyperelastic model, with a Poisson ratio of 0.3 and a Young's Modulus of 12700 MPa²². A quadric yield surface⁴⁰ is given by

$$\mathbb{G}(\boldsymbol{\tau}) = \sqrt{\boldsymbol{\tau} : \mathbb{G} : \boldsymbol{\tau}} + \mathbf{G} : \boldsymbol{\tau} - 1 = 0 \quad (1)$$

where $\boldsymbol{\tau}$ is the Kirchhoff stress, $\mathbb{G}$ and $\mathbf{G}$ are, respectively, a fourth-order tensor and a second-order tensor defined by

$$\mathbb{G} = -\zeta_0 G_0^2 (\mathbf{I} \otimes \mathbf{I}) + (\zeta_0 + 1) G_0^2 (\mathbf{I} \bar{\otimes} \mathbf{I}) \quad (2)$$

and

$$\mathbf{G} = \frac{1}{2} \left(\frac{1}{\sigma_0^+} - \frac{1}{\sigma_0^-} \right) \mathbf{I} \quad (3)$$

where

$$G_0 = \frac{\sigma_0^+ + \sigma_0^-}{2\sigma_0^+\sigma_0^-} \quad (4)$$

$\mathbf{I}$ is the second-order unit tensor, σ_0^+ and σ_0^- are the tensile and compressive yield stresses, respectively, and ζ_0 is a parameter which defines the general shape of the surface.

Equation 1 approximates the DP criterion when $\zeta_0=0.49$ (Figure 2(a)) and we chose an arbitrary $\zeta_0=0.2$, which defines an EE (Figure 2(b)); both yield surfaces are defined in stress space and have the same uniaxial yield values. Uniaxial yield strains of 0.41% in tension and 0.83% in compression⁴¹ were converted to yield stresses by using the approach described in Schwiedrzik, Gross⁴². We assumed a linear hardening of 5% of the elastic slope^{22, 41, 43}. In order to ensure global convergence of the plasticity update Newton-CPPM scheme, a line search procedure as in the primal-CPPM algorithm described in Perez-Foguet and Armero⁴⁴ was implemented.

[insert Figure 2.]

Figure 2. (a) Approximated Drucker-Prager. (b) Eccentric-Ellipsoid. Both of these surfaces are defined in a six-dimensional stress space, but their shapes can be illustrated in principal stress space as shown.

Computational methods

The three cubic specimens were meshed with a voxelised mesh by using trilinear hexahedra, with the largest mesh having around nine million nodes. The applied boundary conditions used to constrain the cubic volume elements (VE) were kinematic uniform boundary conditions, as described by Wang, Feng⁴⁵. These boundary conditions provide an upper bound for trabecular bone stiffness⁴⁵ and also for yield²¹.

Each VE was subjected to 144 strain load cases, which is a slightly reduced number from Levrero-Florencio, Margetts ²⁹, as listed in Table 2.

Table 2. Description of the load cases undertaken. Clockwise and counter-clockwise shear are differentiated by the sign of the off-diagonal terms of the macroscopic strain. Biaxial normal-shear have normal to shear ratios of 1 to 1, 0.25 to 0.75 and 0.75 to 0.25. Epsilon stands for normal strain and gamma stands for shear strain.

Type of analysis		Number of analyses
Uniaxial normal $\varepsilon_{ii} \neq 0$ $\varepsilon_{jj} = \varepsilon_{kk} = 0$ $\gamma_{lm} = \gamma_{ln} = \gamma_{mn} = 0$	3 tensile and 3 compressive	6
Biaxial normal $\varepsilon_{ii} = \varepsilon_{jj} \neq 0$ $\varepsilon_{kk} = 0$ $\gamma_{lm} = \gamma_{ln} = \gamma_{mn} = 0$	3 planes, 1 analysis per quadrant	12
Uniaxial shear $\varepsilon_{ii} = \varepsilon_{jj} = \varepsilon_{kk} = 0$ $\gamma_{lm} \neq 0$ $\gamma_{ln} = \gamma_{mn} = 0$	3 clockwise and 3 counter-clockwise	6
Biaxial shear $\varepsilon_{ii} = \varepsilon_{jj} = \varepsilon_{kk} = 0$ $\gamma_{lm} = \gamma_{ln} \neq 0$ $\gamma_{mn} = 0$	3 planes, 1 analysis per quadrant	12
Biaxial normal-shear $\varepsilon_{ii} \neq 0$ $\varepsilon_{jj} = \varepsilon_{kk} = 0$ $\gamma_{lm} \neq 0$ $\gamma_{ln} = \gamma_{mn} = 0$	9 planes, 3 analysis per quadrant	108
$\forall i, j, k, l, m, n = 1, 2, 3$ $\forall i \neq j \neq k$ $\forall l \neq m \neq n$	Total	144

The simulations were performed on a Cray XC30, hosted by ARCHER (UK National Supercomputing Service). The FE analyses were carried out with an *in-house* developed parallel implicit finite strain solver, within the context of ParaFEM ^{46, 47}. This code uses Message Passing Interface (MPI) to perform the parallelisation ^{48, 49} and its scalability has already been shown in previous studies ^{50, 51}. To solve the

global FE system, a Newton-Raphson scheme was used as the solution tracking technique and a preconditioned conjugated gradient solver was used as the linear algebraic solver. The initial load increment size corresponded to 0.1% macroscopic strain norm and could decrease to a minimum of 0.001% if global convergence was not achieved. However, no convergence problems occurred in our simulations.

Macroscopic yield

Although a finite strain formulation needs to be taken into account when performing the simulations involving the microstructure, strains at the macroscopic level can be considered small due to their relatively small norms ^{5, 22, 23}, and thus a linear kinematic formulation can be used ⁵². The yield points were described in the plane where the abscissa is the Frobenius norm of the applied macroscopic strain and the ordinate is the Frobenius norm of the homogenised stress, described by

$$\boldsymbol{\sigma}_{\text{hom}} = \frac{1}{V_0} \sum_{i=1}^{\text{nel}} \sum_{j=1}^{\text{nip}} w_i \det \mathbf{J}_{ij} \boldsymbol{\sigma}_{ij} \quad (5)$$

where there is no summation implied on repeated indices, V_0 is the initial volume of the VE, nel is the number of elements in the FE system, nip is the number of Gauss integration points in a trilinear hexahedron, $\mathbf{J}$ is the Jacobian, $\boldsymbol{\sigma}$ is the stress at the solid phase, and w are the weights corresponding to the specific Gauss integration point. The 0.2% criterion was used to define the yield points ^{21, 22, 29}.

Results

The samples have been labelled as Low density, Medium density and High density for BV/TV of 14.8%, 23.1% and 30.3%, respectively. The macroscopic yield strains for the three samples considered for the uniaxial normal and biaxial normal cases (row 1 and 2 of Table 2) are shown in Figure 3. Further, since strain-based yield criteria have been previously shown to be approximately isotropic, we use yield points in strain space.

[insert Figure 3.]

Figure 3. Yield strains in normal-normal planes. The axes have been rearranged so that the orthotropic Young's Moduli are descending ($E_{11} > E_{22} > E_{33}$).

In normal-normal planes it can be seen that differences between yield strains when considering these two different yield surfaces for the solid phase are not significant in tension-tension quadrants (Figure 3(a) to (c), upper right quadrant), or even in tension-compression quadrants (Figure 3(a) to (c), upper left and lower right quadrants). However, they become distinguishable in compression-compression quadrants (Figure 3(a) to (c), lower left quadrants).

The macroscopic yield strains for the three samples considered in uniaxial and biaxial shear cases (row 3 and 4 of Table 2) are shown in Figure 4 (a) to (c). It can be seen that there are no significant differences in the macroscopic shear yield strains when using these two different yield criteria for the solid phase.

[insert Figure 4.]

Figure 4. Yield strains in shear-shear planes.

Yield strain norms were evaluated separately for load cases with only: normal compressive components; normal tensile components; and shear components, for both material models and all three samples. These

are shown in Figure 5. It can be seen that the yield strain norm for tension-only and shear-only load cases is almost the same, but differs by around 13% for compression-only load cases.

[insert Figure 5.]

Figure 5. Bar plot showing the average of the macroscopic yield strain norm for load cases that contain only: compressive components, tensile components, and shear components, for both EE and DP. The error bars are the SD of the macroscopic yield strain norms.

Macroscopic yield strains in normal-shear planes are shown in Figure 6(a) to (i) (rows 5 and 6 of Table 2). This figure shows that these yield strains differ for load cases which have compressive components when considering these two different material properties, and this difference increases as the considered load case becomes more compression-dominated (i.e. the load case has a higher proportion of compression over shear) (Figure 7). Figure 7 shows that this effect is also more prominent for the higher density samples. This effect was also found to occur in normal-normal planes (Figure 3) (not illustrated here).

[insert Figure 6.]

Figure 6. Yield strains in normal-shear planes, with the normal component in the X-axis and the shear component in the Y-axis.

[insert Figure 7.]

Figure 7. Difference in macroscopic yield strain norm between DP and EE, for cases in normal-shear planes with a compressive component. The strain norm corresponding to DP is consistently higher. The first number in the proportion on the X-axis corresponds to the normal component, and the second to the shear component.

Discussion

Our study shows that the effect of hydrostatic yield in the solid phase constitutive model is significant for compression-dominated load cases and that this effect is larger for high density samples. Our findings agree with Baumann, Shi ³⁰ who only considered uniaxial unconfined compression and pure shear and consequently concluded that solid phase strength asymmetry dominates the macroscopic mechanical response.

Macroscopic yield strain results in normal-normal planes show that the effects of the two solid phase yield surfaces on the macroscopic behaviour is minimal except for cases containing only compressive components (Figure 3(a) to (c), lower left quadrants). When comparing the macroscopic yield strain norms for the two material models, it can be seen that DP results in a norm which is around 13% larger than when using EE (Figure 5). The highly aligned structure of trabecular bone is likely to partially reflect features of the solid phase yield surface, which in this case is a lack of hydrostatic compression yielding, resulting in an increase of the macroscopic yield strain norms in compression-dominated load cases. Figure 3 also shows that tension-dominated load cases are not affected by the different solid phase yield surfaces.

When considering shear load cases, it can be seen that there are no differences in macroscopic yield strains when using these two different solid phase yield criteria (Figure 4 and 5). This is consistent with Sanyal, Gupta ⁴³ in that tensile microscopic strains predominate in macroscopic shear loading, which results in these load cases being unaffected when using these different solid phase yield surfaces. However, it is important to point out that shear load cases in clockwise and counter-clockwise directions can have different yield strains, especially in low BV/TV samples, as has been shown previously ²⁹.

In normal-shear planes (Figure 6, upper and lower left quadrants), the macroscopic yield strains follow a similar pattern to those in normal-normal planes (Figure 3). Specifically, the two solid phase yield criteria

result in greater differences as the load case becomes more compression-dominated, which is shown graphically in Figure 7. This figure shows the difference in macroscopic yield strains between the DP and EE solid phase yield surfaces in the load cases which are pure shear, or compression-shear. This difference increases as the compression/shear proportion increases and also as density increases; this means that higher density samples, which are more continuum-like, demonstrate a greater difference between the two solid phase material properties, as these properties are more directly mirrored at the macroscale.

As mentioned earlier, to the best of our knowledge, only one previous study has assessed the effect of different solid phase yield criteria on the macroscopic yield strains³⁰. The load cases considered in this study were limited to unconfined compression and shear. As we consider a large number of complex load cases, our study could be considered as a possible extension of the above cited study. Although our material properties are different and the way of assessing macroscopic yield is different, it can be seen that our shear strains are not very dissimilar (our uniaxial shear strains in Figure 4 need to be scaled by $\sqrt{2}$ to be comparable to those in Baumann, Shi³⁰, because these are shown as tensorial components; compression strains cannot be compared because our uniaxial compression cases are confined and theirs are unconfined)

Our study has some limitations. Validation for all the macroscopic yield strains is not possible as these are very complex load cases which cannot be tested experimentally and samples tested once cannot be retested. There have been some attempts to perform complex load cases, such as multiaxial compression, on trabecular bone samples^{53, 54}. For our solid phase properties, we considered homogeneous tissue properties, which may result in an overestimation of the macroscopic yield values^{38, 39}; but the effects are likely to be similar for both the solid phase models. We also assumed that the solid phase can be modelled with plasticity, which may not be true as localised tissue strains can cause microcracks, possibly leading

to an eventual fracture; these are effects that plasticity models are not readily able to capture^{55, 56}.

Furthermore, although our meshes were extremely detailed, and thus these simulations were computationally expensive, we only considered three samples, which, it can be argued, may not deliver statistically conclusive results.

This study provides a comprehensive understanding of how the yield surface at the microscopic level affects the homogenised yield strains at the macroscopic level. Yield strain of high density samples is affected more by the choice of the solid phase criteria. The strain norms associated to the use of DP, which has no yielding in hydrostatic compression, were found to be consistently higher than when using EE for compression-dominated load cases; a difference of up to 20% in some cases. It can be argued that most physiological activities result in compression-dominated loading states in trabecular bone; consequently the choice of the solid phase criterion is of great importance in the development of macroscopic yield criterion.

Acknowledgements

The authors would like to thank EPSRC for providing access to ARCHER, UK National Supercomputing Service, through project e398, “Modelling nonlinear micromechanical behaviour of bone”. We also would like to acknowledge The Hartree Centre, Science and Technology Facilities Council for access to Blue Joule through project HCP010. Additionally, the first author is grateful for the Principal’s Career Development PhD Scholarship of the University of Edinburgh.

Funding acknowledgements

This work was supported by the Engineering and Physical Sciences Research Council [grant number EP/K036939/1]; and the Biotechnology and Biological Sciences Research Council [grant number BB/K006029/1].

Conflict of interests

The authors declare that there is no conflict of interest.

References

1. Pankaj P. Patient-specific modelling of bone and bone-implant systems: the challenges. *Int J Numer Meth Bio*. 2013; 29: 233-49.
2. Cowin SC. Fabric Dependence of an Anisotropic Strength Criterion. *Mech Mater*. 1986; 5: 251-60.
3. Turner CH, Cowin SC, Rho JY, Ashman RB and Rice JC. The Fabric Dependence of the Orthotropic Elastic-Constants of Cancellous Bone. *J Biomech*. 1990; 23: 549-61.
4. Odgaard A. Three-dimensional methods for quantification of cancellous bone architecture. *Bone*. 1997; 20: 315-28.
5. Bayraktar HH, Gupta A, Kwon RY, Papadopoulos P and Keaveny TM. The modified super-ellipsoid yield criterion for human trabecular bone. *J Biomech Eng-T Asme*. 2004; 126: 677-84.
6. Verhulst E, Van Rietbergen B, Muller R and Huiskes R. Micro-finite element simulation of trabecular-bone post-yield behaviour - effects of material model, element size and type. *Comput Method Biomech*. 2008; 11: 389-95.
7. Hellmich C, Ulm FJ and Dormieux L. Can the diverse elastic properties of trabecular and cortical bone be attributed to only a few tissue-independent phase properties and their interactions? Arguments from a multiscale approach. *Biomech Model Mechan*. 2004; 2: 219-38.
8. Malandrino A, Fritsch A, Lahayne O, et al. Anisotropic tissue elasticity in human lumbar vertebra, by means of a coupled ultrasound-micromechanics approach. *Mater Lett*. 2012; 78: 154-8.
9. Wolfram U, Wilke HJ and Zysset PK. Rehydration of vertebral trabecular bone: Influences on its anisotropy, its stiffness and the indentation work with a view to age, gender and vertebral level. *Bone*. 2010; 46: 348-54.
10. Cowin SC. Remarks on the paper entitled 'Fabric and elastic principal directions of cancellous bone are closely related'. *J Biomech*. 1997; 30: 1191-2.
11. van Rietbergen B, Odgaard A, Kabel J and Huiskes R. Direct mechanics assessment of elastic symmetries and properties of trabecular bone architecture. *J Biomech*. 1996; 29: 1653-7.
12. Donaldson FE, Pankaj P, Cooper DML, Thomas CDL, Clement JG and Simpson AHRW. Relating age and micro-architecture with apparent-level elastic constants: a micro-finite element study of female cortical bone from the anterior femoral midshaft. *P I Mech Eng H*. 2011; 225: 585-96.
13. Bevil G, Eswaran SK, Gupta A, Papadopoulos P and Keaveny TM. Influence of bone volume fraction and architecture on computed large-deformation failure mechanisms in human trabecular bone. *Bone*. 2006; 39: 1218-25.
14. Morgan EF, Bayraktar HH, Yeh OC, Majumdar S, Burghardt A and Keaveny TM. Contribution of inter-site variations in architecture to trabecular bone apparent yield strains. *J Biomech*. 2004; 37: 1413-20.
15. Stolken JS and Kinney JH. On the importance of geometric nonlinearity in finite-element simulations of trabecular bone failure. *Bone*. 2003; 33: 494-504.
16. Smith CI, Faraldos M and Fernandez-Jalvo Y. The precision of porosity measurements: Effects of sample pre-treatment on porosity measurements of modern and archaeological bone. *Palaeogeogr Palaeoclimatol*. 2008; 266: 175-82.

17. Tai K, Ulm FJ and Ortiz C. Nanogranular origins of the strength of bone. *Nano Lett.* 2006; 6: 2520-5.
18. Carnelli D, Gastaldi D, Sassi V, Contro R, Ortiz C and Vena P. A Finite Element Model for Direction-Dependent Mechanical Response to Nanoindentation of Cortical Bone Allowing for Anisotropic Post-Yield Behavior of the Tissue. *J Biomech Eng-T Asme.* 2010; 132.
19. Maghous S, Dormieux L and Barthelemy JF. Micromechanical approach to the strength properties of frictional geomaterials. *Eur J Mech a-Solid.* 2009; 28: 179-88.
20. Schwiedrzik JJ and Zysset PK. An anisotropic elastic-viscoplastic damage model for bone tissue. *Biomech Model Mechan.* 2013; 12: 201-13.
21. Panyasantisuk J, Pahr DH and Zysset PK. Effect of boundary conditions on yield properties of human femoral trabecular bone. *Biomech Model Mechanobiol.* 2015.
22. Wolfram U, Gross T, Pahr DH, Schwiedrzik J, Wilke HJ and Zysset PK. Fabric-based Tsai-Wu yield criteria for vertebral trabecular bone in stress and strain space. *J Mech Behav Biomed.* 2012; 15: 218-28.
23. Sanyal A, Scheffelin J and Keaveny TM. The Quartic Piecewise-Linear Criterion for the Multiaxial Yield Behavior of Human Trabecular Bone. *J Biomech Eng-T Asme.* 2015; 137.
24. Schwiedrzik J, Raghavan R, Burki A, et al. In situ micropillar compression reveals superior strength and ductility but an absence of damage in lamellar bone. *Nat Mater.* 2014; 13: 740-7.
25. Luczynski KW, Steiger-Thirsfeld A, Bernardi J, Eberhardsteiner J and Hellmich C. Extracellular bone matrix exhibits hardening elastoplasticity and more than double cortical strength: Evidence from homogeneous compression of non-tapered single micron-sized pillars welded to a rigid substrate. *J Mech Behav Biomed Mater.* 2015; 52: 51-62.
26. van Rietbergen B, Weinans H, Huiskes R and Odgaard A. A New Method to Determine Trabecular Bone Elastic Properties and Loading Using Micromechanical Finite-Element Models. *J Biomech.* 1995; 28: 69-81.
27. Zysset PK. A review of morphology-elasticity relationships in human trabecular bone: theories and experiments. *J Biomech.* 2003; 36: 1469-85.
28. Cowin SC. The Relationship between the Elasticity Tensor and the Fabric Tensor. *Mech Mater.* 1985; 4: 137-47.
29. Levrero-Florencio F, Margetts L, Sales E, Xie S, Manda K and Pankaj P. Evaluating the macroscopic yield behaviour of trabecular bone using a nonlinear homogenisation approach. *J Mech Behav Biomed Mater.* 2016; 61: 384-96.
30. Baumann AP, Shi XT, Roeder RK and Niebur GL. The sensitivity of nonlinear computational models of trabecular bone to tissue level constitutive model. *Comput Method Biomec.* 2016; 19: 465-73.
31. Kruch S and Chaboche JL. Multi-scale analysis in elasto-viscoplasticity coupled with damage. *Int J Plasticity.* 2011; 27: 2026-39.
32. McDowell DL. A perspective on trends in multiscale plasticity. *Int J Plasticity.* 2010; 26: 1280-309.
33. de Souza Neto EA, Blanco PJ, Sanchez PJ and Feijoo RA. An RVE-based multiscale theory of solids with micro-scale inertia and body force effects. *Mech Mater.* 2015; 80: 136-44.
34. Gomez W, Sales E, Lopes RT and Pereira WCA. A comparative study of automatic thresholding approaches for 3D x-ray microtomography of trabecular bone. *Med Phys.* 2013; 40.

35. Harrigan TP, Jasty M, Mann RW and Harris WH. Limitations of the Continuum Assumption in Cancellous Bone. *J Biomech.* 1988; 21: 269-75.
36. Harrigan TP and Mann RW. Characterization of Microstructural Anisotropy in Orthotropic Materials Using a 2nd Rank Tensor. *J Mater Sci.* 1984; 19: 761-7.
37. Doube M, Klosowski MM, Arganda-Carreras I, et al. BoneJ Free and extensible bone image analysis in ImageJ. *Bone.* 2010; 47: 1076-9.
38. Blanchard R, Dejaco A, Bongaers E and Hellmich C. Intravoxel bone micromechanics for microCT-based finite element simulations. *J Biomech.* 2013; 46: 2710-21.
39. Renders GAP, Mulder L, Langenbach GEJ, van Ruijven LJ and van Eijden TMGJ. Biomechanical effect of mineral heterogeneity in trabecular bone. *J Biomech.* 2008; 41: 2793-8.
40. Schwiedrzik JJ, Wolfram U and Zysset PK. A generalized anisotropic quadric yield criterion and its application to bone tissue at multiple length scales. *Biomech Model Mechan.* 2013; 12: 1155-68.
41. Bayraktar HH and Keaveny TM. Mechanisms of uniformity of yield strains for trabecular bone. *J Biomech.* 2004; 37: 1671-8.
42. Schwiedrzik J, Gross T, Bina M, Pretterklieber M, Zysset P and Pahr D. Experimental validation of a nonlinear muFE model based on cohesive-frictional plasticity for trabecular bone. *Int J Numer Method Biomed Eng.* 2015.
43. Sanyal A, Gupta A, Bayraktar HH, Kwon RY and Keaveny TM. Shear strength behavior of human trabecular bone. *J Biomech.* 2012; 45: 2513-9.
44. Perez-Foguet A and Armero F. On the formulation of closest-point projection algorithms in elastoplasticity - part II: Globally convergent schemes. *Int J Numer Meth Eng.* 2002; 53: 331-74.
45. Wang CY, Feng L and Jasiuk I. Scale and Boundary Conditions Effects on the Apparent Elastic Moduli of Trabecular Bone Modeled as a Periodic Cellular Solid. *J Biomech Eng-T Asme.* 2009; 131.
46. Margetts L. Parallel finite element analysis. PhD thesis, University of Manchester. 2002.
47. Smith IM, Griffiths DV and Margetts L. Programming the finite element method. 5th ed. Chichester, West Sussex: Wiley, 2014.
48. Smith IM and Margetts L. Portable parallel processing for nonlinear problems. *International Conference on Computational Plasticity.* Barcelona, Spain 2003.
49. Smith IM and Margetts L. The convergence variability of parallel iterative solvers. *Eng Computation.* 2006; 23: 154-65.
50. Levrero Florencio F, Margetts L, Manda K and Pankaj P. Massively parallel simulations of the nonlinear mechanical behaviour of trabecular bone. *Congress of the European Society of Biomechanics.* Prague, Czech Republic 2015.
51. Margetts L, Arregui JD, Mummery PM, et al. Recent Progress in the Massively Parallel Solution of Implicit Problems. *Proceedings of the NAFEMS World Congress.* San Diego, USA 2015.
52. de Souza Neto EA, Peric D and Owens D. *Computational methods for plasticity : theory and applications.* 1st ed. Chichester, West Sussex, UK: Wiley, 2008, p.xix, 791 p.
53. Keaveny TM, Wachtel EF, Zadesky SP and Arramon YP. Application of the Tsai-Wu quadratic multiaxial failure criterion to bovine trabecular bone. *J Biomech Eng-T Asme.* 1999; 121: 99-107.

54. Rincon-Kohli L and Zysset PK. Multi-axial mechanical properties of human trabecular bone. *Biomech Model Mechan*. 2009; 8: 195-208.
55. Nawathe S, Juillard F and Keaveny TM. Theoretical bounds for the influence of tissue-level ductility on the apparent-level strength of human trabecular bone. *J Biomech*. 2013; 46: 1293-9.
56. Yeh OC and Keaveny TM. Relative roles of microdamage and microfracture in the mechanical behavior of trabecular bone. *J Orthop Res*. 2001; 19: 1001-7.

Notation

$\mathbf{A}$	A second-order tensor
$\mathbb{A}$	A fourth-order tensor
$\boldsymbol{\sigma}$	Infinitesimal stress tensor
$\boldsymbol{\tau}$	Kirchhoff stress tensor
$\mathbf{A}:\mathbf{B}$	$A_{ij}B_{ij}$ in indicial notation
$\mathbb{A}:\mathbf{B}$	$A_{ijkl}B_{kl}$ in indicial notation
$\mathbf{A}\otimes\mathbf{B}$	$A_{ij}B_{kl}$ in indicial notation
$\overline{\mathbf{A}\otimes\mathbf{B}}$	$\frac{1}{2}[A_{ik}B_{jl} + A_{il}B_{jk}]$ in indicial notation
$\mathbf{B}:\mathbb{A}$	$B_{ij}A_{ijkl}$ in indicial notation

Abbreviations

BV/TV	Bone Volume over Total Volume
DP	Drucker-Prager yield criterion
EE	Eccentric-ellipsoid yield criterion
MIL	Mean Intercept Length
MPI	Message Passing Interface
Newton-CPPM	Newton Closest Point Projection Method
VE	Volume Element
μ CT	Micro computed tomography