THE UNIVERSITY *of* EDINBURGH

Edinburgh Research Explorer

Exploiting multimetallic catalysts to access polymer materials from CO₂

Citation for published version:

Garden, JA 2017, 'Exploiting multimetallic catalysts to access polymer materials from CO₂', *Green Materials*, pp. 1-6. <https://doi.org/10.1680/jgrma.16.00022>

Digital Object Identifier (DOI):

[10.1680/jgrma.16.00022](https://doi.org/10.1680/jgrma.16.00022)

Link:

[Link to publication record in Edinburgh Research Explorer](#)

Document Version:

Peer reviewed version

Published In:

Green Materials

General rights

Copyright for the publications made accessible via the Edinburgh Research Explorer is retained by the author(s) and / or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

The University of Edinburgh has made every reasonable effort to ensure that Edinburgh Research Explorer content complies with UK legislation. If you believe that the public display of this file breaches copyright please contact openaccess@ed.ac.uk providing details, and we will remove access to the work immediately and investigate your claim.

Exploiting Multimetallic Catalysts to Access Polymer Materials from CO₂

Jennifer A. Garden*

Christina Miller Research Fellow, University of Edinburgh, Edinburgh, UK

Polycarbonates and polyurethanes derived from CO₂ have the potential to consume a greenhouse gas and convert it into value added polymer products. To be commercially viable, these processes are dependent on the development of highly efficient polymerization catalysts, which are often multimetallic. One emerging method to improve catalyst efficiency is through the design of co-operative, mixed-metal catalysts. Such heterometallic, homogenous catalysts have shown significantly improved performance metrics for CO₂/epoxide ring-opening copolymerization, in comparison to their homometallic analogues. This perspective highlights the recently realized reactivity enhancements achieved using multimetallic catalysts, along with the material properties and scope of CO₂-derived polymers.

1. Introduction

Reforming the current plastics industry to incorporate renewable resources, reduce our reliance on petrochemical feedstocks and diminish our impact on the environment presents a major challenge for the immediate future. Although this is a significant task, progress has already been achieved with some commercial polymer materials now produced either partially or wholly from renewable sources.¹ One of the best-established commercial examples is bio-degradable polylactic acid, produced through the ring-opening polymerization (ROP) of bioderived lactide. Another particularly promising strategy is the ring-opening copolymerization (ROCOP) of CO₂ and epoxides, to form polycarbonates (Scheme 1). In today's climate, the use of CO₂ as an alternative C1 feedstock is rapidly gathering attention, as CO₂ is abundant, cheap, non-toxic and a waste product from many industrial processes. The CO₂/epoxide ROCOP process is currently on the brink of commercialization, and the resultant telechelic polycarbonates can subsequently be used to synthesize polyurethanes, through reaction with a diisocyanate (Scheme 1). Polyurethane materials have many applications, including construction materials, high performance coatings and furniture.² Assessment of the life cycle analysis of polyurethane materials shows that incorporating 20% of CO₂ content can reduce the overall greenhouse gas emissions of the polymer synthesis by up to 19%.³

Scheme 1. Synthesis of polycarbonates and polyurethanes from CO₂/epoxide ring-opening copolymerization.

The commercial success of producing sustainable polymer materials is crucially dependent on a suitable and efficient catalyst system; some of the most active are multimetallic complexes. The emerging theme of mixed-metal (heterometallic) cooperativity is an attractive means to improve catalyst activity and selectivity.⁴ This concept is particularly appealing, from both an economic and environmental perspective, when the metals involved are abundant, low-toxicity main-group and first-row transition metals. When two different metals are held in close proximity within a molecular environment, cooperative effects are often observed, which can give unusual and sometimes unexpected reactivities that cannot be accessed using either homometallic component in isolation.⁴⁻¹⁰ Elegant homogeneous heterometallic catalysts have been designed for a range of polymerizations, which outperform their homometallic analogues in terms of activity and selectivity (Figure 1).¹¹⁻²¹ However, until recently, heterometallic ROCOP catalyst development was lagging behind that of olefin polymerization and the ROP of lactones.

Figure 1. Polymer materials accessed using high efficiency heterometallic catalysts.

2. Advances in Multimetallic Catalyst Development for CO₂/epoxide ROCOP

The presence of a catalyst underpins the successful synthesis of polycarbonates from CO₂/epoxide ROCOP, where some of the most active are homogeneous homometallic metal complexes based on salen,²² porphyrin,²³ β -diiminate²⁴ or di-phenolate²⁵ ligand scaffolds.²⁶⁻²⁹ Careful homogeneous catalyst design has led to improved activities and selectivities, along with high CO₂ uptake (>99%) to form nearly perfect polycarbonate linkages. A breakthrough in the mechanistic understanding came from the realization that epoxide opening and enchainment could occur through a bimetallic mechanism, as discerned using dimeric β -diiminate zinc acetate catalysts bearing two zinc centres in close proximity.³⁰ This finding inspired the development of multimetallic catalysts comprising two metals in a dinucleating ligand scaffold,³¹⁻³⁴ which have shown exceptional activities^{24, 35} and some of which are active at just 1 bar of CO₂ pressure.³⁶⁻³⁹ However, until recently, the development of homogeneous heterometallic catalysts has been neglected, despite reports that ternary mixed-metal systems display cooperative heterometallic effects, and have demonstrated good activities for CO₂/epoxide ROCOP.⁴⁰⁻⁴⁸ A major contributor to this lack of investigation is the synthetic challenge associated with the synthesis and characterization of heterometallic catalysts, which often includes the synthesis, purification and manipulation of highly air- and moisture-sensitive starting materials.

Detailed kinetic and mechanistic studies based on a multimetallic catalyst, supported by a macrocyclic ligand scaffold (Scheme 2, RHS, **1**), have indicated that the polymerization occurs through a “chain shuttling” mechanism, where the growing polymer chain switches between two metal centres (Scheme 2, LHS).⁴⁹ These insights suggested that the two metal centres play different roles in the propagation. Whilst one metal binds the epoxide, to position it in close proximity and activate it towards nucleophilic attack, it is the second metal carbonate bond which ring opens the epoxide to propagate the polymerization. These studies hinted that a heterometallic catalyst could exhibit even greater activity than the homometallic systems. This hypothesis was further supported by preliminary experimental studies, where a mixed catalyst system comprising di-Mg, di-Zn and MgZn acetate complexes (Scheme 2, **3**), gave double the activity of a 1:1 mixture of the di-Zn (Scheme 2, **1**) and di-Mg (Scheme 2, **2**) acetate catalyst systems.⁵⁰

In 2015, a pure, homogeneous, heterometallic MgZn catalyst was reported (Scheme 2, **4**).¹⁸ The preparation of this complex presents a significant synthetic challenge: to incorporate two labile metals of similar properties within a symmetrical ligand scaffold, whilst avoiding redistribution of the two metal centres to form the homometallic analogues (**5** and **6**). This heterometallic catalyst gave efficient, well-controlled polymerizations, with TOF

values of 624 h⁻¹ achieved at 120 °C and 50 bar of CO₂ pressure. Heterometallic **4** showed significantly improved performance metrics for CO₂/cyclohexene oxide (CHO) ROCOP, in comparison to the homometallic analogues, either alone or in combination. Notably, **4** is active at atmospheric pressure, and the productivities (turnover numbers, TON = 344) and activities (turnover frequencies, TOF = 34 h⁻¹) are five times higher than a 1:1 mixture of the homometallic di-Mg and di-Zn analogues.

Scheme 2. “Chain shuttling” mechanism proposed for CO₂/epoxide copolymerization by a multimetallic catalyst.^{49,50}

The concept of heterometallic reactivity enhancement has since been extended to homogeneous rare-earth metal complexes. Rare-earth metal catalysts are attractive for CO₂/epoxide ROCOP, as the oxyphilic and Lewis acidic nature of rare-earth metals can facilitate epoxide activation and CO₂ insertion. Yao *et al.* recently reported the synthesis of two novel heterometallic catalysts for CO₂/CHO ROCOP, based on Nd₂Zn and Y₂Zn complexes supported by di-phenolate ligands.⁵¹ These novel complexes display high catalyst activities with TOF values up to 267 h⁻¹ at 70 °C and 0.7 MPa. Furthermore, these systems give impressive, albeit lowered, catalyst activities at ambient temperature (TOF = 82 h⁻¹, 25 °C, 7 bar of CO₂ pressure). These heterometallic catalysts were successfully applied to synthesize high molecular weight poly(cyclohexene carbonate) (M_n = 296 kg mol⁻¹). In contrast, the homometallic analogues are completely inactive towards CO₂/CHO ROCOP. These recent studies highlight how heterometallic systems can offer new potential within ROCOP, and provide an interesting direction for future catalyst exploration.

3. CO₂-derived Polycarbonates and their Material Properties

The ROCOP of CO₂/epoxides is an attractive route to synthesize polycarbonates which can contain up to 50% CO₂ by mass. The synthesis of CO₂-derived polycarbonates is considered to be safer than that of conventional polycarbonate materials, which are often produced through the condensation polymerization of bisphenol-A (BPA) with phosgene, which is a highly toxic nerve gas.⁵² It is worth noting that an alternative route, based on a melt process using BPA and diphenyl carbonate, is also applied industrially.⁵³ However, it is important to note that the material properties of

CO₂-derived polycarbonates differ from conventional polycarbonates. The amorphous polymers derived from BPA/phosgene copolymerization display high impact strength, heat resistance, toughness and transparency, and are used in a range of applications including medical, optical and electronic devices.⁵⁴ CO₂-derived polycarbonates give markedly different material properties, which vary according to the molecular weight and the epoxide co-monomer selected.

Within academic research, CHO is often selected as the benchmark epoxide for catalyst development, on account of its lower toxicity and ease of handling compared to other epoxides. Characterization studies of high molecular weight poly(cyclohexene carbonate) (PCHC) with a broad distribution ($M_w = 252 \text{ kg mol}^{-1}$, $\bar{D} = 6$) have revealed it to be a brittle material, which displayed an elongation at break of just 1-2% and a T_g value of 115 °C.⁵⁵ Industrial interest has largely focused on CO₂/propylene oxide ROCOP, where the poly(propylene carbonate) products have environmental benefits, including biodegradability and benign decomposition emissions. Poly(propylene carbonate) materials are of high commercial relevance, thanks to their suitability for many applications including adhesives, coatings and binders.^{22, 56} However, the range of applications is limited by the low softening temperature of this material ($T_g = 40 \text{ °C}$). Studies of a homologous series of CO₂-derived polycarbonates have shown that poly(propylene carbonate), poly(pentene carbonate), poly(hexene carbonate), poly(octene carbonate) and poly(cyclohexene carbonate) are all amorphous materials, and display initial decomposition temperatures (T_d) under 300 °C, as determined using TGA and DSC analysis.⁵⁷ The T_d values increase in line with increasing hydrocarbon content of the polymer, with the exception of PCHC, which displays the highest initial decomposition temperature ($T_d = 290 \text{ °C}$) on account of the stiff cyclohexyl rings incorporated into the polymer chain.

To access completely bio-based poly(carbonates) from CO₂/epoxide ROCOP, additional research has focused on the use of renewable epoxides, such as limonene oxide⁵⁸ and 1,4-cyclohexadiene oxide.⁵⁹ Limonene oxide is derived from limonene, an alicyclic terpene which is annually produced on a scale exceeding 70, 000 tons from waste orange peel.⁶⁰ High molecular weight (>100 kg mol⁻¹) poly(limonene carbonate) has successfully been synthesized through CO₂/limonene oxide ROCOP, using a β -diiminate zinc acetate catalyst.⁵² This bio-based polycarbonate displayed attractive material properties, including excellent thermal resistance ($T_g = 130 \text{ °C}$), thermal stability (up to 240 °C), hardness and optical transparency. Indeed, recent advances have shown that post-polymerization modification of poly(limonene carbonate) can offer rigid polymers, with tunable T_g values up to 180 °C, as a potential

alternative to BPA-based polycarbonates.^{61, 62} An alternative renewable epoxide, 1,4-cyclohexadiene oxide, has been derived from the mono-epoxidation of cyclohexa-1,4-diene from fatty acid methyl esters found in plant oils.⁵⁹ Subsequent ROCOP with CO₂ produced renewable, unsaturated polycarbonates, with the same T_g value as the saturated analogue, PCHC ($T_g = 115 \text{ °C}$).

Through rapid recent advances in CO₂/epoxide ROCOP, a range of polycarbonate materials have been synthesized, with different material properties. To make these processes truly sustainable, the CO₂ source must be carefully considered. High energy compressions of CO₂ gas should be avoided, and the reaction system must be tolerant towards impurities found in industrial waste CO₂. Promising advances have recently been made in this area. The application of metal-organic frameworks (MOFs), to capture, store and release CO₂ into CO₂/epoxide ROCOPs, has been reported by Darensbourg *et al.* The commercially available MOF, HKUST-1 ([Cu₃(btc)₂(H₂O)₃], where btc = benzene-1,3,5-tricarboxylate), was used to capture CO₂ under aerobic conditions at atmospheric pressure.⁶³ The captured CO₂ was thermally released and directly copolymerized with propylene oxide or *cis*-2-butylene oxide, in the presence of a Co(III) salen catalyst, to form poly(propylene carbonate) or poly(butylene carbonate), respectively. Importantly, the polymer yields obtained and the material properties observed were near-equivalent, when the CO₂ source was the MOF filled under aerobic conditions, or a pressurized CO₂ cylinder in the absence of HKUST-1. Studies using CO₂ captured from a CCS demonstrator plant attached to a UK power station showed that a homogeneous di-Mg catalyst (Scheme 2, 2) could successfully catalyze CO₂/CHO ROCOP.³⁶ The catalyst performance was almost equivalent using this “impure” CO₂ source in comparison to “pure”, research grade CO₂. Further studies revealed that this catalyst system demonstrated a high level of tolerance towards added impurities which are often present in captured CO₂, including air, water, CO, N₂ and amines. These findings indicate that CO₂/epoxide ROCOP has real world potential to convert waste CO₂ to useful polymer materials. There is much scope to derivatize such polycarbonate materials, through reaction with diisocyanates to form polyurethanes,⁶⁴ “switch chemistry” to form block copolymers,^{65, 66} or post-polymerization derivatization of functional groups on the epoxide, such as olefins⁵⁹ or trimethoxysilane.⁶⁷

4. Conclusion

Whilst homogeneous heterometallic catalyst design for CO₂/epoxide ROCOP is still in its infancy, recent findings suggest that it has the potential to grow into a fruitful area of high activity catalyst development. Not only have enhanced activities been reported using cooperative heterometallic catalysts but good

activities have been achieved under atmospheric pressure and ambient temperature reaction conditions. Thanks to efforts across a range of fields, including catalyst design, engineering and materials, CO₂-derived polymers synthesized through CO₂/epoxide ROCOP are now on the edge of commercialization.

This process provides an exciting opportunity to expand and exploit multimetallic catalyst development for a range of CO₂-derived materials in the immediate future, to contribute to a more sustainable world.

Acknowledgements J. A. Garden gratefully acknowledges the University of Edinburgh for funding (Christina Miller Research Fellowship).

References

- Zhu Y, Romain C and Williams CK (2016), Sustainable polymers from renewable resources. *Nature* **540**(7633): 354-362.
- <http://www.covestro.de/en/projects-and-cooperations/co2-project>. Accessed 14/12/16.
- von der Assen N and Bardow A (2014), Life cycle assessment of polyols for polyurethane production using CO₂ as feedstock: insights from an industrial case study. *Green Chemistry* **16**(6): 3272-3280.
- Buchwalter P, Rosé J and Braunstein P (2015), Multimetallic catalysis based on heterometallic complexes and clusters. *Chemical Reviews* **115**(1): 28-126.
- Shibasaki M and Yoshikawa N (2002), Lanthanide complexes in multifunctional asymmetric catalysis. *Chemical Reviews* **102**(6): 2187-2210.
- Mulvey RE (2009), Avant-garde metalating agents: Structural basis of alkali-metal-mediated metalation. *Accounts of Chemical Research* **42**(6): 743-755.
- Haag B, Mosrin M, Ila H, Malakhov V and Knochel P (2011), Regio- and chemoselective metalation of arenes and heteroarenes using hindered metal amide bases. *Angewandte Chemie International Edition* **50**(42): 9794-9824.
- Mongin F and Harrison-Marchand A (2013), Mixed aggregate (MAA): A single concept for all dipolar organometallic aggregates. 2. Syntheses and reactivities of homo/heteroMAAs. *Chemical Reviews* **113**(10): 7563-7727.
- Harrison-Marchand A and Mongin F (2013), Mixed aggregate (MAA): A single concept for all dipolar organometallic aggregates. 1. Structural data. *Chemical Reviews* **113**(10): 7470-7562.
- Mulvey RE, Mongin F, Uchiyama M and Kondo Y (2007), Deprotonative metalation using ate compounds: Synergy, synthesis, and structure building. *Angewandte Chemie International Edition* **46**(21): 3802-3824.
- Delferro M and Marks TJ (2011), Multinuclear olefin polymerization catalysts. *Chemical Reviews* **111**(3): 2450-2485.
- McInnis JP, Delferro M and Marks TJ (2014), Multinuclear group 4 catalysis: Olefin polymerization pathways modified by strong metal-metal cooperative effects. *Accounts of Chemical Research* **47**(8): 2545-2557.
- Mandal SK and Roesky HW (2010), Assembling heterometals through oxygen: An efficient way to design homogeneous catalysts. *Accounts of Chemical Research* **43**(2): 248-259.
- Sarazin Y, Howard RH, Hughes DL, Humphrey SM and Bochmann M (2006), Titanium, zinc and alkaline-earth metal complexes supported by bulky *O,N,N,O*-multidentate ligands: syntheses, characterisation and activity in cyclic ester polymerisation *Dalton Transactions* **2**: 340-350.
- Gao A-H, Yao W, Mu Y, Gao W, Sun M-T and Su Q (2009), Heterobimetallic aluminium and zinc complex with *N*-arylanilido-imine ligand: Synthesis, structure and catalytic property for ring-opening polymerization of ϵ -caprolactone. *Polyhedron* **28**(13): 2605-2610.
- Sheng H-T, Li J-M, Zhang Y, Yao Y-M and Shen Q (2008), Synthesis and molecular structure of new heterometal alkoxide clusters $\text{Ln}_2\text{Na}_8(\text{OCH}_2\text{CF}_3)_{14}(\text{THF})_6$ (Ln = Sm, Y, Yb): Highly active catalysts for polymerization of ϵ -caprolactone and trimethylene carbonate. *Polyhedron* **27**(6): 1665-1672.
- Gurubasavaraj PM, Roesky HW, Nekoueishahraki B, Pal A and Herbst-Irmer R (2008), From unstable to stable: Half-metallocene catalysts for olefin polymerization. *Inorganic Chemistry* **47**(12): 5324-5331.
- Garden JA, Saini PK and Williams CK (2015), Greater than the sum of its parts: A heterodinuclear polymerization catalyst. *Journal of the American Chemical Society* **137**(48): 15078-15081.
- Hild F, Haquette P, Brelot L and Dagorne S (2010). *Dalton Trans.* **39**(2): 533-540.
- Wang L, Rosca S-C, Poirier V, Sinbandhit S, Dorcet V, Roisnel T, Carpentier J-F and Sarazin Y (2014), Stable divalent germanium, tin and lead amino(ether)-phenolate monomeric complexes: structural features, inclusion heterobimetallic complexes, and ROP catalysis. *Dalton Transactions* **43**(11): 4268-4286.
- Char J, Brulé E, Gros PC, Rager M-N, Guérineau V and Thomas CM (2015), Synthesis of heterotactic PLA from rac-lactide using hetero-bimetallic Mg/Zn-Li systems. *Journal of Organometallic Chemistry* **796**(47-52).
- Darensbourg DJ (2007), Making plastics from carbon dioxide: Salen metal complexes as catalysts for the production of polycarbonates from epoxides and CO₂. *Chemical Reviews* **107**(6): 2388-2410.
- Mang S, Cooper AI, Colclough ME, Chauhan N and Holmes AB (2000), Copolymerization of CO₂ and 1,2-cyclohexene oxide using a CO₂-soluble chromium porphyrin catalyst. *Macromolecules* **33**(2): 303-308.
- Lehenmeier MW, Kissling S, Altenbuchner PT, Bruckmeier C, Deglmann P, Brym A-K and Rieger B (2013), Flexibly tethered dinuclear zinc complexes: A solution to the entropy problem in CO₂/epoxide copolymerization catalysis? *Angewandte Chemie International Edition* **52**(37): 9821-9826.

25. Kember MR, Buchard A and Williams CK (2011), Catalysts for CO₂/epoxide copolymerisation *Chemical Communications* **47(1)**: 141-163.
26. Trott G, Saini PK and Williams CK (2016), Catalysts for CO₂/epoxide ring-opening copolymerization. *Philosophical Transactions of the Royal Society A: Mathematical, Physical and Engineering Sciences* **374(2061)**.
27. Childers MI, Longo JM, Van Zee NJ, LaPointe AM and Coates GW (2014), Stereoselective epoxide polymerization and copolymerization. *Chemical Reviews* **114(16)**: 8129-8152.
28. Darensbourg DJ and Holtcamp MW (1996), Catalysts for the reactions of epoxides and carbon dioxide. *Coordination Chemistry Reviews* **153(0)**: 155-174.
29. Lu X-B and Darensbourg DJ (2012), Cobalt catalysts for the coupling of CO₂ and epoxides to provide polycarbonates and cyclic carbonates. *Chemical Society Reviews* **41(4)**: 1462-1484.
30. Moore DR, Cheng M, Lobkovsky EB and Coates GW (2003), Mechanism of the alternating copolymerization of epoxides and CO₂ using β -diiminate zinc catalysts: Evidence for a bimetallic epoxide enchainment. *Journal of the American Chemical Society* **125(39)**: 11911-11924.
31. Lee BY, Kwon HY, Lee SY, Na SJ, Han S-I, Yun H, Lee H and Park Y-W (2005), Bimetallic anilido-aldimine zinc complexes for epoxide/CO₂ copolymerization. *Journal of the American Chemical Society* **127(9)**: 3031-3037.
32. Xiao Y, Wang Z and Ding K (2005), Copolymerization of cyclohexene oxide with CO₂ by using intramolecular dinuclear zinc catalysts. *Chemistry – A European Journal* **11(12)**: 3668-3678.
33. Piesik DFJ, Range S and Harder S (2008), Bimetallic calcium and zinc complexes with bridged β -diketiminato ligands: Investigations on epoxide/CO₂ copolymerization. *Organometallics* **27(23)**: 6178-6187.
34. Xiao Y, Wang Z and Ding K (2006), Intramolecularly dinuclear magnesium complex catalyzed copolymerization of cyclohexene oxide with CO₂ under ambient CO₂ pressure: Kinetics and mechanism. *Macromolecules* **39(1)**: 128-137.
35. Kissling S, Lehenmeier MW, Altenbuchner PT, Kronast A, Reiter M, Deglmann P, Seemann UB and Rieger B (2015), Dinuclear zinc catalysts with unprecedented activities for the copolymerization of cyclohexene oxide and CO₂. *Chemical Communications* **51(22)**: 4579-4582.
36. Chapman AM, Keyworth C, Kember MR, Lennox AJJ and Williams CK (2015), Adding value to power station captured CO₂: Tolerant Zn and Mg homogeneous catalysts for polycarbonate polyol production. *ACS Catalysis*: 1581-1588.
37. Kember MR, Knight PD, Reung PTR and Williams CK (2009), Highly active dizinc catalyst for the copolymerization of carbon dioxide and cyclohexene oxide at one atmosphere pressure. *Angewandte Chemie International Edition* **48(5)**: 931-933.
38. Kember MR, White AJP and Williams CK (2010), Highly active di- and trimetallic cobalt catalysts for the copolymerization of CHO and CO₂ at atmospheric pressure. *Macromolecules* **43(5)**: 2291-2298.
39. Buchard A, Kember MR, Sandeman KG and Williams CK (2011), A bimetallic iron(III) catalyst for CO₂/epoxide coupling *Chemical Communications* **47(1)**: 212-214.
40. Tan C-S and Hsu T-J (1997), Alternating copolymerization of carbon dioxide and propylene oxide with a rare-earth-metal coordination catalyst. *Macromolecules* **30(11)**: 3147-3150.
41. Chen X, Shen Z and Zhang Y (1991), New catalytic systems for the fixation of carbon dioxide. 1. Copolymerization of carbon dioxide and propylene oxide with new rare-earth catalysts-RE(P₂₀₄)₃-Al(*i*-Bu)₃-R(OH)_n. *Macromolecules* **24(19)**: 5305-5308.
42. Nikitinskii AV, Bochkarev LN, Khorshev SY and Bochkarev MN (2004), Synthesis of heterobimetallic lanthanide tert-butoxides and their catalytic properties in reactions of CO₂ with epoxides. *Russian Journal of General Chemistry* **74(8)**: 1197-1200.
43. Liu B, Zhao X, Wang X and Wang F (2001), Copolymerization of carbon dioxide and propylene oxide with Ln(CCl₃COO)₃-based catalyst: The role of rare-earth compound in the catalytic system. *Journal of Polymer Science Part A: Polymer Chemistry* **39(16)**: 2751-2754.
44. Hsu T-J and Tan C-S (2001), Synthesis of polyethercarbonate from carbon dioxide and cyclohexene oxide by yttrium-metal coordination catalyst. *Polymer* **42(12)**: 5143-5150.
45. Guo J-T, Wang X-Y, Xu Y-S and Sun J-W (2003), Copolymerizations of carbon dioxide and epoxides in the presence of rare earth coordinate catalyst. *Journal of Applied Polymer Science* **87(14)**: 2356-2359.
46. Quan Z, Wang X, Zhao X and Wang F (2003), Copolymerization of CO₂ and propylene oxide under rare earth ternary catalyst: design of ligand in yttrium complex. *Polymer* **44(19)**: 5605-5610.
47. Dong Y, Wang X, Zhao X and Wang F (2012), Facile synthesis of poly(ether carbonate)s via copolymerization of CO₂ and propylene oxide under combinatorial catalyst of rare earth ternary complex and double metal cyanide complex. *Journal of Polymer Science Part A: Polymer Chemistry* **50(2)**: 362-370.
48. Lu H, Qin Y, Wang X, Yang X, Zhang S and Wang F (2011), Copolymerization of carbon dioxide and propylene oxide under inorganic oxide supported rare earth ternary catalyst. *Journal of Polymer Science Part A: Polymer Chemistry* **49(17)**: 3797-3804.
49. Buchard A, Jutz F, Kember MR, White AJP, Rzepa HS and Williams CK (2012), Experimental and computational investigation of the mechanism of carbon dioxide/cyclohexene oxide copolymerization using a dizinc catalyst. *Macromolecules* **45(17)**: 6781-6795.
50. Saini PK, Romain C and Williams CK (2014), Dinuclear metal catalysts: improved performance of heterodinuclear mixed catalysts for CO₂-epoxide copolymerization *Chemical Communications* **50(32)**: 4164-4167.
51. Qin J, Xu B, Zhang Y, Yuan D and Yao YM (2016), Cooperative rare earth metal-zinc based heterometallic catalysts for copolymerization of CO₂ and cyclohexene oxide. *Green Chemistry* **18(15)**: 4270-4275.
52. Hauenstein O, Reiter M, Agarwal S, Rieger B and Greiner A (2016), Bio-based polycarbonate from limonene oxide and CO₂ with high molecular weight, excellent thermal resistance, hardness and transparency. *Green Chemistry* **18(3)**: 760-770.
53. Hucks U, Hallenberger K, Kratschmer S, Prein M and Kühling S, (2004) *Process for producing polycarbonate*. US Patent US6703473 B2
54. LeGrand DG and Bendler JT. *Handbook of Polycarbonate Science and Technology*: Marcel Dekker, Inc.; 2000.
55. Koning C, Wildeson J, Parton R, Plum B, Steeman P and Darensbourg DJ (2001), Synthesis and physical

-
- characterization of poly(cyclohexane carbonate), synthesized from CO₂ and cyclohexene oxide. *Polymer* **42**(9): 3995-4004.
56. <http://www.empowermaterials.com/>. Accessed 09/12/16.
57. Thorat SD, Phillips PJ, Semenov V and Gakh A (2003), Physical properties of aliphatic polycarbonates made from CO₂ and epoxides. *Journal of Applied Polymer Science* **89**(5): 1163-1176.
58. Byrne CM, Allen SD, Lobkovsky EB and Coates GW (2004), Alternating copolymerization of limonene oxide and carbon dioxide. *Journal of the American Chemical Society* **126**(37): 11404-11405.
59. Winkler M, Romain C, Meier MAR and Williams CK (2015), Renewable polycarbonates and polyesters from 1,4-cyclohexadiene. *Green Chemistry* **17**(1): 300-306.
60. Ciriminna R, Lomeli-Rodriguez M, Demma Cara P, Lopez-Sanchez JA and Pagliaro M (2014), Limonene: a versatile chemical of the bioeconomy. *Chemical Communications* **50**(97): 15288-15296.
61. Li C, Sablong RJ and Koning CE (2016), Chemoselective Alternating Copolymerization of Limonene Dioxide and Carbon Dioxide: A New Highly Functional Aliphatic Epoxy Polycarbonate. *Angewandte Chemie International Edition* **55**(38): 11572-11576.
62. Kindermann N, Cristòfol À and Kleij AW (2017), Access to Biorenewable Polycarbonates with Unusual Glass-Transition Temperature (T_g) Modulation. *ACS Catalysis* **7**(6): 3860-3863.
63. Darensbourg DJ, Chung W-C, Wang K and Zhou H-C (2014), Sequestering CO₂ for Short-Term Storage in MOFs: Copolymer Synthesis with Oxiranes. *ACS Catalysis* **4**(5): 1511-1515.
64. Cyriac A, Lee SH, Varghese JK, Park JH, Jeon JY, Kim SJ and Lee BY (2011), Preparation of flame-retarding poly(propylene carbonate). *Green Chemistry* **13**(12): 3469-3475.
65. Romain C and Williams CK (2014), Chemoselective polymerization control: From mixed-monomer feedstock to copolymers. *Angewandte Chemie International Edition* **53**(6): 1607-1610.
66. Paul S, Romain C, Shaw J and Williams CK (2015), Sequence selective polymerization catalysis: A new route to ABA block copoly(ester-b-carbonate-b-ester). *Macromolecules* **48**(17): 6047-6056.
67. Darensbourg DJ, Rodgers JL and Fang CC (2003), The copolymerization of carbon dioxide and [2-(3,4-epoxycyclohexyl)ethyl]trimethoxysilane catalyzed by (Salen)CrCl. Formation of a CO₂ soluble polycarbonate. *Inorganic Chemistry* **42**(15): 4498-4500.