

THE UNIVERSITY of EDINBURGH

Edinburgh Research Explorer

Seismic Retrofit Schemes with FRP for Deficient RC Beam-Column Joints

State-of-the-Art Review

Citation for published version:

Pohoryles, DA, Melo, J, Rossetto, T, Varum, H & Bisby, L 2019, 'Seismic Retrofit Schemes with FRP for Deficient RC Beam-Column Joints: State-of-the-Art Review', *Journal of Composites for Construction*, vol. 23, no. 4, 03119001. https://doi.org/10.1061/(ASCE)CC.1943-5614.0000950

Digital Object Identifier (DOI): 10.1061/(ASCE)CC.1943-5614.0000950

Link:

Link to publication record in Edinburgh Research Explorer

Document Version: Peer reviewed version

Published In: Journal of Composites for Construction

General rights

Copyright for the publications made accessible via the Edinburgh Research Explorer is retained by the author(s) and / or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

The University of Edinburgh has made every reasonable effort to ensure that Edinburgh Research Explorer content complies with UK legislation. If you believe that the public display of this file breaches copyright please contact openaccess@ed.ac.uk providing details, and we will remove access to the work immediately and investigate your claim.



1

Review of experimental research on seismic retrofit schemes with FRP for deficient RC beam-column joints

2 Daniel A. Pohorvles, PhD. EPICentre, Dept. Civil, Environmental and Geomatic Engineering, UCL, U.K., 3 daniel.pohoryles.10@ucl.ac.uk (corresponding author)

4 Jose Melo, EPICentre, PhD, EPICentre, Dept. Civil, Environmental and Geomatic Engineering, UCL, U.K.

- 5 Tiziana Rossetto, Professor, EPICentre, Dept. Civil, Environmental and Geomatic Engineering, UCL, U.K.
- 6 Humberto Varum, Professor, CONSTRUCT-LESE, Faculty of Engineering, University of Porto, Portugal
- 7 Luke Bisby, Professor, Dept. Civil and Environmental Engineering, The University of Edinburgh, U.K.

8 Abstract

- 9 This paper aims to review and critically assess experimental research efforts on the seismic retrofit of
- 10 existing reinforced concrete (RC) beam-column joints with fibre-reinforced polymer (FRP) sheets of
- 11 the past 20 years. The review of the literature revealed several promising features of FRP
- 12 strengthening schemes. FRP retrofits can be used to address a number of different deficiencies in
- 13 non-seismically designed RC members framing into beam-column joints. A majority of studies
- 14 concentrate on joint shear strengthening and strengthening in the axis of principle stress is found to
- 15 be most effective. Other strategies include counter-acting the weak-column/strong-beam in non-
- 16 seismically designed specimens by means of column flexural strengthening, as well as plastic hinge
- 17 relocation within the beams, away from the joint. Only a limited number of studies look at combining
- 18 several of these retrofit objectives into a more complete retrofit of the joint sub-assemblage. In most
- 19 studies it is observed that simple FRP wrapping is used for anchorage, which is not always effective.
- 20 Instead, it is shown that anchorage by means of FRP anchors or mechanical anchors is required to
- 21 achieve adequate strengthening in most cases. Next to the detailed discussion of the literature, a
- 22 database of all tested specimens is compiled and analysed. An assessment of shear strengthening
- 23 design equations from major design guidelines is made based on the experimental results collected in
- 24 this database, highlighting the need for their further improvement. Moreover, analysis of the database
- 25 reveals a lack of tested specimens with realistic test set-ups, including scaled specimens, testing
- without axial load, as well lack of slab and transverse beams. It is found that these parameters heavily 26
- 27 affect retrofit effectiveness and may lead to non-conservative results. Moreover, on average, the
- 28 effectiveness of repairing pre-damaged specimens is found to be similar to that of retrofitting
- 29 specimens without damage.

30 Introduction

Reinforced concrete (RC) structures built in earthquake prone areas and designed to resist gravity loads only or before the introduction of modern seismic codes (pre-1970's or 80's), typically display several deficiencies resulting in inadequate behaviour under seismic loading. In particular, the hierarchy of strengths around beam-column joints plays a critical role in the overall cyclic behaviour of RC structures. Avoiding premature failure of said joints is hence a fundamental principle in modern seismic design to allow the framing members reach full capacity (Kappos and Penelis 1996).

37 Adequate energy dissipation under seismic loading also relies on an appropriate hierarchy of

38 strengths between the framing members of the joints. To achieve larger global structural

39 displacements and hence higher ductility under seismic loading, modern seismic design guidelines

40 aim to ensure beam-hinging precedes column-hinging mechanisms (Fardis 2009).

41 For existing structures, in which an adequate seismic behaviour is not ensured, structural retrofit often 42 allows changing the expected failure mechanism. A variety of retrofit methodologies and materials 43 exist, traditional retrofitting techniques, such as concrete or steel jacketing, addition of shear walls and 44 epoxy repair, have proven effective and popular, as suggested in a detailed review by Thermou and 45 Elnashai (2006). Concrete jacketing involves addition of new longitudinal bars, ties and a layer of 46 concrete which increase the cross-section dimensions. Steel jacketing refers to encasing the element 47 with steel plates and filling the gap with grout or epoxy resin. These techniques aim increase both 48 flexural and shear strength and improve concrete confinement. Yet, many of these methods present 49 practical issues, namely, adding weight and stiffness to structural elements, increasing their cross-50 section dimension, as well as being and labour intensive (Engindeniz et al. 2005).

51 In the last twenty years, retrofitting RC structures with fibre-reinforced polymer (FRP) are growing in 52 interest due to the light weight and high strength combined with corrosion resistance of FRP 53 materials. The application of FRP wraps can be performed rapidly and without disrupting the building 54 occupancy, which is another major advantage, as it reduces the down-time in businesses and the 55 need of relocating inhabitants in residential properties (Bousselham 2010). FRP retrofits however also 56 suffer from disadvantages, such as weak bond to concrete and low fire resistance. To improve the fire 57 resistance of FRP, however, solutions are being investigated, for instance applying intumescent 58 coatings (e.g.: Ji et al. 2013). Recently, beam-column joint retrofits using other composite materials 59 using mortar instead of epoxy to bind the fibres to the concrete substrate have hence also become

popular, including the use of textile reinforced mortars (Al-Salloum et al. 2011), or fibre reinforced
cement composites (Del Vecchio et al. 2018), benefiting from better bond, as well as improved
thermal and fire resistance.

This paper will instead focus on the use of FRP for joint shear strengthening. FRP can be used to
ensure capacity design hierarchy of strengths by providing selective strengthening of members
framing into the joint relative to their respective load capacities. FRP upgrades are used to address
distinct strengthening objectives:

- Joint shear strengthening by means of sheets placed in the horizontal (e.g.: El-Amoury and
 Ghobarah 2002), vertical (e.g.: Le-Trung et al. 2010) or diagonal axis (e.g.: D'Ayala et al.
 2003) across unobstructed joint panels.
- Column flexural strengthening to prevent unwanted column hinging failure, using straight FRP
 sheets along the column axis (Antonopoulos and Triantafillou 2003), L-shapes (Akguzel and
 Pampanin 2012a; Garcia et al. 2014; Yu et al. 2016), near-surface-mounted (NSM) FRP
 (Hasan et al. 2016; Prota et al. 2004) or FRP anchors (Shiohara et al. 2009).
- Increasing confinement and ductility (Akguzel and Pampanin 2012a; Al-Salloum and
 Almusallam 2007; Antonopoulos and Triantafillou 2003; Del Vecchio et al. 2014; Engindeniz
 et al. 2008b; Shiohara et al. 2009) or shear strengthening (Lee et al. 2010) of columns using
 sheets wrapped fully around the column.
- Preventing beam bar-slippage and cracks opening at the beam-joint interface using FRP
 sheets along the bottom face of beams (Engindeniz et al. 2008b) or L-shapes at the bottom
 corner between beams and columns (El-Amoury and Ghobarah 2002; Ghobarah and El Amoury 2005).
- Shear strengthening beams with FRP U-wraps perpendicular to the beam axis (Akguzel and
 Pampanin 2012a; Alsayed et al. 2010; Antonopoulos and Triantafillou 2003; Engindeniz et al.
 2008b).

While the number of research papers in this field is increasing rapidly in the last years, the last
thorough state-of-the-art review paper dates back to 2010 (Bousselham 2010). Understanding current

trends and compiling what has been tested so far is crucial to reveal promising avenues for future
research, as well as uncovering gaps in available experimental data. The aim of this paper is hence to
address this need to review and critically assess the state of experimental research on RC beamcolumn joint retrofits with FRP.

91 A detailed review and a database of all existing experimental research on seismically strengthened 92 beam-column joints with FRP is presented in this paper. The retrofit schemes are assessed in terms 93 of their effectiveness (increase in strength or ductility), as well as their practical applicability to real 94 structures. At the end of this review, an assessment of shear strengthening design equations from 95 major design guidelines is made based on the experimental results collected in the database. This is 96 followed by a statistical analysis of the database addressing the experimental design in terms of type 97 and geometry of set-ups, material properties and leading to a discussion on the parameters affecting 98 the effectiveness of retrofits.

99

100 Review of existing research

Beam-column joint specimens with typical pre-1970's design deficiencies, retrofitted with FRP and tested under cyclic loading are the focus of this review. Research papers only considering static loading (push-over) are hence excluded and so are experimental specimens designed according to modern seismic design codes. Shake table tests on full frames or cyclic tests on individual RC members are also excluded from this review. Furthermore, research on retrofitting bridge pier connections is excluded in this study, due to the significant differences in terms of size, loading and desired response to seismic actions between buildings and bridges.

To facilitate a critical and systematic review of the literature a database of experimental work on the seismic FRP strengthening of RC beam-column joints in buildings is compiled. A summary of this database can be found in Appendix A. This work builds upon similar efforts by other researchers (Bousselham 2010). In the process of the review of existing literature, a number of parameters were recorded, including the type of deficiencies in the control specimen, the geometry and dimensions of specimens, the material properties (concrete, steel, FRP), details on the FRP strengthening (aim, fibre type, number of layers, dimensions, surface preparation, presence and type of anchors), as well

as information on the experimental set-up, loading, instrumentation and the available results of theexperiments (load and displacement ductility).

This review is organised thematically by geometry of the tested beam-column joint specimens (exterior, interior or corner joints), as well as the main strengthening objective (joint shear strengthening, column strengthening, beam strengthening, or multi-objective retrofit). Every major section is completed by a concise summary of observations, as well as a table summarising representative results obtained from the respective experiments and visually describing the different retrofits using schematics. As the achieved ductility is not always published in the studied papers, for the summary tables of each chapter, only comparisons in strength increase are given.

124 Shear strengthening of two-dimensional exterior joints

A well-researched topic in the literature is the shear strengthening of shear-deficient exterior joints without slab or transverse beams. A summary of the four main avenues for shear retrofitting is found in Fig. 1, in which schematics of the X-shaped (a), U-shaped (b), T-shaped (c) and retrofits with multiaxial sheet (d) can be seen. In Table 1, representative strength increases obtained by the different papers described in this section are also included to ease their comparison.

Ghobarah et al tested six shear deficient full-scale exterior joints and propose two different 130 retrofit layouts (Ghobarah and Said 2002). The "U"-configuration, with a single layer of bi-directional 131 132 GFRP sheet wrapped around the free sides of joint, performs well when anchored with steel plates 133 (specimen T1R). Delayed shear failure with nearly double the ductility is observed, limited only by the 134 tearing of the single layer of FRP. With two GFRP-layers extended above and below the joint on the 135 column faces (T2R), the behaviour is further improved. Failure is transferred to a ductile beam hinging 136 mechanism, achieving a five-fold increase in energy dissipation. Without anchorage (T4), early 137 debonding occurs, impeding contribution to the shear strength.

For an "X"-configuration of unidirectional GFRP wrapped diagonally around the joint (T9), using steel angles to ease the FRP-application, initial damage is transferred to the beam, however, as the FRP debonds, the joint still fails in shear. An increase in ductility similar to T2R is achieved, with a slightly lower increase in energy dissipation. The results would suggest that adequate anchorage to resist

debonding could improve this layout. Overall, the importance of anchorage to avoid debonding isparticularly highlighted by these experiments.

144 Compared to a joint designed to modern Canadian RC guidelines (CSA A23.3 1994), 80% of the
145 displacement ductility and 90% of the load capacity can be achieved by the best retrofit, however with
146 about half the energy dissipation (Said and Nehdi 2004).

147 Antonopoulos and Triantafillou (2003) designed 18 2/3-scale exterior joints to fail in shear, so 148 as to assess the relative contribution of different retrofit parameters on their shear capacity. In all 149 retrofits, FRP is placed on the joint along the vertical and horizontal axis in a T-shape and delayed 150 shear failure is observed. Using an equivalent amount of GFRP results in slightly better energy 151 dissipation and shear strength (+45%) compared to CFRP (+41%), likely due to its higher rupture 152 strain, as fracture is observed for the CFRP sheet. An increase in number of FRP layers is also found 153 to enhance strength and energy dissipation, but not proportionally. Specifically, doubling the number 154 of horizontal layers (F21) is found to achieve a higher strength increase (+65%), than in the vertical 155 direction (F12, +15%), compared to a single-layer retrofit (F11).

Doubling the applied axial load in F22A, is found to be an important factor (+22% of strength), due to enhanced joint confinement. Bond properties are shown to be equally important, as in all unanchored retrofits, debonding is observed. Using FRP wraps for anchorage (F22W), achieves significant shear strength enhancement (+24%) compared to an unanchored counterpart F22. The effect of anchorage is dramatically stronger (+250%) for an FRP-strip retrofit anchored with steel plates (S33L). This can be attributed to the weaker bond properties of FRP strips compared to sheets.

Other important factors for retrofit effectiveness are reinforcement detailing and geometry, with just one joint shear stud significantly reducing the effectiveness of the retrofit (-48%). For specimens with a stub transverse beam, the efficiency of the retrofit is significantly reduced (up to -78%), as FRP cannot be fully applied to both sides of the joint panel. This indicates that results of retrofit efficiency inferred from scaled specimens with simplified geometry may not be transferrable to actual structures.

167 The effect of the steel shear reinforcement in the joint is the objective of Karayannis and 168 Sirkelis (2008) study on 12 half-scale joints strengthened by U-shaped CFRP wraps. Anchorage is 169 achieved perpendicular wrapping in beam and columns. The retrofit strategy is effective in

strengthening the joint and relocating damage into the beam. Lower damage is observed for
specimens with transverse steel reinforcement, but the retrofit effectiveness is higher for specimens
with no shear studs (+88.4% vs +65.3%). This highlights the effect of steel reinforcement ratio on the
FRP retrofit effectiveness. In real pre-1970's joints, often the steel reinforcement is low or inexistent,
which means the potential strength enhancement with FRP will be higher.

Le-Trung et al. (2010) tested seven 1/3-scaled exterior joints with no transverse steel
reinforcement, using two different CFRP retrofit layouts to prevent joint shear failure and ensure
ductile beam hinging instead. Combined with the unrealistic scale of specimens, also no axial load is
applied in these experiments, meaning the results should be taken with care.

179 For the "T"-shaped configuration, CFRP sheets are applied on two sides of the joint, extended onto 180 column and beam. Additional "L"-shaped FRP sheets are applied at the corners between beams and 181 columns to prevent bar-slippage and delay crack opening, with anchorage strips at column-ends 182 and/or beam-ends. Delamination is observed for all specimens but delayed for specimens with 183 anchorage strips compared to the non-anchored specimen (RNS-1). This leads to higher ductility, up 184 to three times the control specimen. For specimen RNS-5 with beam-end anchorage, debonding near 185 the joint is observed rather than the beam-end, leading to a low strength increase (+11%). Strip 186 anchorage at the extremities only is hence not sufficient and further strips, or mechanical anchorage, 187 would be required. Compared to a seismically designed specimen, only specimen RNS-6, with two 188 FRP-layers, achieves a higher strength increase (+32% vs +22%).

189 The "X"-shaped configuration with fibres at 45° on three sides of the joint (RNS-3 and RNS-4) is found 190 to be most effective in increasing ductility, with a five-fold increase compared to the control specimen. 191 Compared to Ghobarah's (2002) retrofit, diagonal wrapping is extended onto the columns, which 192 creates better anchorage, hence preventing debonding. Additional "L"-shaped strips without 193 anchorage in specimen RNS-4 only achieve a delay in the onset of failure, however early debonding 194 reduces its effectiveness at higher drift ratios. In terms of strength, the improvement is less significant 195 than for the T-shaped retrofit, with a similar increase is obtained for both X-shaped retrofitted joints 196 (+17% and +16%).

197 Realfonzo et al. (2014) tested a series of eight full-scale shear-deficient exterior joints, half 198 with a "weak column" configuration (Type 1) and the other half with a "strong column" configuration.

While all eight specimens are two-dimensional, for six specimens, the presence of a floor slab issimulated by means of thick steel plates positioned over a depth of 300 mm from the top of the beam.

201 Both types of specimens are retrofitted with U-shaped CFRP sheets for joint strengthening and CFRP 202 wrapping of the columns for confinement. For the "weak column" specimens, additional threaded steel 203 rods for column flexural strengthening are provided. The first specimen was retrofitted with the largest 204 amount of FRP in the joint, using two U-shapes of 150 mm width, but without anchorage. Only a slight 205 increase in strength (+23%) was obtained and joint shear failure was not prevented due to FRP 206 delamination. The strength is nearly doubled (+98%) for a retrofit of the same specimen with two U-207 shapes of only 100 mm width but adequate anchorage. In this case joint shear failure can be 208 prevented and a ductile beam hinging mechanism is promoted. For the three "strong column" 209 specimens, three anchored U-shaped CFRP strips of 50 mm width are applied in the joint area. Joint 210 shear failure is delayed, but not prevented due to delamination of the U-shapes after opening of 211 flexural cracks at the column-joint face. Due to differences in the CFRP strengthening of the exterior 212 column face, flexural cracking occurred at different stages for the three specimens, hence leading to 213 strength increases varying from 54% for X-shaped column strengthening to 75% for longitudinal 214 strengthening. It is important to add that FRP strain in the U-shapes was measured throughout the 215 tests, with maximum recorded strain values between 1/3 (0.25%) and 1/2 (0.4%) of the ultimate FRP 216 strain (0.8%). These values are similar in magnitude to the 0.4% design strain often assumed in 217 design codes to avoid potential debonding (Pohoryles and Rossetto 2014). Finally, while the authors 218 made an effort to include the presence of a floor slab in their design, the presence of potential 219 transverse beams would affect the feasibility of the retrofit scheme significantly.

Hadi and Tran (2014, 2016) proposed an unusual retrofit method for shear deficient exterior joints. Glued-on concrete covers are installed around the columns and joint to modify the square cross-sections and exploit the increased effectiveness of FRP wrapping in circular cross-sections. Three full-scale specimens with different amounts of U-shaped CFRP in the joint (one, three and six layers) are then tested. While the retrofits with lower amounts of FRP achieve delaying joint shear failure, only with six layers of FRP a successful change to beam hinging is observed. The increase in strength and ductility observed is not proportional to the amount of FRP used. With one (+84% in

strength) and three layers (+116%), FRP rupture in the column and joint are observed, while for the
specimen with six layers of FRP (+140%), no debonding or rupture is seen.

While the increase in strength employing this joint shear strengthening strategy is significant, it is highly impractical in real structures with transverse beams, walls or slabs present, which prevent the placement and continuity of the additional circular covers. Moreover, the effect of the additional concrete covers alone is not assessed by the authors of the study. This would however allow a fairer assessment of the effectiveness of the FRP intervention.

This section presented arguably the most prominently featured retrofit objective in the field, shear strengthening of two-dimensional exterior joints. As highlighted in Fig. 1, the suggested retrofits in this section can be split into four groups:

• the U-shaped configuration, wrapping the joint horizontally using U-shaped FRP;

• the T-shaped configuration, applying FRP in horizontal and vertical directions in the joint;

the X-shaped configuration, applying the FRP in the diagonal of the joint, following the angle
 of principle stress.

• Application of bi- or quadri-axial FRP in the joint, similarly to the X-shaped configuration.

242 A main observation from all experiments is the need for anchorage. For U-shaped configurations, 243 Ghobarah and Said observed no improvement in behaviour without anchorage. Similarly, Realfonzo 244 et al (2014) obtained a modest strength increase without anchorage, compared to a very strong 245 (+99%) increase for an adequately anchored U-shaped retrofit. Anchorage is also found to be crucial 246 in the study by Antonopoulous and Triantafillou (2003), which compared a variety of T-shaped retrofits 247 with different amounts of horizontal and vertical FRP. It is found that the effect of horizontal FRP 248 layers on the strength of retrofitted joints is more important than that of vertical layers. The effect of 249 axial load is also found to be a critical parameter.

Comparing X-shaped retrofits with U-shaped or T-shaped retrofits, despite having the fibres oriented
in the axis of principle stress, a reduced strength enhancement is found by Ghobarah and Said (2002)
and Le-Trung et al. (2010). In both cases, this may however be associated to debonding problems for
the X-shaped configuration. In practical terms, retrofits with horizontal and vertical sheets of FRP are

easier to anchor, as they can be anchored on beams and columns using steel anchors or FRPwrapping.

Hadi and Tran (2016) proposed a highly successful retrofit scheme, which consists of adding concrete covers to render the joint cross-section rounder before applying U-shaped FRP-wrapping. While the retrofit is the most effective in terms of strength increase (+140%), it's applicability to real structure is debatable. Generally, practical applicability of the retrofit schemes presented in this section is limited to structures without RC slabs or transverse beams, as these would obstruct the retrofits and require significant changes to the proposed lay-outs or partial removal of RC members.

262 Shear repair of two-dimensional exterior joints

Five recent studies specifically investigated the effect of pre-damage on the effectiveness of interventions by repairing exterior joints with FRP. Agarwal et al. (2014) repaired a damage full-scale specimen using cement grouting and five layers of GFRP U-wrap in the joint, extended and anchored by five layers of full-wraps around the beam. The full strength of the control specimen is not recovered, as only 68% of the capacity is reached. Moreover, a reduction in initial stiffness is observed and joint shear failure is not prevented, due to debonding of the GFRP in the joint panel. An improvement in ductility is however observed (+43%).

270 Garcia et al. (2012, 2014) repaired three full-scale exterior joints by replacing the damaged 271 core with concrete of nearly double the compressive strength. The joints are then rehabilitated with 272 CFRP U-wraps around the joint extending into the column, longitudinal FRP along the column for 273 flexural strengthening, as well as full confinement wraps of the column and beam to ensure an 274 adequate beam hinging mechanism. While FRP rupture and significant damage are observed in the 275 joint core of the repaired specimens, a significant strength increase of +51.2% (two layers of FRP) up 276 to +119% (three layers) over the control specimen, corresponding to a maximum of +69% compared 277 to a specimen repaired by concrete replacement only, is achieved. Notably, this increase in capacity 278 corresponds to 85% of the shear strength of ACI code-compliant RC joints (ACI 2002a).

Yurdakul and Avsar (2015) employed an improved version of "X"-configuration proposed by
Ghobarah and Said (2002), with two layers of CFRP and additional FRP wrapping for anchorage to
the beam and column, to repair one full-scale exterior joint. After application of a strong repair mortar

(60 MPa), two layers of 200 mm wide CFRP sheets were applied in the joint region at a ±45° angle 282 283 with respect to beam axis. Joint shear failure, as observed for the control specimen, is not prevented, 284 as FRP fracture, followed by spalling of the repair mortar is observed. The repaired specimen does 285 hence not reach the capacity of the original specimen (-25%) and the initial stiffness is reduced by 286 28%. The non-achievement of the retrofit objective is explained by an eccentricity in axial loading, 287 causing larger stress in one side of the retrofit. It can however also be deduced that the repair of 288 damaged concrete with the mortar was not done in the most effective way, as a significant reduction 289 in strength and stiffness were obtained. The type of shear failure with rupture of the FRP is also a 290 reminder with regards to the use of lower design strains in the design procedures, rather than 291 assuming full development of the FRP, hence avoiding brittle rupture.

292 Beydokhti and Shariatmadar (2016) tested the effect of the level of pre-damage on repair 293 effectiveness, applying cement mortar and CFRP U-wraps on the joint for four 2/3-scaled exterior 294 joints of increasing pre-damage. L-shaped CFRP is also applied at the beam-column interface and 295 anchored using a layer of FRP. Despite adequate anchorage length according to the ACI 440.2R.08 296 guidelines (ACI 2008), buckling and debonding of the beam-CFRP is observed, resulting in flexural 297 failure of the beams at the joint-interface. With increasing pre-damage levels, an increasing 298 deterioration of initial stiffness is observed. For the two specimens with the lowest pre-damage, the 299 strength of the control specimens is recovered, with a slight increase of 2.5% and 5.9% respectively. For the specimens damaged to near-collapse and collapse damage states however, a reduction in 300 301 strength of 19.5% and 15.3%, respectively, is obtained. These observations suggest that a full 302 recovery of a severely damaged structure is not achievable with the proposed repair scheme and a 303 storey drift of 1.5 % for a damaged structure is introduced as reparability storey drift based on the 304 tested joints.

Faleschini et al. (2019) repaired three full-scale, one-way exterior joints damaged by a shear mechanism in the joint region. The repair process of the pre-damaged joints started with restoring the joint with a premixed cement-based mortar. Two CFRP retrofits were tested and compared to a textile-reinforced mortar (TRM) repair scheme. The first FRP repair used diagonal FRP in the direction of expected principal stress, while the second scheme used U-shaped FRP. In both schemes, FRP jacketing of the columns above and below the joint is applied. This provides anchorage for the X-

311 shaped scheme, while the U-shaped scheme uses transversal FRP in the beams for anchorage. 312 None of the repair schemes achieved restoration of the original strength of the joints. While 313 detachment of the TRM lead to a loss in strength of 41%, for the X-shaped FRP fracture in direction of 314 the principal stress with a strength loss of 30% was observed. For the U-shaped FRP, damage in 315 concrete below the jacket lead to bulging of the FRP and a 34% loss in strength. Overall the 316 performance of the two FRP schemes can be seen as similar, but in the case of the diagonal retrofit, 317 due to the obtained fracture of fibres, it can be hypothesised, that a larger number of FRP layers may 318 improve the repair performance.

319 With regards to repair of exterior joints, similar approaches to the retrofit schemes have been 320 tested, however the behaviour of the undamaged specimen was often not recovered. Based on the 321 limited tests, it would appear that this is mainly due to the level of repair of the damaged concrete with 322 mortars being insufficient to rehabilitate the joint, combined with an insufficient amount of FRP 323 calculated for the pre-damaged joints. Looking at results by Beydokhti and Shariatmadar (2016), the 324 level of pre-damage is the most important aspect deciding whether the strength of a damaged joint 325 can be reinstated. This observation is of interest, when looking at the repair scheme by Garcia et al 326 (2012, 2014), which starts with a complete replacement of the damaged joint core concrete, rather 327 than only superficially repairing the joint with mortar. For this repair a significant increase in strength is 328 achieved, while the repaired joints by Agarwal et al. (2014), Yurdakul and Avsar (2015) or Faleschini 329 et al. (2019), which only repair the damaged joint core by grouting before the FRP retrofit, cannot 330 recover the strength of the pre-damaged joint.

331 Shear strengthening of corner joints with slabs and/or transverse beams

A shear-deficient corner joint with slab and a (stub) transverse beam, retrofitted with CFRP is compared to RC-jacketing by Tsonos (2008). The retrofit scheme considers realistic geometric constraints and uses ten horizontal layers of FRP applied on the accessible joint face, as well as nine vertical and seven horizontal layers to improve flexural and shear capacities of the columns, respectively. The joint FRP is anchored with CFRP strips fully wrapped around the beam through predrilled slots in the slab. The strength of the joint is improved by 70% and a more ductile beam hinging mechanism is achieved, however due to the lack of anchorage along the beam, damage is

concentrated at the beam-joint interface. In comparison to an equivalent RC-jacketed retrofit, similar
 strength is obtained, but energy dissipation and stiffness are reduced.

341 Ilki et al. (2011) test corner beam-column joints with slab and transverse beams with very low 342 concrete strength (8.3 MPa) and without joint shear reinforcement, representing a typical Turkish pre-343 1990's structure. Three layers of bi-directional CFRP are placed on the free side of the joint and anchored using diagonal sheets of FRP wrapped across the beams, which is practically feasible for 344 345 exterior joints. For the strengthened specimen, joint shear failure is obverted, but beam bar slippage 346 becomes the dominant mechanism, hence only a slight increase in strength is achieved (+18%). To 347 avoid this, beam bars are welded to the back of the joint, which leads to a more ductile and dissipative 348 beam-hinging failure. Using FRP sheets in the bottom face of the beam instead of welding additional 349 bars is not considered as an option but would be an interesting avenue to explore to achieve a full 350 FRP retrofit.

351 Full-scale corner joints (Del Vecchio et al. 2014) with one transverse beam are retrofitted with 352 quadri-axial CFRP sheets in the joint panel and FRP U-wraps at the beam-joint interface to avoid 353 brittle joint shear failure (specimen FL1). While failure mode and ductility cannot be changed, strength 354 is increased by 17%. A second, more complete scheme, adds perpendicular unidirectional sheets on 355 columns and beams (specimen FS1) to change the failure mechanism, but also to increase the 356 energy dissipation. A variation of this scheme with double the amount of FRP is also tested (specimen 357 FS2). With confinement of the column, a ductile behaviour with large increase in strength (+32% and 358 +49% for FS1 and FS2, respectively) is observed. For specimen FS1, shear failure in the joint is not 359 prevented, but only delayed. Doubling the amount of FRP achieves preventing joint shear failure and 360 moving failure to column hinging, highlighting the need for column flexural strengthening to overcome 361 a strong-beam/weak-column strength hierarchy in pre-1970's structures. Finally, an important 362 observation is made in terms of the recorded strain values. Larger strains, close to the ultimate strain 363 of the material are recorded by the authors, suggesting that the limits proposed by design guidelines 364 (e.g. 0.4% strain) are conservative.

365 Shear strengthening of two-dimensional interior joints

366 Mosallam (2000) compared the effectiveness of CFRP and GFRP on two half-scale interior 367 joints retrofitted with two layers of bi-directional sheets fully wrapped around beams, columns and

joint, as well as diagonal straps around the joint. The tested specimens with GFRP display a greater increase in ductility, but in terms of ultimate load, the results for both materials are identical. The retrofit is heavily limited by practical considerations in terms of retrofit layout and scale, as slabs and transverse beams would not allow placing FRP wraps around every member.

D'Ayala et al. (2003) studied the retrofit of interior joints characterised by either a weak-beam (WB) or a weak-column configuration (SB). L-strips are applied at the corners of the joint to improve the capacity of the beam, as well as vertical and horizontal FRP sheets in T-form on the joint to increase its shear strength (W1). All strips are anchored by perpendicular wraps at beams and columns, but delamination still occurs and the retrofit is not successful in shifting the failure mode. A maximum increase in strength of 17% is obtained for this strengthening scheme.

378 A further layout is hence tested, using diagonal strips around the joint core with full wrapping of 379 beams and column (W2). This X-shaped retrofit is more effective than the orthogonal retrofit, not only 380 because of the direction of fibres, but also because the joint is more confined at its corners. The most 381 significant improvement in terms of strength (+93%), but also in energy dissipation and reduction in 382 stiffness degradation are obtained. Still, joint cracking is observed, mainly attributed to the low 383 concrete strength (f_{ck} = 10MPa). The same retrofit schemes are also tested as repair schemes on the 384 fully damaged control specimens, following removal of damaged concrete and grouting. In line with 385 observations for exterior joints in this review, no improvement in behaviour is observed, even if the 386 strength of the original joint is recovered. Finally, the authors state that their retrofit design does not 387 include the presence of floor slabs, which would restrict the applicability of the suggested retrofit, 388 unless the floor slab is perforated.

Lee et al. (2010), applies horizontal FRP in the joint for full-scale interior specimens, anchored to the beams with steel-angles to provide shear strengthening. The strengthening is combined with four layers of CFRP strip along the corner of the columns and through the joint. The retrofit is successful in increasing damage in the beams and delaying joint shear failure. This leads to improved ductility, with a more dissipative failure mechanism (+90%) and a higher load capacity (+36%).

394 Column-strengthening in interior joints

395 To achieve an adequate failure mechanism, next to joint shear strengthening, column flexural 396 strengthening is often also required. Three distinct strengthening schemes for columns in beam-397 column joint sub-assemblies are identified in the literature and summarised in Table 2 and Fig. 2, in 398 which the retrofits are also depicted schematically. Prota et al (2004) carried out tests on ten half-399 scale interior joints with weak-column/strong-beam configuration under three different axial load levels 400 (v=0.1, 0.2 and 0.3). The aim of their work is to move failure from the columns to the beams. In a first 401 stage, the effect of column confinement CFRP wrapping alone is compared to wrapping combined 402 with flexural strengthening through near-surface mounted (NSM) CFRP rods applied continuously 403 through the joint between both columns.

404 Using continuous NSM rods, as shown in Fig. 2 (b), failure can successfully be moved away 405 from the columns, leading to higher strength increase (up to +62%) compared to confinement 406 wrapping alone (+33%). As failure is now moved to the joint, ductility is lowered, and additional 407 strengthening of the joint is hence applied by means of bidirectional CFRP sheets (labelled JS in Fig. 408 2 (b)). This full retrofit can lead to similar strength increase (+83%), but also strong increase in 409 ductility (up to +73%). In practice, addition of the bidirectional sheets however prevents the retrofit 410 from application in interior joints with transverse beams. The two main observations of this study are 411 that higher axial loads lead to a larger strength increase and that the flexural strengthening of the 412 columns (NSM rods) needs to be applied continuously through the joint, otherwise flexural failure of 413 the columns cannot be prevented.

414 A similar method, feasible for interior joints with slabs, uses bundled CFRP strands with fan-415 shaped anchors on either end, passed through small plastic tubes at the column corners (Shiohara et 416 al. 2009). This retrofit shown in Fig. 2 (c) has the advantage of providing continuity of the longitudinal 417 FRP along the column, as well as contributing to the shear resistance mechanism by confinement of 418 the joint. The retrofit is tested on one-third scale interior joints without slab and no axial load. An 419 increase in maximum story drift (+30%) and shear force (+13%) are obtained, as yielding of the column bars is prevented, but damage in the joint core is not reduced. Slippage of the CFRP strands 420 421 is observed and energy dissipation hence not improved. The retrofit shows potential for flexural 422 column strengthening, however testing on a more realistic specimen and additional joint shear 423 strengthening are required.

424 Recently, Yu et al. (2016) proposed an easily applicable retrofit using L-shaped FRP 425 laminates at the corners of beams and columns in weak-column interior joints. The L-shapes are 426 anchored by full wraps on the columns and U-shapes on the beams (Fig. 2 (a)). The effect of pre-427 damage level, axial load (v= 0.3 and 0.5), as well as FRP material (CFRP and BFRP) are tested on 428 realistic interior joints with slab and transverse beams. Successful reversal of the hierarchy of 429 strengths with beam-hinging is observed for all specimens. With increased extent of damage, a 430 reduction in initial stiffness, but no significant influence on maximum strength (less than 5% 431 difference) or ultimate drift are observed. Unlike observations by Prota (2004), the effect of increased 432 axial load on strength is minimal (+3%).

Finally, using CFRP results in a stronger increase in capacity (up to +26%) compared to BFRP (+11%), but a lower increase in ultimate drift (24% vs 49%). This is a consequence of the higher strength and stiffness of CFRP and echoes results obtained for CFRP and GFRP by other authors (e.g. Antonopoulos and Triantafillou 2003). It is worth noting that the effective strain in both FRP materials is half the guideline predictions (ACI 2008). Yu et al. propose an improved conservative strain calculation for L-shaped laminates, highlighting that effective strain in FRP can limit retrofit effectiveness.

440 Column strengthening in beam-column joint sub-assemblies is a topic generally only 441 addressed by providing confinement to the column above and below the joint. The three studies in 442 this section however highlight the importance of flexural strengthening of columns in pre-1970's joints 443 that often suffer from an inadequate weak-column/strong-beam hierarchy of strengths. Prota et al. 444 (2004) show the need for using continuous flexural strengthening through the joint in order to prevent 445 column hinging. Their use of NSM bars at the column faces is however considerably less practical 446 then the proposal of Shiohara et al. (2009), which instead use FRP strands passed through holes at 447 the corners of the columns. This retrofit has the advantage of only needing minor intervention to the 448 slab in order to be applicable in structures with slabs and transverse beams, while the NSM bars on the column face could not be continued through the transverse beam. Using L-shapes in the top and 449 450 bottom columns anchored with FRP wraps around the beams (Yu et al. 2016) is also successful in 451 preventing column hinging, while being much simpler to apply. Only in the presence of infill walls this 452 retrofit would be less practical then Shiohara's.

453 Beam-strengthening in joints

Following capacity design principles, beam-hinging is the preferred mode of failure for a joint subassembly. After considering retrofits against brittle joint and column failure, the focus of the research presented in this section lies on eliminating brittle beam-bar bond-slip failures and relocating the plastic hinge away from the beam-joint interface. Typical retrofit layouts for beam-strengthening in beam-column joint sub-assemblies are depicted in Fig. 3, while key results are shown in Table 3.

459 Mukherjee and Joshi (2005) aim to prevent brittle beam-bar anchorage failures in 1/3-scale interior joints using L-shaped FRP sheets between beams and columns (Fig. 3 (a)), or a pre-cured 460 461 CFRP strip along the top and bottom of the beams (Fig. 3 (b)). For scheme (a), the type of FRP used 462 (CFRP and GFRP) and amount of FRP (one or two layers) are varied. The three retrofit variations successfully prevent pull-out of the beam rebars. For ductile specimens with adequate bar anchorage, 463 464 the CFRP-sheet retrofit leads to higher strength (+58% vs +53%), but lower ductility than GFRP. The 465 strip retrofit (b) proves however most effective (+113%). For non-ductile specimens, the GFRP 466 retrofitted specimen achieves a larger strength increase (+99% vs +79%), while the strip retrofit (b) 467 proves less effective (+68%) than the L-shape retrofit (a). While the obtained strength increase is 468 significant, it is important to re-iterate the 1/3-scale of the specimens, which may increase the retrofit 469 effectiveness.

470 Ghobarah and El-Amoury (2005) propose to increase resistance to bond-slip in full-scale 471 exterior joints using CFRP sheets along the bottom of the beam, continued in an L-shape along the 472 interior face of the bottom column of two exterior joints (Fig. 3 (a)). Using two FRP layers and a simple 473 steel angle with expansion anchors for anchorage, the behaviour does not improve, due to debonding 474 and fracturing of the sheets. A reduction in strength (-11%) and the same ductility are observed. With 475 four CFRP layers and an improved anchorage system using a curved steel plate on a concrete 476 haunch and four external steel ties around the outside of the column, a ductile hinging mechanism is 477 achieved, however very close to the joint interface. A large strength increase (+40%) and a nearly 478 doubled ductility are the consequence of the improved anchorage, highlighting how important it is to 479 be considered.

480 Attari et al. (2010) worked on improving the behaviour of 1/3-scaled deficient interior beam-481 column joints by addition of horizontal strips of FRP on the top and bottom of the beams (Fig. 3 (b)).

482 In a first retrofitted specimen, a strip of CFRP laminate is applied, while in a second repaired 483 specimen, next to the CFRP, additionally two layers of GFRP L-shapes are applied at the four beam-484 column corners and anchored using GFRP wraps on the column (Fig. 3 (a)). For the first retrofit, 485 initially an improved behaviour is obtained with an increased peak load of +24%. However, with 486 increased cycling, pull-out of the FRP strip is observed, leading to abrupt reduction in resistance and 487 sever pinching, ultimately causing failure of the specimen. For the specimen with combined CFRP 488 plates and GFRP L-shapes, a larger increase in strength (+44%) is obtained attributed to the 489 prevention of debonding due to additional anchorage with column GFRP wraps.

Russo and Pauletta (2012) combine a CFRP retrofit with steel-plate anchorage of plain
reinforcing bars with inadequate bar anchorage length. The retrofit of exterior joints successfully
prevents bond-slip, which is however mainly attributed to the steel-plate anchorage. Strength increase
in 2/3-scaled specimens is more pronounced for smaller bar diameters (266% for 12 mm vs 136% for
16 mm), for which bond-slip is more critical. For full-scale joints, the strength increase is significantly
lower (49%).

496 Choudhury et al. (2013) developed two retrofits for exterior joints with bond-slip- or shear-497 deficient beams, respectively. Unidirectional CFRP sheets are used at the bottom of the beam to 498 improve bar anchorage, while bidirectional GFRP wraps around the beam aim to improve its shear 499 capacity (Fig. 3 (b)). Bidirectional GFRP U-wraps are also used to strengthen the joint in shear. 500 Investigating the effect of specimen scale (full-, 2/3 and 1/3-scale) for both retrofits, the gain in load 501 capacity is found to decrease with specimen size (from 27% to 12% for the shear- and from 24% to 502 5% for the bond-slip retrofit). Although the findings are based on a specific layout, they still mandate 503 caution when inferring results from scaled experiments.

504 Strengthening of beams near the joint to relocate the plastic hinge (PH) further along the 505 beam is tested by Mahini and Ronagh (2007, 2011) on 1:2.2-scaled exterior joints. Bonding three 506 layers of CFRP-sheet to the beam-web (Fig. 3 (c)), parallel to the beam-axis, anchored with CFRP 507 along the length of the column, which also serves to improve its flexural behaviour, leads to 508 successful PH relocation 150 mm away from the joint face.

This scheme would however not be applicable with slab and transverse beams and an improved
retrofit without FRP in the joint panel and thin FRP-wraps that fit through slots drilled in a slab, is

511 proposed (Eslami et al. 2013; Eslami and Ronagh 2014). As shown in Fig. 3 (b), to achieve PH 512 relocation, CFRP sheets are extended along the beam top and bottom faces for 1) a short length (175 513 mm - one beam depth) or 2) a longer length (350 mm - two beam depths). Anchorage is provided by 514 embedding the FRP into a 25 mm deep groove in the cover of the joint. For one test without this 515 embedment, no improvement in the specimen's behaviour is observed. The shorter beam FRP length 516 (1) successfully relocates PH with a strength increase of 31%. With a longer FRP length, instead, flexural failure is observed at the joint interface, attributed to the anchorage length (groove depth) not 517 518 being sufficient for the length of FRP. While the strength increase is larger (45%), ductility is found to 519 be reduced (-36%).

520 For beam strengthening in deficient beam-column joint sub-assemblies, two main 521 strengthening aims can be discerned. The first one is improvement of beam-bar anchorage to prevent 522 bond-slip failures, the second is plastic hinge relocation away from the joint. Both issues have been 523 addressed by means of applying L-shapes along the corner of beam and column, as well as using 524 strips or plates of FRP on bottom and/or top faces of the beams, often anchored into groves at the 525 joint. Representative results for the strength increase obtained by the retrofit scheme layouts are 526 summarised in Table 3.

Two issues are found to be crucial in the behaviour of these retrofitted joints. Only when adequate anchorage is provided, both types of retrofit are shown to be effective. L-shape retrofits, steel anchors or FRP wraps around the column are shown to be successful. For the simple strips or plates retrofit, embedment into 25 mm deep groves has shown good results for the retrofit scheme suggested by Eslami and Ronagh (2014). The same depth of groove provides insufficient anchorage in the scheme proposed by Attari et al. (2010). The required depth of embedment is indeed not a constant and is dependent on the length of the FRP strip (Eslami et al. 2013).

A second critical element is the effect of scale on the retrofit effectiveness. Choudhury's work showed that the efficiency of beam retrofit schemes in joint sub-assemblies heavily depends on the scale, with scaled specimens achieving larger improvements in performance. This is also confirmed by the results from Russo and Pauletta (2012), who obtain lower strength increase for full-scale specimens or specimens with larger bar diameters.

539 Overall all proposed retrofits are potentially applicable in real buildings. Apart from the initial retrofit by 540 Mahini and Ronagh (2007), which would be restrained by the presence of transverse beam and slab, 541 the other proposed retrofits do not present any practical application issues. The strip retrofit proves 542 more effective in the case of improving ductility of the beams, while the L-shapes are more effective in 543 addressing beam bar anchorage issues. A combination of the two with adequate anchorage and 544 embedment (Attari et al 2010), would hence appear to be the most logical solution.

545 Multi-objective retrofits of joints

546 One major advantage of FRP retrofitting is the possibility of a selective upgrading, e.g. of joint shear 547 capacity, as well as bond-improvement in bottom beam bars and confinement or flexural 548 strengthening of the column. A number of multi-objective retrofit schemes for beam-column joints are 549 identified in the literature and are summarised in Fig. 4, which shows schematics of typical retrofit 550 schemes, and Table 4, highlighting key results. A two-part GFRP retrofit for exterior joints (El-Armoury 551 and Ghobarah 2002) sets the basis for the fib 35 (2006) guidelines. For joint shear strengthening, U-552 wraps anchored with steel plates connected by steel rods are applied. Four unidirectional FRP L-553 shapes along the beam bottom face and inside face of the bottom column, secured using bolted steel 554 angles, are used for rebar bond-slip enhancement (retrofit TR1). A variation of this scheme with 8 layers and two U-shaped steel anchors at the beam ends is also tested (TR2, as shown in Fig. 4 (a)). 555 556 The latter prevents debonding and hence bond-slip observed for TR1, leading to much higher values 557 of drift and an increase in load of 52% (compared to 40%), but ultimately leads to joint shear failure.

558 Interior joints (Al-Salloum and Almusallam 2007) and exterior joints (Alsayed et al. 2010) with 559 a 600 mm wide slab, but no transverse beams, are retrofitted with CFRP, calculated in accordance to 560 El-Amoury and Ghobarah (2002). Two different retrofit layouts are tested: (a) applying horizontal FRP 561 on both faces of the joint (U-wrap for the external joint), wrapping the column above and below the 562 joint, and finally U-wrapping the beam(s) (Fig. 4 (a)); (b) strengthening the joint only, but with steel 563 bolts as anchorage. Both CFRP retrofit schemes delay joint shear cracking, however for the 564 specimens without mechanical anchorage, debonding and rupture of the FRP in the beam is 565 observed. With layout (b), the failure mode is shifted from joint shear failure, to beam hinging and 566 hence a larger ductility. The lateral load capacities for retrofit (a) are however higher (+32% compared 567 to +27%), as the joint and beams are also strengthened, but retrofit (b) can be seen as more efficient

using less material for a similar strength gain. Finally, as mentioned for other schemes, one constraint
ignored by both retrofit designs is the presence of transverse beams, which would render them
difficult or impossible to apply.

571 Pantelides et al. (2008) tested cruciform interior specimen without joint shear reinforcement 572 and insufficient bottom beam bar anchorage. A CFRP retrofit developed to address both deficiencies, 573 consists of sheets along the bottom of the beam, U- wraps for anchorage and shear strengthening of 574 the beams and two CFRP layers at an angle of 60° in the joint region, in the style of X-shaped retrofits 575 in Fig.1, as well as column confinement. The retrofit amounts can be adjusted depending on the 576 relative strengths of the members, hence joints with stronger beams, assumed to fail in joint shear, 577 and joints with stronger columns, predicted to fail in beam bar anchorage are tested. Ductile 578 behaviour is achieved for all retrofitted specimens, but greater strength improvements are obtained for 579 joints with joint shear deficiency (+55% vs +50%).

580 A capacity design CFRP retrofit promoting beam hinging failure in pre-1970's corner joints 581 with slabs under bi-directional loading is proposed by Engindeniz et al. (2008a). Extensive yielding of 582 column bars, joint shear cracking, and beam rebar bond-slip are to be prevented by a two-step 583 retrofit, first adding column rebars and then applying CFRP wrapping to columns, L-shaped CFRP 584 around the joint and U-shaped CFRP around the beams, as shown in Fig. 4 (b), in amounts designed 585 to ACI-440 guidelines (2002b). An extra layer of FRP is applied to the joint for a specimen with half 586 the concrete strength. The proposed multi-objective retrofit is successful in preventing joint shear 587 failure, achieving a shear capacity compliant with modern codes. The specimen with stronger 588 concrete achieves a strong increase in strength (+36%) with a ductile beam hinging failure 589 characterised by high energy dissipation. The FRP ruptures at 94% of its ultimate strain rather than 590 debonding, indicating that the anchorage consisting of full FRP wrapping only is sufficient. The 591 specimen with lower concrete grade, due to reduced bond with the beam bars, experiences a 592 reduction in strength (-5%), significant reduction in stiffness (44% lower) and strongly reduced energy 593 dissipation (37% lower), indicating a more severe and impractical retrofit, including concrete 594 replacement may be needed for very weak concrete.

595 A performance-based FRP retrofit approach to provide a ductile failure is proposed by 596 Akguzel et al. (2011; 2009). An initial test of the principle on two-dimensional interior and exterior

joints without slab uses a simple system of vertical and horizontal CFRP sheets (Pampanin et al.
2004). The retrofit successfully alters the hierarchy of strength, but debonding reduces its
effectiveness, as no anchorage is provided.

A similar retrofit using GFRP is used on three-dimensional corner joint without slabs under bidirectional loading (Akguzel and Pampanin 2007). With bidirectional loading, increased joint damage and faster strength degradation is observed for the control specimen. The GFRP retrofit protects the joint from excessive damage but is less effective than in an equivalent 2D specimen (+61% vs +75% strength increase). Complete relocation of damage from the joint to the end of the beam GFRP sheet is observed for both geometries, resulting in a more ductile and dissipative mechanism.

In additional tests (Akguzel and Pampanin 2010), the effect of the amount of horizontal FRP (1 or 2
layers) in the beam and joint, having one stirrup in the joint, and the effect of bidirectional or
unidirectional lateral loading are investigated. A reduced shear strain in the joint at maximum drift
from 0.76%, with one layer, to 0.25%, with two layers of horizontal FRP, is observed, which is in line
with earlier results (Antonopoulos and Triantafillou 2003). In turn, the joint shear stud improves the
retrofit effectiveness, maintaining the integrity of the core and preventing buckling of column bars.
There is 10% additional stiffness degradation per drift level for 3D compared to 2D specimens.

614 An effort combining the GFRP retrofit, shown in Fig. 4 (c), with selective weakening of slabs is tested 615 on a corner joint specimen with slab and transverse beam and compared to an equivalent specimen 616 without slab (Akguzel and Pampanin 2012b). Selective weakening consists of reducing the 617 contribution of the slab to the hogging capacity and stiffness of the beams, by cutting rebars around 618 the beam perimeter near the joint. This intervention aims to promote a beam hinging mechanism, 619 while protecting the assembly from brittle joint or column failure with GFRP sheets, anchored with fan-620 shaped FRP dowels through the slab. An increase in strength of 28%, slightly lower than for the 621 specimen without slab (+34%), is obtained. Despite the weakening cuts, beam hinging is however not 622 achieved for the specimen with slab. Detachment of column FRP causes ultimate failure at the 623 column/joint interface, while the retrofit is effective in transferring damage to the beams for the 624 specimen without slab. Anchorage of the joint and beam FRP with dowels was however effective in 625 preventing debonding.

626 The idea of controlling the hierarchy of strength between columns and beams prior to 627 retrofitting using selective-weakening is also adopted by Pohoryles et al. (2018) for retrofitting interior 628 beam-column joints with slab and transverse beams (see Fig. 4 (d)). The retrofit uses rolled strands of 629 CFRP sheet at the corners of the columns for continuous flexural strengthening, similar to Shiohara et 630 al. (2009), but tested under more realistic loading conditions. Joint shear strengthening is applied by 631 means of two CFRP strands applied through holes drilled through the transverse beams, which 632 presents an effort to tackle joint shear strengthening in the presence of transverse beams realistically. 633 Furthermore, next to selective weakening of the slab, continuous beam strengthening with fan-shaped FRP is applied to the beams to achieve plastic hinge relocation away from the beam/joint interface. A 634 635 combination of FRP anchor fans and metallic anchors is used to prevent any potential debonding 636 mechanisms. Overall, a behaviour close to a specimen designed to Eurocode 8 (CEN 2004) is 637 achieved, with transfer of damage to the expected plastic hinge zone and a significant strength 638 (+38%) and ductility increase (+90%). The same retrofit applied to a 2D cruciform specimen, however 639 achieves an even stronger strength increase (+50%), but reduced ductility (-46%), again highlighting 640 the importance of testing realistic specimen geometries (Pohoryles 2017).

641 In this section, retrofits with multiple strengthening objectives were discussed. The aim of 642 these retrofits follows the principle of capacity design. To protect the joint, in most analysed retrofits, 643 horizontal FRP, placed as U-shapes for exterior joints or L-shapes for corner joints is used. Pohoryles 644 et al. (2018) use horizontal FRP strands passed through holes drilled into the transverse beams, 645 hence explicitly considering practical considerations. Only Pantelides et al. (2008) used the X-shaped 646 configuration. Column confinement and flexural strengthening are then applied, with vertical sheets of 647 FRP applied on the column faces being the most common solution. In the presence of slabs or 648 transverse beams, this is however highly impractical. Pampanin et al. (2012) suggest the use of L-649 shaped FRP, while Pohoryles et al. (2018) use vertical FRP strands passed through pre-drilled holes. 650 Finally beam bar anchorage or plastic hinge relocation in the beams is the last objective in order to 651 ensure a ductile hinging mechanism. For this generally sheets or strips of FRP placed along the beam 652 or L-shapes are used. The proposed schemes all highlight the potential of FRP retrofits to achieve 653 multiple objectives, with increases in lateral capacity and change in failure mechanism observed. The study by Engindeniz et al. (2008) highlights the higher effect of retrofits for larger concrete strengths. 654 655 while Pampanin et al. (2012) and Pohoryles et al. (2018) show that 2D specimens tested without slab

display a larger retrofit effectiveness. Overall, the two latter retrofit schemes can be deemed most
realistic for practical applications, as geometric constraints of slab and transverse beams are explicitly
addressed, and the retrofit schemes are shown to be effective in eliminating brittle failure, while
ensuring large increases in strength.

660 Analysis and Discussion

661 The state-of-the-art review presented in this paper highlights the vast number of experimental efforts 662 conducted in the area of seismic strengthening using FRP. With this comes a wide variety of retrofit configurations, test set-ups and specimen geometries that may all affect the retrofit effectiveness. To 663 664 understand the existing data better and assess any gaps in the literature in terms of experimental 665 data, the statistics on the configuration of the 260 tested specimens in the database are shown in 666 Table 5. The variety of FRP configurations proposed in the literature are in direct relation to the type 667 of pre-1970's structural design deficiencies identified for beam-column joints. The statistics related to 668 the studied deficiencies are presented in Fig. 5. Note that an overlap of two or more deficiencies is 669 common in the presented studies and the percentage values are hence not in direct relation to the 670 number of specimens tested.

It can be observed that most specimens (37%) are joint shear deficient (JTR) and retrofit layouts often only focus on this deficiency. With this in mind, it is important to indicate a heavy bias in specimen geometry in Table 5, with 82% of tested specimens presenting no transverse beams or slab, hence making the joint accessible for this type of shear strengthening. This joint geometry may however be seen as overly simplified and hides potential practical issues with the proposed retrofit solutions.

676 Assessment of joint shear strengthening equations

As most papers in this review focus on joint shear strengthening, it is attempted to compare the experimental results to design equations from three FRP strengthening guidelines: Eurocode 8 – Part 3 (CEN 2006), CNR-DT 200.R1 (CNR 2013) and ACI-400.2R08 (ACI 2008). For the purpose of this analysis, shear retrofitted specimens from the database that failed in joint shear failure are selected. This results in a total of 41 specimens summarised in Table 6. Of the chosen specimens, most are external joints (74%), but also internal (16%) and corner joints (10%) are included. Nearly half of the specimens used for analysis are full-scale (46%), with the rest mainly being 2/3 scale (44%). Finally,

the type of retrofits is also diverse, with most specimens used for this analysis retrofitted using Ushaped FRP (54%), and X-shaped and L-shaped (both 17%) also being commonly used. Strips are only used in the three specimens tested by Antonopoulos and Triantafillou. The selected specimens are hence diverse in geometry, size and retrofit layout. This gives this study a wider outlook on the issue of joint shear strengthening equations, as it allows testing the equations on a larger dataset compared to previous efforts (Bousselham, 2010).

First, to determine the experimental shear capacities of joints, the published values of ultimate force acting on beam or column (depending on the experimental set-up) are used. The horizontal shear acting at the centre of the joint, V_{jh} , is evaluated by equilibrium considerations. More details on this can be found elsewhere (Pohoryles and Rossetto 2014). The FRP contribution to the joint shear resistance of the tested joints is then calculated by deducting the capacity of the respective control specimen. Specimens for which a reduction in strength (e.g. heavily pre-damaged repair specimens) are excluded from this assessment.

697 The increase in capacity due to FRP is strengthening is then calculated for all 41 specimens for the 698 three guidelines. In Eurocode 8-Part 3 (EC8), the contribution of FRP to the shear capacity can be 699 calculated according to equations A.22 and A.23. It is suggested that FRP is placed with fibres in the 700 direction of hoops (cl. 4.4.1(1)). In the Italian CNR DT-200.R1 (CNR) guidelines, for the shear 701 strengthening of RC joints, clause 4.7.2.1.4 (1) applies, which states that FRP fibres should be placed 702 in the direction of principal tensile stresses, rather than the hoop direction, as suggested by EC8 and 703 ACI. Finally, for ACI 440.2R-08 (ACI) equations from section 11.4 for shear strengthening of 704 rectangular members are taken. Equation 11-3 allows calculation of the contribution of FRP to the 705 shear force, which is however limited by the maximum given by equation 11-11.

The equations for the strengthened joint shear capacity (V*t*) in the three guidelines are summarised in Table 7. Note that the symbols and equations are slightly adapted in order to ease comparison. The factor β corresponds to the angle of the fibres to the axis of the column, while θ is the angle of the principal stress in the joint (assumed to be the angle of the diagonal) to the axis of the column. In the case of strips used for retrofitting, *w_t* is the width of FRP strip, measured in the orthogonal direction to the fibres, and *s_t* the spacing between the strips of FRP (equal to *w_t* for sheets). The ratio of *w_t* to *s_t* simplifies to 1 in the case of continuous shear strengthening is applied. In terms of the retrofit

dimensions, d_{fv} is the breadth of applied sheet and t_i is its total thickness. The geometry of the joint is represented by d, the effective depth and b_j the width of the joint. The partial reduction factor γ_{Rd} in the CNR equation is ignored for the purpose of this comparison.

As it can be observed, the equations are similar in nature, albeit different in their details. In particular, the EC8 and CNR guidelines include the angle of principle stress, which is not foreseen in the ACI guidelines. Between the CNR and EC8 guidelines, the EC8 equation includes an additional sin β factor, as well as a separate equation for FRP strengthening that is not applied in a U-shape, but only side bonded. The main differences between the guidelines lie however in the calculation in the effective strength, *f*_{fe} of the FRP, in turn related to the effective strain developed in the material.

The ACI equations calculate effective strain based on the geometry of the retrofit, i.e. for fully

wrapped members clause 11-6a is used, which limits the FRP strain to a maximum of 75% of the

rupture strain, while for U-wraps or side-bonded FRP, a bond reduction factor κ_{ν} , is first calculated.

This factor takes into account the compressive strength of concrete, f_c , the active bond length of FRP,

as well as the material stiffness and thickness of the FRP strengthening.

727 In EC8, in turn, the effective strain is calculated based on cl.A.4.2(5) for fully wrapped or properly 728 anchored jackets, cl.A.4.4.2(6) for U-wraps, and cl.A.4.4.2(7) for side-bonded sheets and strips. The 729 effectiveness of anchorage is hence explicitly addressed in the guideline. Other factors in the 730 equations affecting effective strain include concrete tensile strength, FRP ultimate tensile strength, the 731 corner radius of the element, as well as an effective bond length. In the CNR guidelines, cl. 4.3.3.2 732 used to calculate the effective strain is similar to the EC8 equation and also dependent on FRP 733 shape, material strength, bond length and corner radius. Anchorage is explicitly addressed in clause 734 4.7.2.1.4 (1)). Finally, it is stated that the maximum tensile strain of FRP wraps in RC joint 735 strengthening shall not exceed 4‰, which is in line with ACI.

The results of the analysis of the joint shear strengthening guideline equations are displayed in Table 6 for each specimen and summarised in Fig. 6. Looking at the results, it can be observed that all three guidelines achieve a relatively accurate prediction of the strengthened capacity. The CNR guidelines are found to be slightly conservative leading to an average ratio of 0.82 of the predicted to experimental results. The equation also delivers the lowest variance (0.52). The EC8 equation gives the best results on average (ratio of 1.08), albeit slightly non-conservative. The coefficient of variance

is the highest for the EC8 equation (0.85), indicating a larger spread of predicted capacities. The ACI
guidelines, are found to overestimate the contribution of the FRP by 53%, with a relatively high
variance (0.78).

Looking at the equations in the guidelines, it would appear that a main reason for the CNR and EC8 guidelines performing better can be found in the use of the angle of fibres and the angle of principal stress, which allows for a more accurate calculation of the contribution of the fibres in tension. Ignoring this, leads to an overestimation of the FRP contribution as seen for the ACI equations. Furthermore, evaluating the bond strength of FRP to concrete, by explicitly taking into account anchorage in EC8, permits a relatively accurate estimation of the retrofitted joint shear capacity without overestimating the contribution of FRP.

752 Factors affecting FRP retrofits

753 The evaluation of design guidelines highlights the need for further improvements in order to enable a 754 wider applicability of full FRP retrofits of RC structures. To improve guidelines and design better 755 retrofits, it is important to understand which parameters affect the retrofits the most. As shown in this 756 review, next to joint shear strengthening, more elaborate retrofit layouts dealing with additional 757 deficiencies are also found in the literature. Looking at in Fig. 5., inadequate beam bar anchorage 758 (BA) or a weak-column/strong-beam mechanisms (WC/SB) are examples of these (12% and 11% of 759 tested specimens, respectively). To fully capture the effectiveness of these types of retrofit and their 760 practical implementation, more complex (and realistic) sub-assemblies geometries may be required, 761 as the presence of transverse beams or slabs affects the accessibility of the areas to be retrofitted, as 762 well as the relative hierarchy of strengths.

763 The full database is further analysed to assess the influence of scale and geometry, as well as of pre-764 damage, on the increase in strength and ductility of retrofitted specimens (Table 8). The analysis 765 confirms general observations from the review, namely that specimens without slab and transverse 766 beams (2D) present a higher effectiveness of FRP retrofit in terms of average strength increase 767 (+44% compared to +27%). Also, in terms of ductility, 2D specimens achieve a much larger 768 improvement (+63%) then 3D specimens (+38%). The effect of scaled specimens is less pronounced 769 for strength increase (+42% compared to +39% in full-scale) and reversed for ductility (+55% 770 compared to +63% in full-scale specimens). Finally, repairs of pre-damaged specimens are not, as

one would expect, less effective in increasing the load capacity than retrofits of existing structures
(+41% compared to +39%). This may be attributed to the replacement of damaged concrete by
stronger mortar. As a decrease in initial stiffness for repaired specimens is commonly observed, in
terms of ductility, repaired specimens present however a lower increase (+36% compared to +67%).

The geometry, scale and pre-damage of test specimens are hence crucial aspects affecting retrofit effectiveness. Based on the wealth of experimental knowledge developed by the scientific community, the authors of this review determined other factors that have an important effect on the effectiveness of the FRP retrofit, defined in terms of increase in lateral load capacity or ductility. These factors are summarised and discussed concisely in this section.

780 • **FRP** material: CFRP having higher strength, but lower ultimate strain than GFRP or BFRP, 781 the choice of FRP material often falls to the first, with 80% of all specimens retrofitted with 782 CFRP and the rest mostly with GFRP (18%) and limited studies on BFRP (<3%). Due to the 783 properties of the material, higher strength increases are observed for the stronger CFRP, but 784 lower ductility (Mukherjee and Joshi 2005). As a result of higher ultimate strain in GFRP, 785 using more layers of GFRP can achieve a higher increase in ductility (Antonopoulos and 786 Triantafillou 2003). Similar effects are observed for BFRP (Yu et al. 2016). A variety of 787 factors, including cost, anchorage solution and retrofit layout may however also favour one 788 material over the other.

Amount of FRP: A variety of retrofits solutions are tested in the literature, with number of
 layers varying from one up to ten layers (Tsonos 2008). The amount of FRP layers used
 affects the retrofit effectiveness, the increase in strength is however not proportional to the
 increase in FRP layers (e.g.: Antonopoulos and Triantafillou 2003).

Angle of fibres: For shear strengthening of joints or beams, in particular, a more effective
 retrofit is achieved by orientating the fibres in the angle of principal stress, compared to the
 use of horizontal and vertical sheets. For joints, placing sheets diagonally is however often
 difficult or impossible due to the presence of slab or transverse beams. Using horizontal
 sheets with bi-directional fibres at 45° is an option, however (currently) leads to more
 expensive solutions.

Strips vs sheets: In terms of lateral load capacity, sheets seem more effective than strips.
 This is however based on limited evidence and may be mainly attributed to weaker bond
 characteristics of the latter (Antonopoulos and Triantafillou 2003).

802 Anchorage: In all major design guidelines FRP debonding is recognised as a brittle failure • mechanism, which leads to an abrupt loss of capacity in retrofitted members. Adequate FRP 803 804 development lengths and reduced levels of FRP design strain are hence generally recommended to prevent it. In the literature, premature failure through FRP delamination is 805 806 observed when the FRP sheets are not anchored adequately, which can cause the retrofit to 807 be ineffective (e.g.: Ghobarah and Said 2002). Lack of anchorage affects retrofits with FRP 808 strips more than when using sheets of FRP (Antonopoulos and Triantafillou 2003). Using 809 transversal sheets of FRP to wrap the main strengthening has shown little effect on its own (Akguzel and Pampanin 2010). Other anchorage solutions are hence recommended: 810

811 812 FRP dowels or fan-shaped anchors through slabs or beams (Akguzel et al. 2011; 2012a).

813 o Steel plates and rods (Al-Salloum and Almusallam 2007; Ghobarah and Said 2002).

814 o Steel angles connected between beams and column (El-Amoury and Ghobarah 2002;
815 Lee et al. 2010).

816 o U-shaped steel anchors (El-Amoury and Ghobarah 2002).

817 Fig. 7 displays the percentage of retrofits in the literature providing anchorage and the type of anchorage provided. Anchorage using strips or sheets of FRP are labelled as 'FRP', while 818 819 FRP dowel or fan-shaped anchors are labelled 'FRP-anchors'. Steel anchors using plates, rods or bolts are simply labelled 'steel'. It can be seen that a majority of studies (65%) 820 821 recognises the need to provide anchorage. This anchorage is mainly provided by FRP Uwrapping or full-wrapping ('FRP'), while only 18% of studies employ steel devices or FRP 822 823 fan/dowel anchors. In a review of anchorage systems metallic anchors are shown to be the 824 most effective method (Kalfat et al. 2013), with FRP-based anchors however being less invasive, more practical to apply and often providing a similar level of anchorage. FRP fan-825 826 shaped anchors may enhance the effective strain in FRP sheets to 75% of the rupture strain

827 (Bournas et al. 2015), which is significantly larger than typical design strain values in828 guidelines.

829 Continuous strengthening: For effective flexural strengthening of columns, an adequate 830 bond length is required, which needs continuity through the joint. For cruciform specimen, this is addressed by simply applying FRP sheets or NSM rods continuously from the superior to 831 832 the inferior column (Antonopoulos and Triantafillou 2003; Mahini and Ronagh 2011). With a 833 slab or transverse beams, this would however not be achievable for all sides of the column (Prota et al. 2004; Shiohara et al. 2009) without the need of cutting or drilling through adjacent 834 835 members. To date, only Pohoryles et al. (2018) addressed this issue explicitly. Similarly, the 836 continuity and anchorage through the joints for longitudinal FRP sheets in the beams is only 837 addressed by anchorage with U-wraps (Akguzel et al. 2011; Al-Salloum and Almusallam 838 2007) or by bending the sheets in an L-shape onto the columns (Ghobarah and El-Amoury 2005). 839

840 **Pre-damage**: Generally, the extent of pre-damage affects the effectiveness of FRP repairs. • While moderately pre-damaged specimens can be repaired to achieve similar performance to 841 retrofitted counter-parts, for severely pre-damaged joints, the strength may not be recovered 842 843 (Agarwal et al. 2014; Beydokhti and Shariatmadar 2016). The analysis of the database 844 highlights that on average for the many repaired specimens in the database, however, the 845 effectiveness in terms of strength increase resembles that of retrofits closely (+39% vs +41%). Only in terms of ductility a large difference is found due to the reduced stiffness of 846 pre-damaged specimens. 847

Concrete strength: The distribution of concrete strengths of the experimental specimens
 presented in the literature is shown in Fig. 8. The majority of specimens (65%) have a
 concrete with a mean strength (*f_{cm}*) of 20-30 MPa. While most studies aim to replicate pre 1970s structures which often have lower concrete strengths, these are difficult to produce
 nowadays with modern materials. In limited studies with very weak concrete, it is observed
 that FRP retrofits may not be viable without partial replacement of existing concrete (D'Ayala
 et al. 2003; Engindeniz et al. 2008a).

855 Axial load: The effectiveness of FRP retrofits is generally found to be strongly affected by the 856 level of axial load. Higher levels of axial load lead to a stronger enhancement of ductility and 857 strength for retrofitted specimens (Antonopoulos and Triantafillou 2003; Prota et al. 2004). 858 Using an axial load varying with lateral load, however, leads to an unfavourable effect on the 859 retrofit (Akguzel and Pampanin 2010, 2012b). In most experiments reported in the literature. one constant value of normalised axial load is used, a majority of which using values from 0.1 860 861 to 0.2, as shown in Fig. 9. This value can be deemed typical for lower storey columns. It is worth noting that no axial load is applied in nearly 15% of studies. 862

Effect of scale: The effectiveness of retrofits is seen to be reduced for full-scale specimens
 compared to smaller specimens (e.g.: Choudhury et al. 2013). Non-conservative results may
 hence be reported when basing outcomes on experiments on scaled specimens. Looking at
 the statistics on specimens tested in the literature (Table 5), this effect of scale may affect a
 large number of experiments, as 59% of specimens are less than full-scale. Indeed, the
 analysis of the database has highlighted that scaled specimens have a larger improvement in
 strength increase, however this effect is less clear then anticipated.

870 • 3D vs 2D set-up: Again looking at Table 5, most of the present studies test two-dimensional 871 (2D) specimens without slab or transverse beams (82%). The presence of framing members, 872 but also bi-directional loading, are however seen to reduce the effectiveness of FRP retrofits (Akguzel et al. 2011). Slabs contributing to the moment capacity of the beams can influence 873 the failure mechanism of sub-assemblies (Kam et al. 2010; Park and Mosalam 2013), often 874 promoting unwanted column hinging mechanisms despite retrofit (Akguzel and Pampanin 875 876 2012b). In practical terms, the placement of sheets and location of anchorage are also 877 affected by the real geometry of the structure, with slabs and transverse beams typically 878 being present for most moment-resisting frame (MRF) buildings (Genesio et al. 2010; Lehman 879 et al. 2004; Pampanin et al. 2002). Regarding the tested joint geometries, as shown in Table 880 5, most retrofitted specimens are exterior joints (54%), which generally are more critical, as, 881 unlike interior joints, these are not confined from four sides and are subjected to lower axial 882 forces. Still, there is also a large interest in interior joints, corresponding to 32% of the tested 883 specimens. Looking at limited experimental evidence for full frames (Akguzel et al. 2011;

Gallo et al. 2012), it appears that retrofitting exterior joints only may not be sufficient to
improve the global structural behaviour, hence the need for investigating the retrofit of interior
joints too.

887 The analysis of the database together with a discussion of the factors affecting the effectiveness of 888 FRP retrofits highlights the need for assessing the practical engineering aspects of the retrofits. From 889 the reviewed studies, many ignore the presence of practical challenges to the retrofit application. 890 When these factors are included, it becomes clear that full FRP retrofits of structures will need to 891 include additional drilling of holes through slabs or walls in order to enable transversal FRP 892 strengthening or anchorage of longitudinal FRP sheets. An often-cited benefit of FRP strengthening 893 compared to conventional retrofitting (e.g. concrete jacketing) is the reduced labour, reduced time of 894 the intervention and being less invasive. In order to fully confirm this, it is however important to test 895 proposed retrofitting schemes on full-scale three-dimensional set-ups that accurately reflect real 896 structures. Ignoring these effects will lead to an over-estimation of the effect of FRP retrofits, but also 897 lead to easier applications and anchorage of FRP, hence not giving a correct picture on the practical 898 applicability of the scheme.

899 Conclusions

A review of the state-of-the-art of FRP retrofitting of beam-column joint subassemblies presents
 numerous successful implementations that address various retrofit objectives. A detailed analysis of
 the proposed schemes and a compilation of a database of experiments allows important conclusions
 to be drawn from this review.

A plethora of successful implementations of joint shear strengthening schemes have been presented. While sheets in the angle of principal stress are shown to be most effective, horizontal strengthening with FRP sheets is deemed most realistic. To address other design deficiencies of pre-1970's RC frames, such as the low flexural capacity of weak columns, a range of implementations are reported in the literature. At beam-column joints, continuous flexural strengthening of columns through slabs and transverse beams is proposed, with FRP anchors deemed most appropriate, as they can be passed through small holes at the corners of the columns.

911 Beam plastic hinge relocation (PHR) is another application of FRP that shows potential in improving 912 the seismic behaviour of structures. Studies show that strengthening the beam in the proximity of the 913 joint allows relocation of damage and plastic hinge formation away from the joint. This protects the 914 joint from yield penetration and improves the dissipative behaviour of the specimen further. 915 Anchorage of the FRP sheets at the beam/joint interface is a practical challenge that is not sufficiently 916 addressed.

Any type of anchorage solution is deemed to be critical in ensuring FRP retrofit effectiveness. Most
studies consider anchorage; however, looking at the database of experiments, simple FRP wrapping
is the most common application, which is not always effective. A combination of FRP anchor fans and
metallic anchors is shown to be most successful.

921 With regards to the assessment of joint shear strengthening equations in design guidelines, it is found 922 that the ACI guidelines overestimate the FRP contribution. While the CNR and EC8 equations give a 923 better fit to experimental data, the variance in the results is still relatively large and hence require 924 improvement. Even though the database encompasses a wide range of joint types and geometries, 925 there is still a need for more data to validate and improve code provisions. As the aim of most retrofit 926 interventions is to avoid brittle failure mechanisms and promote ductile failure, there is a lack of 927 experiments on retrofitted specimens that fail in joint shear. While this demonstrates the effectiveness 928 of joint shear retrofitting with FRP, it reduces the available data for validating or developing design 929 equations. One conclusion from this review is hence the need for experiments with purposefully 930 understrengthened retrofitted specimens to obtain further experimental data on the contribution of 931 FRP to the joint shear strength.

Finally, despite the large number of conducted studies, a strong bias towards scaled cruciform test specimens is observed. The ease of construction and testing, as well as their less complex behaviour, have led to increased testing of these types of joints. This review, however, highlights the important effect of realistic size, loading and geometry of test specimens on FRP retrofit effectiveness. Without these elements, the joint region is more accessible and practical challenges for the schemes, including placement of anchors, are ignored. Future studies should hence consider more realistic test set-ups to explicitly address potential practical issues in the retrofit design.

939 Acknowledgments

940 The presented research is part of the Challenging RISK project funded by EPSRC (EP/K022377/1).

941 **Bibliography**

- 942 ACI (American Concrete Institute). (2002a). "Recommendations for Design of Beam-Column 943 Connections in Monolithic Reinforced Concrete Structures". ACI 352R-02, Farmington Hills, 944 Mich.
- 945 ACI (American Concrete Institute). (2002b). "Guide for the design and construction of externally 946 bonded FRP systems for strengthening concrete structures", ACI 440.2R-02, Farmington 947 Hills, Mich.
- 948 ACI (American Concrete Institute), (2008), "Guide for the design and construction of externally 949 bonded FRP systems for strengthening concrete structures". ACI 440.2R-08, Farmington 950 Hills, Mich.
- 951 Agarwal, P., Gupta, A., and Angadi, R. G. (2014). "Effect of FRP wrapping on axial behavior of 952 concrete and cyclic behavior of external RC beam column joints." KSCE Journal of Civil 953 Engineering, 18(2), 566-573.
- Akguzel, U., and Pampanin, S. (2007). "Experimental behaviour of exterior beam-column joint 954 955 subassemblies retrofitted using GFRP composites." Proceedings of the 2007 NZSEE Conference, Palmerston North, New Zealand. 956
- Akguzel, U., and Pampanin, S. (2009). "Analytical model for shear strengthening of RC beam-column 957 958 joints using composite materials." Proceedings of the 2009 NZSEE Conference, Christchurch, 959 New Zealand.
- Akguzel, U., and Pampanin, S. (2010). "Effects of Variation of Axial Load and Bidirectional Loading on 960 Seismic Performance of GFRP Retrofitted Reinforced Concrete Exterior Beam-Column 961 962 Joints." Journal of Composites for Construction, 14(1), 94–104.
- Akguzel, U., and Pampanin, S. (2012a). "Assessment and Design Procedure for the Seismic Retrofit 963 of Reinforced Concrete Beam-Column Joints using FRP Composite Materials." Journal of 964 965 Composites for Construction, 16(1), 21-34.
- 966 Akguzel, U., and Pampanin, S. (2012b). "Recent Developments in Seismic Strengthening of RC Beam-Column Joints with FRP Materials." Proceedings of the 15th world conference on 967 968 earthquake engineering, Lisbon, Portugal,
- 969 Akguzel, U., Quintana Gallo, P., and Pampanin, S. (2011). "Seismic strengthening of a non-ductile RC 970 frame structure using GFRP sheets." Proceedings of the Ninth Pacific Conference on 971 Earthquake Engineering, Auckland, New Zealand.
- 972 Al-Salloum, Y., and Almusallam, T. (2007). "Seismic Response of Interior RC Beam-Column Joints 973 Upgraded with FRP Sheets. I: Experimental Study." Journal of Composites for Construction, 974 11(6), 575-589.
- 975 Al-Salloum, Y. A., Siddigui, N. A., Elsanadedy, H. M., Abadel, A. A., and Agel, M. A. (2011). "Textile-976 reinforced mortar versus FRP as strengthening material for seismically deficient RC beam-977 column joints." Journal of Composites for Construction, 15(6), 920-933.
- 978 Alsayed, S. H., Al-Salloum, Y. A., Almusallam, T. H., and Siddigui, N. A. (2010). "Seismic Response 979 of FRP-Upgraded Exterior RC Beam-Column Joints." Journal of Composites for Construction, 980 14(2), 195-208.
- Antonopoulos, C., and Triantafillou, T. (2003). "Experimental Investigation of FRP-Strengthened RC 981 982 Beam-Column Joints." Journal of Composites for Construction, 7(1), 39-49.
- Attari, N., Amziane, S., and Chemrouk, M. (2010). "Efficiency of Beam-Column Joint Strengthened by 983 FRP Laminates." Advanced Composite Materials, 19(2), 171-183. 984
- Beydokhti, E. Z., and Shariatmadar, H. (2016). "Strengthening and rehabilitation of exterior RC beam-985 column joints using carbon-FRP jacketing." Materials and Structures, 1–17. Bournas, D. A., Pavese, A., and Tizani, W. (2015). "Tensile capacity of FRP anchors in connecting 986
- 987 988 FRP and TRM sheets to concrete." Engineering Structures, 82, 72-81.
- 989 Bousselham, A. (2010). "State of Research on Seismic Retrofit of RC Beam-Column Joints with 990 Externally Bonded FRP." Journal of Composites for Construction, 14(1), 49-61.
- 991 CEN (European Committee for Standardization). (2004). "Design of structures for earthquake 992 resistance. General rules, seismic actions and rules for buildings, part 1." Eurocode 8, 993 Brussels.
- 994 CEN (European Committee for Standardization). (2006). "Design of structures for earthquake 995 resistance. Assessment and retrofitting of buildings, part 3" Eurocode 8, Brussels.

- 996 CNR (National Research Centre). (2013). "Guide for the Design and Construction of Externally
 997 Bonded FRP Systems for Strengthening Existing Structures Materials, RC and PC
 998 structures, masonry structures." *DT 200.R1*, Rome.
- 999 Choudhury, A. M., Deb, S. K., and Dutta, A. (2013). "Study on size effect of fibre reinforced polymer
 1000 retrofitted reinforced concrete beam–column connections under cyclic loading." Canadian
 1001 Journal of Civil Engineering, 40(4), 353–360.
- 1002 CSA (Canadian Standards Association). (1994). "Design of Concrete Structures". CSA A23.3,
 1003 Rexdale, Ontario, Canada.
- D'Ayala, D., Penford, A., and Valentini, S. (2003). "Use of FRP fabric for strengthening of reinforced
 concrete beam-column joints." Proceedings of the 10th International conference on structural
 faults and repair, London.
- 1007 Del Vecchio, C., Di Ludovico, M., Balsamo, A., Prota, A., Manfredi, G., and Dolce, M. (2014).
 1008 "Experimental Investigation of Exterior RC Beam-Column Joints Retrofitted with FRP
 1009 Systems." Journal of Composites for Construction, 18(4).
- Del Vecchio, C., Di Ludovico, M., Balsamo, A., and Prota, A. (2018). "Seismic Retrofit of Real Beam Column Joints Using Fiber-Reinforced Cement Composites." Journal of Structural
 Engineering, 144(5), 04018026.
- 1013 El-Amoury, T., and Ghobarah, A. (2002). "Seismic rehabilitation of beam–column joint using GFRP 1014 sheets." Engineering Structures, 24(11), 1397–1407.
- 1015 Engindeniz, M., Kahn, L. F., and Zureick, A.-H. (2005). "Repair and strengthening of reinforced 1016 concrete beam-column joints: State of the art." ACI structural journal, 102(2), 187–197.
- Engindeniz, M., Kahn, L. F., and Zureick, A. (2008a). "Pre-1970 RC corner beam-column-slab joints:
 Seismic adequacy and upgradability with CFRP composites." Proceedings of the 14th World
 Conf. on Earthquake Engineering, Beijing, China, 12–17.
- Engindeniz, M., Kahn, L. F., and Zureick, A. H. (2008b). "Performance of an RC corner beam-column joint severely damaged under bidirectional loading and rehabilitated with FRP composites."
 Seismic Strengthening of Concrete Buildings Using FRP Composites, 19–36.
- Eslami, A., Dalalbashi, A., and Ronagh, H. R. (2013). "On the effect of plastic hinge relocation in RC
 buildings using CFRP." Composites Part B: Engineering, 52, 350–361.
- Eslami, A., and Ronagh, H. (2014). "Experimental Investigation of an Appropriate Anchorage System for Flange-Bonded Carbon Fiber–Reinforced Polymers in Retrofitted RC Beam–Column Joints." Journal of Composites for Construction, 18(4), 04013056.
- Fardis, M. N. (2009). Seismic Design, Assessment and Retrofitting of Concrete Buildings: based on
 EN-Eurocode 8. Springer.
- Faleschini, F., Gonzalez-Libreros, J., Zanini, M.A., Hofer, L., Sneed, L., Pellegrino, C. (2019). "Repair
 of severely-damaged RC exterior beam-column joints with FRP and FRCM composites. "
 Composite Structures, 207, 352–363.
- fib (International Federation for Structural Concrete). (2006). "Retrofitting of concrete structures by
 externally bonded FRPs, with emphasis on seismic applications." *Bulletin 35*, Lausanne,
 Switzerland.
- Gallo, P. Q., Akguzel, U., Pampanin, S., Carr, A. J., and Bonelli, P. (2012). "Shake table tests of nonductile RC frames retrofitted with GFRP laminates in beam column joints and selective weakening in floor slabs." Proceedings of the 2012 NZSEE Conference, Christchurch, NZ.
- 1039Garcia, R., Jemaa, Y., Helal, Y., Guadagnini, M., and Pilakoutas, K. (2014). "Seismic Strengthening of1040Severely Damaged Beam-Column RC Joints Using CFRP." Journal of Composites for1041Construction, 18(2), 04013048.
- Garcia, R., Jemaa, Y., Helal, Y., Pilakoutas, K., and Guadagnini, M. (2012). "FRP Strengthening of Seismically Deficient Full-Scale RC Beam-Column Joints." Proceedings of the 15th world conference on earthquake engineering, Lisbon, Portugal.
- Genesio, G., Eligehausen, R., Sharma, A., and Pampanin, S. (2010). "Experimental and numerical study towards a deformation-based seismic assessment of substandard exterior RC beam-column joints." Proceedings of the 7th Int. Conf. on Fracture Mechanics of Concrete and Concrete Structures (FRAMCOS-7), Jeju, Korea.
- Ghobarah, A., and El-Amoury, T. (2005). "Seismic Rehabilitation of Deficient Exterior Concrete Frame
 Joints." Journal of Composites for Construction, 9(5), 408–416.
- 1051 Ghobarah, A., and Said, A. (2002). "Shear strengthening of beam-column joints." Engineering 1052 Structures, 24(7), 881–888.
- Hadi, M. N. S., and Tran, T. M. (2014). "Retrofitting nonseismically detailed exterior beam–column
 joints using concrete covers together with CFRP jacket." Construction and Building Materials,
 63, 161–173.

- Hadi, M. N. S., and Tran, T. M. (2016). "Seismic rehabilitation of reinforced concrete beam–column joints by bonding with concrete covers and wrapping with FRP composites." Materials and Structures, 49(1–2), 467–485.
- Hasan, Q. F., Tekeli, H., and Demir, F. (2016). "NSM Rebar and CFRP laminate strengthening for RC columns subjected to cyclic loading." Construction and Building Materials, 119, 21–30.
- 1061 Ilki, A., Bedirhanoglu, I., and Kumbasar, N. (2011). "Behavior of FRP-Retrofitted Joints Built with Plain 1062 Bars and Low-Strength Concrete." Journal of Composites for Construction, 15(3), 312–326.
- Ji, G., Li, G., and Alaywan, W. (2013). "A new fire resistant FRP for externally bonded concrete
 repair." Construction and Building Materials, 42, 87–96.
- Kalfat, R., Al-Mahaidi, R., and Smith, S. (2013). "Anchorage Devices Used to Improve the
 Performance of Reinforced Concrete Beams Retrofitted with FRP Composites: State-of-the Art Review." Journal of Composites for Construction, 17(1), 14–33.
- Kam, W. Y., Quintana Gallo, P., Akguzel, U., and Pampanin, S. (2010). "Influence of slab on the seismic response of sub-standard detailed exterior reinforced concrete beam column joints." Porceedings of the 9th US National and 10th Canadian Conference on Earthquake
 Engineering: Reaching Beyond Borders, Toronto, Canada.
- Kappos, A., and Penelis, G. G. (1996). Earthquake Resistant Concrete Structures. CRC Press,
 London/New York.
- Karayannis, C. G., and Sirkelis, G. M. (2008). "Strengthening and rehabilitation of RC beam–column
 joints using carbon-FRP jacketing and epoxy resin injection." Earthquake Engineering &
 Structural Dynamics, 37(5), 769–790.
- Lee, W. T., Chiou, Y. J., and Shih, M. H. (2010). "Reinforced concrete beam–column joint strengthened with carbon fiber reinforced polymer." Composite Structures, 92(1), 48–60.
- Lehman, D., Stanton, J., Anderson, M., Alire, D., and Walker, S. (2004). "Seismic performance of
 older beam-column joints." Proc. 13th world conf. earthquake engineering, Vancouver,
 Canada.
- Le-Trung, K., Lee, K., Lee, J., Lee, D. H., and Woo, S. (2010). "Experimental study of RC beam–
 column joints strengthened using CFRP composites." Composites Part B: Engineering, 41(1),
 76–85.
- Mahini, S. S., and Ronagh, H. R. (2007). "A new method for improving ductility in existing RC ordinary
 moment resisting frames using FRPs." Asian Journal of Civil Engineering (Building and
 Housing), 8(6), 581–595.
- 1088 Mahini, S. S., and Ronagh, H. R. (2011). "Web-bonded FRPs for relocation of plastic hinges away 1089 from the column face in exterior RC joints." Composite Structures, 93(10), 2460–2472.
- Mosallam, A. (2000). "Strength and ductility of reinforced concrete moment frame connections
 strengthened with quasi-isotropic laminates." Composites Part B: Engineering, 31(6–7), 481–
 497.
- 1093 Mukherjee, A., and Joshi, M. (2005). "FRPC reinforced concrete beam-column joints under cyclic 1094 excitation." Composite Structures, 70(2), 185–199.
- Pampanin, S., Bolognini, D., Pavese, A., Magenes, G., and Calvi, G. M. (2004). "Multi-level seismic rehabilitation of existing frame systems and subassemblies using FRP composites."
 Proceedings of the 2nd International Conference on FRP Composites in Civil Engineering, Adelaide, Australia.
- Pampanin, S., Calvi, G. M., and Moratti, M. (2002). "Seismic Behavior of R.C. Beam-Column Joints
 Designed for Gravity Only." Proceedings of the 12th European Conference on Earthquake
 Engineering, Elsevier Science Ltd., London, U.K., Paper 726.
- Pantelides, C., Okahashi, Y., and Reaveley, L. (2008). "Seismic Rehabilitation of Reinforced Concrete
 Frame Interior Beam-Column Joints with FRP Composites." Journal of Composites for
 Construction, 12(4), 435–445.
- Park, S., and Mosalam, K. M. (2013). "Experimental Investigation of Nonductile RC Corner Beam Column Joints with Floor Slabs." Journal of Structural Engineering, 139(1), 1–14.
- Pohoryles, D. A., and Rossetto, T. (2014). "A critical evaluation of current design guidelines for the
 seismic retrofit of beam-column joints with FRP." Proceedings of the 2nd Second European
 Conference on Earthquake Engineering and Seismology, Istanbul, Turkey.
- Pohoryles, D. A. (2017). "Realistic FRP Seismic Strengthening Schemes For Interior Reinforced
 Concrete Beam-Column Joints." PhD, University College London, London, U.K.
- Pohoryles, D. A., Melo, J., Rossetto, T., D'Ayala, D., and Varum, H. (2018). "Experimental comparison of novel CFRP retrofit schemes for realistic full-scale RC beam-column joints." Journal of Composites for Construction, 22(5), 04018027.

- Prota, A., Nanni, A., Manfredi, G., and Cosenza, E. (2004). "Selective upgrade of underdesigned reinforced concrete beam-column joints using carbon fiber-reinforced polymers." ACI structural journal, 101(5), 699–707.
- 1118 Realfonzo, R., Napoli, A., and Pinilla, J. G. R. (2014). "Cyclic behavior of RC beam-column joints 1119 strengthened with FRP systems." *Construction and Building Materials*, 54, 282–297.
- 1120 Russo, G., and Pauletta, M. (2012). "Seismic Behavior of Exterior Beam-Column Connections with 1121 Plain Bars and Effects of Upgrade." ACI Structural Journal, 109(2), 225.
- Said, A. M., and Nehdi, M. L. (2004). "Use of FRP for RC Frames in Seismic Zones: Part I. Evaluation
 of FRP Beam-Column Joint Rehabilitation Techniques." Applied Composite Materials, 11(4),
 205–226.
- Shiohara, H., Kusuhara, F., Tajiri, S., and Fukuyama, H. (2009). "Seismic Retrofit of Reinforced
 Concrete Beam-Column Joints with CFRP Composites." Improving the Seismic Performance
 of Existing Buildings and Other Structures, American Society of Civil Engineers, San
 Francisco, California, 1449–1459.
- 1129 Thermou, G. E., and Elnashai, A. S. (2006). "Seismic retrofit schemes for RC structures and local-1130 global consequences." Progress in Structural Engineering and Materials, 8(1), 1–15.
- Tsonos, A. G. (2008). "Effectiveness of CFRP-jackets and RC-jackets in post-earthquake and pre earthquake retrofitting of beam–column subassemblages." Engineering Structures, 30(3),
 777–793.
- Yu, J., Shang, X., and Lu, Z. (2016). "Efficiency of Externally Bonded L-Shaped FRP Laminates in
 Strengthening Reinforced-Concrete Interior Beam-Column Joints." Journal of Composites for
 Construction, 20(3), 04015064.
- 1137 Yurdakul, Ö., and Avşar, Ö. (2015). "Structural repairing of damaged reinforced concrete beam-1138 column assemblies with CFRPs." Structural Engineering and Mechanics, 54(3), 521–543.

1140

1141 List of Figures

1142 Fig. 1. Schematics of typical joint shear retrofit schemes found in the literature.

1143 Fig. 2. Schematics of retrofit schemes for columns through beam-column joint sub-assemblies found

1144 in the literature (Note: dashed line represents embedded NSM rods; JS = Joint strengthening, C =

1145 confinement).

- 1146 Fig. 3. Schematics of retrofit schemes for beams in beam-column joint sub-assemblies found in the
- 1147 literature. (Note: C = confinement, L = L-shape, U = U-shape, emb. = embedment; CL = centre line).

1148 Fig. 4. Schematics of multi-objective retrofit schemes for beam-column joint sub-assemblies found in

the literature: (a) El-Amoury and Ghobarah (2002) and Alsayed et al. (2010); (b) Engindeniz et al.

1150 (2008); (c) Akguzel and Pampanin (2012) and (d) Pohoryles et al (2018). (Note: JS = Joint

1151 strengthening, C = confinement, BA = beam bar anchorage, U = U-shape, F= full wrap, anch =

anchor).

1153 Fig. 5. Type of design deficiency analysed for tested specimens reported in the literature.

- 1154 Fig. 6. Average ratio of the predicted (V_{F,pred}) to experimental (V_{F,exp}) FRP contribution to shear
- 1155 strength of joints for the three design guidelines.

1156 Fig. 7. Statistics of employed anchorage solutions in the experimental database.

- 1157 Fig. 8. Statistics of mean concrete strengths (f_{cm}) of tested specimens in the experimental database.
- 1158 Fig. 9. Statistics of normalised axial load in the experimental database.

1160 Table 1. Representative strength increases obtained due to the joint shear retrofits.

Author	Main parameter	U-shaped	T-shaped	X-shaped	Multi-axial
Ghobarah and Said (2002)		+18%		+11%	
Antonopoulos and	CFRP		+41%		
Triantafillou (2003)	GFRP		+45%		
Karayannis and Sirkelis (2008)		+88%			
Le-Trung et al. (2010)			+32%	+17%	
Poplfonzo et al. (2014)	Unanchored	+23%			
Realion20 et al. (2014)	Anchored	+99%			
Hadi and Tran (2014, 2016)	Rounded	+140%			
Agarwal et al. (2014)	Repaired	-32%			
Garcia et al. (2012, 2014)	Repaired	+69%			
Yurdakul and Avsar (2015)	Repaired			-25%	
Faleschini et al. (2019)	Repaired	-34%		-30%	
	Moderate	+6%			
Beydokhti and	damage	1070			
Shariatmadar (2016)	Near-Collapse	-19%			
	Collapse	-15%			
Del Vecchio et al. (2014)	Corner				+49%
llki et al. (2011)	Corner				+18%
$D'A_{vale}$ at al. (2002)	Retrofit		+17.3%	+92.6%	
	Repair		-5.2%	+2%	
Lee et al. (2010)	Interior		+36%		

1162 Table 2. Representative strength increases obtained due to the retrofit schemes for columns in beam-

1163 column joint sub-assemblies (JS = joint shear strengthening).

Author	Retrofit	Main	Strength
		parameter	increase
Yu et al	المعمد ما	CFRP	+26%
(2016)	L-snaped	BFRP	+11%
Prota et al.	NSM	Without JS	+62%
(2004	rods	With JS	+83%
Shiohara et al (2009)	FRP strands		+13%

1167 Table 3. Representative strength increases obtained due to the retrofit schemes for beams in beam-

1168 column joint sub-assemblies found in the literature.

1169

Author	Main parameter	L-shaped	Top and/or bottom strips	Web- bonded
Mukherjee and Joshi (2005)	GFRP CFRP	+99% +79%	+68 %	
Ghobarah and El- Amoury (2005)	Simple anchor	-11%		
	Well anchored	+40%		
Attari et al. (2010)		+44%	+24%	
Choudhury et al. (2013)	Full 2/3 1/3		+5% +22% +24%	
Mahini and Ronagh (2011)				+9%
Eslami and Ronagh (2014)	Short FRP Long FRP		+31% +45%	

- 1171 Table 4. Representative strength increases obtained using multi-objective retrofit schemes for beam-
- column joint sub-assemblies.
- 1173

Author	Main	Strength
	parameter	increase
El-Amoury and Ghobarah (2002)	- F	+52%
Alsayed et al. (2010)		+32%
Engindeniz et al.	Weak concrete	-5%
(2008)	Strong concrete	+36%
Akguzel and	No slab	+34%
Pampanin (2012)	With slab	+28%
Pohoryles et al	No slab	+50%
(2018)	With slab	+38%

1175 Table 5. Geometrical statistics of joints contained in database.

	Joint type			Contain	S	Scale				
	Number	Interior	Exterior	Corner	Slab	Trans. Bea	mFull	2/3	Half	1/3
Control	91	32%	54%	14%	18%	22%	44%	15%	14%	26%
Retrofitted	125	43%	47%	10%	12%	16%	37%	26%	14%	22%
Repaired	44	34%	61%	5%	32%	27%	48%	5%	27%	20%
Total	260	37%	52%	11%	18%	20%	41%	19%	16%	23%

	Experimental			ACI-440		EC8-3		CNR DT 200			
Specimen ¹	Geor	netry ²	Scale	FRP ³	V _{f,exp}	V _{f,ACI}	<u>Vf,ACI</u> Vf,exp	V _{f,EC8}	<u>Vf.EC8</u> Vf,exp	V _{f,CNR}	<u>Vf.CNR</u> Vf,exp
Gho(T1)	Ext	2D	1	U	52.4	121.8	2.3	91.5	1.7	102.4	2.0
Gho(T2)	Ext	2D	1	Х	69.5	256.3	3.7	49.7	0.7	49.7	0.7
Gho(T1R)	Ext	2D	1	U	233.3	137.1	0.6	135.9	0.6	126.8	0.5
Gho(T4)	Ext	2D	2/3	ST	17.6	59.7	3.4	14.7	0.8	6.8	0.4
Gho(T9)	Ext	2D	2/3	ST	34.9	85.4	2.4	25.4	0.7	6.4	0.2
EI-(T0)	Ext	2D	2/3	ST	44.6	60.2	1.3	65.5	1.5	43.1	1.0
El-(TR2)	Ext	2D	2/3	U	45.0	87.5	1.9	48.5	1.1	35.1	0.8
Ant(C)	Ext	2D	2/3	U	70.2	125.4	1.8	76.3	1.1	52.0	0.7
Ant(C)	Ext	2D	2/3	U	74.1	111.9	1.5	76.0	1.0	51.8	0.7
Ant(S33)	Ext	2D	2/3	U	51.5	130.6	2.5	56.4	1.1	40.9	0.8
Ant(S63)	Ext	2D	2/3	U	89.6	126.8	1.4	77.2	0.9	52.7	0.6
Ant(S33L)	Ext	2D	2/3	U	91.0	130.0	1.4	127.9	1.4	93.9	1.0
Ant(F11)	Ext	2D	2/3	U	42.1	110.2	2.6	65.0	1.5	44.0	1.0
Ant(F22)	Ext	2D	2/3	U	48.6	78.6	1.6	47.1	1.0	31.7	0.7
Ant(F21)	Ext	2D	2/3	U	39.6	104.8	2.6	60.5	1.5	40.9	1.0
Ant(F12)	Ext	3D	2/3	L	34.2	37.0	1.1	23.3	0.7	15.8	0.5
Ant(F22A)	Ext	3D	2/3	L	18.0	37.9	2.1	16.5	0.9	14.2	0.8
Ant(F22W)	Int	2D	1	Х	443.2	590.4	1.3	135.2	0.3	141.1	0.3
Ant(F22in)	Int	2D	1	Х	344.7	590.4	1.7	167.6	0.5	183.0	0.5
Ant(GL)	Int	2D	1	Х	305.0	590.4	1.9	58.8	0.2	65.9	0.2
Ant(S-C)	Int	2D	1	Х	403.4	590.4	1.5	58.0	0.1	64.7	0.2
Ant(S-F22)	Int	2D	1	Х	452.6	590.4	1.3	69.0	0.2	80.9	0.2
Ant(T-C)	Ext	2D	1	U	141.3	263.0	1.9	129.6	0.9	105.5	0.7
Ant(T-F33)	Ext	2D	1	U	300.1	293.5	1.0	170.8	0.6	132.9	0.4
Ant(T-F22S2)	Ext	2D	1	U	314.2	297.7	0.9	172.3	0.5	134.6	0.4
Pro(L3)	Cor	3D	2/3	L	39.1	41.5	1.1	146.6	3.8	89.8	2.3
Pro(H2)	Cor	2D	2/3	U	32.4	54.3	1.7	50.3	1.6	41.4	1.3
Pro(H2U)	Cor	2D	2/3	U	51.2	52.6	1.0	49.2	1.0	40.5	0.8
Pro(H3)	Cor	3D	2/3	L	10.8	15.9	1.5	58.2	5.4	47.9	4.4
Pro(H4)	Ext	2D	1/2	U	75.7	94.7	1.2	51.2	0.7	39.9	0.5
Pro(M3)	Ext	2D	1/2	U	61.1	94.7	1.5	60.2	1.0	45.7	0.7
Al-(IC1)	Ext	3D	1	L	28.4	9.2	0.3	31.0	1.1	31.5	1.1
Al-(IR1)	Ext	3D	1	L	92.2	11.0	0.1	38.5	0.4	37.6	0.4
AI-(IC2)	Ext	3D	1	L	92.2	11.0	0.1	38.5	0.4	37.6	0.4
Tso(F1)	Ext	2D	1/2	Х	169.3	593.3	3.5	125.1	0.7	115.8	0.7
Kar(A2)	Ext	2D	1	U	62.0	87.4	1.4	114.7	1.8	76.5	1.2
Pan(24-1)	Ext	2D	1	U	158.8	43.7	0.3	145.2	0.9	84.8	0.5
Pan(24-2)	Ext	2D	1	U	165.2	43.7	0.3	145.2	0.9	84.8	0.5
Pan(R24-3)	Ext	2D	1	U	219.0	43.7	0.2	145.2	0.7	84.8	0.4
Pan(R24-4)	Int	2D	1	S	326.2	269.5	0.8	453.2	1.4	354.1	1.1

Table 6. Experimental versus predicted contributin to shear capacity for strenghtened specimens 1178

¹Specimen name based on: "First three letters of first author (Specimen)" ²Ext = External; Int = Internal; Cor = Corner Joint ³Shape of FRP joint retrofit: U=U-shape; L=L-shape; X=X-shape; ST=strip; S=Single sheet

1180 Table 7. Summary of the equations for evaluating joint shear strengthening

Guideline	Clause	Equation
Eurocode 8	A.22	$V_{f,EC8} = 0.9 \cdot d \cdot f_{fe} \cdot 2 \cdot t_f \cdot \left(\frac{w_f}{s_f}\right)^2 \cdot (\cot\theta + \cot\beta) \cdot \sin\beta \text{ (U-shaped)}$
– Part 3	A.23	$V_{f,EC8} = 0.9 \cdot d \cdot f_{fe} \cdot 2 \cdot t_f \cdot \frac{\sin \beta}{\sin \theta} \cdot \left(\frac{w_f}{s_f}\right)$ (side bonded)
CNR DT-200	4.19	$V_{f,CNR} = \frac{1}{\gamma_{Rd}} \cdot 0.9 \cdot d \cdot f_{fe} \cdot 2 \cdot t_f \cdot (\cot\theta + \cot\beta) \cdot \frac{w_f}{s_f}$
ACI 440.2R-08	11-3	$V_{f,ACI} = 2 \cdot t_f \cdot f_{fe} \cdot (\cot\beta + \cot\beta) \cdot d_{fv} \cdot \frac{w_f}{s_f}$
		with a maximum of (11-11): $V_S + V_f \le 0.66\sqrt{f_{cm}} \cdot b_j \cdot d$

1182 Table 8. Analysis of the literature database in terms of retrofit effectiveness.

	Geometry		Scale	Scale		Retrofit type	
	3D 2D Full Le		Less than full	Repair	Retrofit		
Average strength increase	27%	44%	39%	42%	39%	41%	
Average ductility increase	38%	63%	63%	55%	36%	67%	

-